

Aquaguard

Elastomeric acrylic waterproof coating for roofs



DESCRIPTION

Aquaguard is an acrylic based highly flexible, high performance elastomeric, waterproof coating for roofs and walls. Aquaguard is suitable for application on various construction substrates such as concrete, masonry, plaster and terrazzo tiles.

Aquaguard is available in variety of colours and ideally suited for external applications.

APPLICATIONS

Aquaguard is designed for use as:

- » Waterproof coating for sloped roofs and vertical walls.
- » Waterproof coating over existing terrazzo tiles.
- » Waterproof and protective coating over roof polyurethane foam.
- » Waterproofing and protection over bituminous waterproofing membranes and coatings.

ADVANTAGES

- » Elastomeric.
- » Single component, easy to apply.
- » Available in different colours.
- » UV stable and resistant.
- » Will not support fungus growth.
- » Easy maintenance.

METHOD OF USE

SURFACE PREPARATION

Surfaces to receive Aquaguard should be clean, sound, and free from oil, grease, dirt and loose particles. Substrate should be dry, with no standing water. Spalled surfaces, cracks and defected concrete should be repaired. New concrete substrate should be at least 14 days old.

PRIMING

Aquaguard is designed to be applied over well prepared substrates directly without a primer.

For extremely porous surfaces, it is recommended to dilute Aquaguard with water 1:1 and apply it as a primer coat @ 5 m²/ltr and allow it to dry.

For fairface concrete surfaces, roughening the surface before application is needed. Alternatively, if roughening is not possible, Repcoat Primer should be used

TECHNICAL PROPERTIES @ 25°C:

Appearance:	Thick liquid
Colour:	White, grey, beige (various)
Overcoating time:	Minimum 4 hr
Solid content:	
By weight	60 ± 2%
By volume	50 ± 2%
Specific gravity:	1.25 ± 0.05
Permeability to water: EN 1062-3	< 0.1 kg/m ² .h ^{0.5}
Adhesion strength: ASTM D4541	≥ 1.5 MPa @ 7 days
Tensile strength: ASTM D412	≥ 1.3 MPa @ 7 days
Elongation: ASTM D412, Die C	> 350% @ 2 mm dry thickness
Minimum application temperature:	5°C
VOC:	< 50 g/ltr

APPLICATION

Aquaguard can be applied by brush, roll, or airless spray machine. The first coat of Aquaguard should be applied at the rate of 2.5 m²/litre and allowed to cure for 4 - 12 hours (depending in the ambient temperature) before being overcoated with the second coat.

The second coat should be applied perpendicular to the first coat at the same rate above, and allowed to cure.

For heavy pedestrian traffic, it is recommended to use fibreglass scrim reinforcement, embedded firmly in the second coat while wet, and a third coat should be applied.

Note: Aquaguard should not be applied at ambient temperatures below 5°C and dropping. Aquaguard should not be applied on surfaces expected to suffer from rising dampness or relative humidity greater than 75%.

CLEANING

All tools should be washed and cleaned immediately after use with clean water.





Aquaguard

PACKAGING

Aquaguard is available in 16 litres (20 kg), 18 litres (22.5 kg) and 120 litres (150 kg) packs.

Aquaguard Primer is available in 5 litres (5 kg) and 25 litres (25 kg) packs.

COVERAGE

Approximately 0.40 litre/m² per coat (0.50 kg/m²) to achieve 200 micron dry film thickness.

STORAGE

Aquaguard has a shelf life of 18 months from date of manufacture if stored at temperatures between 5°C and 40°C.

If these conditions are exceeded, DCP Technical Department should be contacted for advise.

CAUTIONS

HEALTH AND SAFETY

As with all acrylic paints, care should be taken during use and storage to avoid contact with skin, eyes and mouth. Wear suitable protective clothing, gloves and eye/face protection.

Should accidental skin contact occur, remove immediately with plenty of clean water. If swallowed, seek medical attention immediately - do not induce vomiting.

For further information refer to the Material Safety Data Sheet.

FIRE

Aquaguard and Aquaguard Primer are nonflammable.

MORE FROM DON CONSTRUCTION PRODUCTS

A wide range of construction chemical products are manufactured by DCP which include:

- » Concrete admixtures.
- » Surface treatments
- » Grouts and anchors.
- » Concrete repair.
- » Flooring systems.
- » Protective coatings.
- » Sealants.
- » Waterproofing.
- » Adhesives.
- » Tile adhesives and grouts.
- » Building products.
- » Structural strengthening.



Note:

We endeavour to ensure that any information, advice or recommendation we may give in product literature is accurate and correct. However, because we have no control over where and how products are applied, we cannot accept any liability arising from the use of the products.