

Cemfair PF Method Statement

(One component polymer modified cementitious fairing coat and cosmetic repair mortar)

Section A : General Comments

General

- (i) Cemfair PF can be applied in a single application from feather edging to 3 mm.
- (ii) Cemfair PF shall be used when the ambient temperature is between 5°C and 50°C. Cold water should be used to prevent mixed materials temperature exceeding 32°C.
- (iii) The area to be repaired should be marked on the structure.

Equipment

It is suggested that the following list of equipment is adopted as a minimum requirement:

<i>Protective clothing</i>	:	<i>Protective overalls</i>
	:	<i>Good quality gloves and goggles</i>
<i>Equipment</i>	:	<i>Slow speed mixer fitted with large mixing paddle</i>
	:	<i>Graduated cylinder</i>
	:	<i>Clean empty drum (25 litre)</i>
	:	<i>Wooden and steel trowel</i>

Section B : Application

1.0 Surface Preparation

- 1.1 Clean the surface and remove any dust, loose particles, unsound materials and general curing compounds.

2.0 Priming

- 2.1 Thoroughly soak the substrate with clean water approximately one hour prior to applying the repair.
- 2.2 Remove all surface water leaving the substrate saturated surface dry.

3.0 Mixing

- 3.1 Dampen all surfaces of mixing equipment, removing any excess water.



expertise



quality



full range



- 3.2 Measure out the correct amount of clean, cool water (7.5 - 8.5 litre) dependent on application requirements) into a mixer that has been pre-dampened. Ensure any excess water is removed. To enhance the scratch resistance of Cemfair PF, an addition of Cempatch SBR is advisable. 1/2 of the total mixing water shall be replaced by Cempatch SBR.
- 3.3 With the machine in operation slowly add one full 25 kg bag of Cemfair PF to the water and mix continuously, for a minimum period of 3 - 5 minutes until fully homogeneous. Small quantities up to 5 kg, can be mixed by hand, Cemfair PF should be volume-batched. Add 3 volumes of the powder to 1 volume of water and mix vigorously until fully homogeneous. In case of addition of Cempatch SBR, add 6 volumes of Cemfair PF: 1 volume of Cempatch SBR: 1 volume of water.

4.0 Application

- 4.1 Apply the mixed Cemfair PF to the prepared surface using a steel trowel.
- 4.2 Cemfair PF should be allowed to partly set before final trowelling to a smooth finish. If a high quality finish is required, a small amount of water should be flicked on to the surface of Cemfair PF prior to final trowelling.

5.0 Curing

- 5.1 The cementitious fairing coat generally does not require curing. However, in adverse conditions (e.g. windy conditions or ambient temperatures above 30°C) supplementary curing with Setseal A or wet hessian with polyethylene should be considered.

Section B : Approval and variations

This method statement is offered by DCP as a 'standard proposal' for the application of **Cemfair PF**. It remains the responsibility of the Engineer to determine the correct method for any given application. Where alternative methods are to be used, these must be submitted to DCP for approval, in writing, prior to commencement of any work. DCP will not accept responsibility or liability for variations to the above method statement under any other condition.