

Cemfix TB

Thick bed, non-slip cementitious ceramic tile and stone adhesive for thicknesses up to 10 mm (Formerly known as Aylafix TB)



Description

Cemfix TB is a grey or white blend of cement, well graded aggregates and special additives that forms when mixed with water a good workable and non-slip tile adhesive excellent for fixing all types of ceramic tiles and stone on floors and walls up to 10 mm thickness with no need for previous leveling internally or externally.

The non-slip properties that characterized Cemfix TB makes it suitable to be applied vertically without sagging and with no need for using spacers for normal sized tiles.

Applications

- ▲ For permanent fixing of ceramic tiles and natural stone on irregular concrete and cement based substrates up to 10 mm thickness.
- ▲ Installing of natural stone and tiles with large thicknesses variation over all common construction substrates.
- ▲ Suitable for vertical wall applications.
- ▲ Suitable for internal and external applications.
- ▲ Can be used in wet or dry areas.
- ▲ Can be used with underfloor heating systems.
- ▲ On drywalls such as gypsum boards and plaster boards.

Advantages

- ▲ Specially designed to accommodate thick bed applications.
- ▲ Good bond strength.
- ▲ Easy to apply, non-sag with good workability.
- ▲ Ready mixed, just require requires the addition of water.

Limitations

Do not use for:

- ▲ Continuously submerged conditions.
- ▲ Tile over tile applications.
- ▲ Cases that require a rapid utilization for the surfaces.
- ▲ On metal, rubber, PVC, or wood substrates

Standards

Cemfix TB complies with the following standards:

- ▲ ISO 13007-1 and BS EN 12004 as a normal cementitious tile adhesive with slip resistance (C1T).

Technical Properties. W/P = 0.26:

Colour:	White or grey
Fresh wet density:	1.8 ± 0.1 g/m ³
Open time: ISO 13007-2.4.1	20 min
Pot life:	2 hr @ 25°C
Tensile adhesion strength in compliance with ISO 13007-2.4.4	
Initial bond @ 28 days	≥ 0.5 MPa
After heat exposure	≥ 0.5 MPa
After water immersion	≥ 0.5 MPa
After freeze/thaw cycles	≥ 0.5 MPa
Slip: ISO 13007-2.4.2	< 0.5 mm
VOC: ASTM D2369	< 10 g/ltr (complies with LEED)

- ▲ ANSI A118.1 for shear strength requirements.

Method of use

Substrate Preparation

All surfaces must be clean, dry and free from dust, oil, grease, paints or any loose material.

Concrete and cement based substrates must be sufficiently cured and dimensionally stable. Allow time for shrinkage and structural strain movements.

Gypsum boards, plaster boards, anhydrite screeds, or any highly absorbent cement based substrates such as hollow blocks and foam concrete must be sufficiently dry and free from dust. These substrates must be primed with Keybond 2000 diluted with water at a ratio of 1:2 by volume (1 part Keybond 2000 to 2 parts water).

Tiles should not be placed over expansion and contraction joints, these joints should be filled with a suitable flexible sealant from the DCP Flexseal range.



Cemfix TB

Mixing

To ensure proper mixing, a mechanically powered mixer or drill fitted with suitable paddle should be used.

5.0 - 5.4 litres of clean fresh water for each 20 kg bag (water/powder ratio of 0.25 - 0.27 by weight) should be added to a clean container. The powder is then added slowly to the water while mixing continuously at low speed (400 - 600 rpm).

Mixing time should be continued for 3 minutes until a uniform consistency and free of lumps mixture is obtained. Allow a slake time for 2 - 3 minutes, then remix for additional 1 minute without adding any more water

Application

- ▲ Apply a layer of the adhesive onto the substrate using the flat edge of the trowel.
- ▲ Comb the adhesive with a suitable notched trowel horizontally to achieve a bed thickness up to 10 mm.
- ▲ Place the tiles with firm pressure to ensure proper contact with the adhesive.
- ▲ It is always better to work in a manageable area that can be tiled within the open wet time of the adhesive.
- ▲ Leave the tiled surfaces for 24 hours before grouting.

Cleaning

All tools should be cleaned immediately after use fresh clean water. Hardened materials should be cleaned mechanically.

Remarks

- ▲ Do not apply at temperature below 2°C.
- ▲ For heavy traffic areas, it is good practice to back butter the tile back surfaces with the adhesive to ensure 100% coverage.
- ▲ For large format and heavy tiles where the weight of the tiles cannot be supported by the adhesive, the installation method shall follow a bottom-up approach, and If more than two rows of tiles are to be fixed simultaneously, the tiles are to be mechanically supported using temporary anchor nails in between tile gaps or by using inclined support stud.

For further information please contact your local DCP Representation Office.

Packaging

Cemfix TB is available in 20 kg bags.

Yield

2.8 m²/20 kg bag @ 5 mm thickness.

Storage

Cemfix TB has a shelf life of 12 months from date of manufacture if stored at temperatures between 2°C and 50°C.

If these conditions are exceeded, DCP Technical Department should be contacted for advice.

Cautions

Health and Safety

As Cemfix TB contains Portland cement and sand, Cemfix TB may cause irritation to skin or eyes.

In case of accidental contact with eyes, immediately flush with plenty of water for at least 10 minutes and seek medical advice if necessary.

For further information refer to the Material Safety Data Sheet.

Fire

Cemfix TB is nonflammable.

More from Don Construction Products

A wide range of construction chemical products are manufactured by DCP which include:

- ▲ Concrete admixtures.
- ▲ Surface treatments
- ▲ Grouts and anchors.
- ▲ Concrete repair.
- ▲ Flooring systems.
- ▲ Protective coatings.
- ▲ Sealants.
- ▲ Waterproofing.
- ▲ Adhesives.
- ▲ Tile adhesives and grouts.
- ▲ Building products.
- ▲ Structural strengthening.

Note:

We endeavour to ensure that any information, advice or recommendation we may give in product literature is accurate and correct. However, because we have no control over where and how products are applied, we cannot accept any liability arising from the use of the products.

