

Cemflow Topping

Industrial grade floor topping



DESCRIPTION

Cemflow Topping is a self-smoothing, dimensionally stable, and fast drying industrial grade floor topping designed for upgrading and renovating new and existing internal floors.

Cemflow Topping is supplied as a pre-blended dry powder designed for application between 5 mm to 20 mm (in one application) to provide a finished industrial floor. Typically, Cemflow Topping can be pumped up to 1500 m² per day. Coverage of 600 m² can be achieved when hand applied, dependent upon manpower and equipment used.

To ensure that the surface is fully sealed, it is recommended that Cemflow Topping is sealed with two coats of water based Strongcoat WD for a semi-matt finish and pigmentation if required. If a matt finish is preferred, it is recommended to seal the surface with Cemflow Sealer (see related data sheets for further details and chemical resistance tables).

APPLICATIONS

Cemflow Topping is suitable for use in a wide range of industrial environments such as warehouses, food processing plants etc. subjected to medium to heavy traffic. It is suitable for application onto a wide range of subfloor types, including; sand and cement screeds, concrete, terrazzo, granolithic, epoxy and polyurethane resins and waterproof membranes.

ADVANTAGES

- » Single component, requires only addition of water.
- » Fast setting.
- » Easy and fast application.
- » Excellent adhesion.
- » Excellent abrasion resistance
- » High coverage efficiency.
- » Low application thickness threshold.

METHOD OF USE

SUBSTRATE PREPARATION

Concrete and sand/cement screeds must be sound, dry and fully cured (not subject to shrinkage) and any laitance or surface treatments must be removed by mechanical means such as grit blasting.

The surface tensile strength of the substrate should be a minimum 1.5 N/mm². For uneven surfaces, apply Cemflow Base/Renovation to a minimum 5 mm to provide a smooth level surface, prior to the application of Cemflow Topping. (Please refer to relevant product Technical Data Sheets).

TECHNICAL PROPERTIES:

| | |
|---|---|
| Working time: | 20 – 30 min @ 20°C |
| Setting time: | 90 min @ 20°C |
| Foot traffic: | 3 hr |
| Light traffic: | 24 hr |
| Heavy traffic: | 3 days |
| Compressive strength: EN 13892-2 | > 20 N/mm ² @ 1 day > 30 N/mm ² @ 7 days > 40 N/mm ² @ 28 days |
| Flexural strength: EN 13892-2 | > 4 N/mm ² @ 1 day > 7 N/mm ² @ 7 days > 10 N/mm ² @ 28 days |
| Abrasion resistance: EN 13892-4 | AR0.5 |
| Slip resistance: EN 13036-4 | Dry > 60 Wet > 45 |
| Flow properties using 30 mm Ø x 50 mm flow ring: EN 12706 | 120 – 150 mm |
| Taber abrasion resistance: ASTM D4060 (1000 g, 1000 cycles) H22 wheel | < 7 grams |
| Application thickness: | 5 to 20 mm |

Don Construction Products Ltd.

Helions Bumpstead Road, Haverhill CB9
United Kingdom
info.uk@dcp-int.com; info@dcp-int.co.uk
www.dcp-int.com

Cemflow Topping

PRIMING

TO CONCRETE AND CEMENT SCREEDS

For application onto sand/cement screeds, concrete and other porous substrates, first seal the prepared surface by applying one coat of Cemflow Primer diluted with 3 parts potable water and allow to dry.

Apply a second coat of primer diluted 3:1 by the same method and allow thoroughly to dry. Depending on the porosity of the substrate a further coat may be required.

To confirm if this is necessary a small application area should be undertaken to ascertain the correct priming requirements. As an alternative, Strongcoat Primer may be used.

PRIMING WITH STRONGCOAT PRIMER

Apply one coat Strongcoat Primer and allow to cure. Apply 2nd coat and whilst still tack fully blind with DCP Aggregate at approximately 3 kg/m² until the surface is covered and no resin spots remain.

The rate of application is approximately 3 kg/m². Allow to dry fully overnight and remove excess aggregate before applying the Cemflow Topping.

TO IMPERVIOUS SURFACES

For application on to impervious surfaces, such as tiles, coatings or onto Strongcoat DPM (please read relevant product technical data sheet).

Apply Strongcoat Primer and whilst it is still tacky fully blind with DCP Coarse Aggregate at approximately 3 kg/m², until the surface is covered and no resin spots remain. Allow to dry fully overnight and remove excess aggregate before applying the Cemflow Topping.

MIXING

PUMP APPLICATION

Mix the powder and water according to the method recommended by the pump manufacturers. In the case of pumps having a continuous water feed adjust the rate of water flow until the mix is a smooth fluid, uniform grey liquid with no surface separation, producing a flow of approximately 130 mm using a 35cc flow ring.

HAND APPLICATION

Use a power-whisk fitted in a heavy-duty slow speed electric drill. Mix in the proportion of 25 kg of powder to 4.5 – 5.0 litres of potable water.

Pour the water into a suitably sized bucket and gradually add the powder while stirring, until a smooth, lump free consistency is achieved. The material should be mixed for a minimum of 3 minutes. Leave to stand for 2 - 3 minutes and mix briefly for 1 minute before applying.

APPLICATION

Pour or pump the mixed material onto the prepared surface and allow to attain a smooth finish. The use of a spiked roller will help eliminate entrapped air and smooth out flow lines.

Apply at a thickness between of 5 mm to 20 mm in one pass only. For the application of any seal coats, please refer to relevant Technical Data Sheets.

PRECAUTIONS

- » Do not place when the substrate temperature is below 10°C or when the ambient temperature is 10°C and falling. Protect from frost.
- » Do not exceed the maximum recommended water content and only use potable cold water.
- » This product is not recommended for external use or situations where water may come into direct contact with the cured material.
- » This product should not be applied to asphalt or bituminous surfaces.

Cemflow Topping

CLEANING

Wash tools with water immediately after use.

PACKAGING

25 kg paper sacks.

COVERAGE

A 25 kg pack of Cemflow Topping will cover approximately 3.0 m² at 5 mm thickness.

YIELD

A 25 kg pack using 5 litres of clean water will yield approximately 15 litres.

STORAGE

Protect from frost and store under dry warehouse conditions at a temperature between 10°C and 30°C.

SHELF LIFE

6 months in unopened bags and stored under good conditions.



Cemflow Topping

HEALTH AND SAFETY

Consult the appropriate Material Safety Data Sheet prior to using each product.

MORE FROM DON CONSTRUCTION PRODUCTS

A wide range of construction chemical products are manufactured by DCP which include:

- » Concrete admixtures.
- » Surface treatments
- » Grouts and anchors.
- » Concrete repair.
- » Flooring systems.
- » Protective coatings.
- » Sealants.
- » Waterproofing.
- » Adhesives.
- » Tile adhesives and grouts.
- » Building products.
- » Structural strengthening.

Don Construction Products Ltd.

Helions Bumpstead Road, Haverhill CB9
United Kingdom

info.uk@dcp-int.com; info@dcp-int.co.uk

www.dcp-int.com

Note:

We endeavour to ensure that any information, advice or recommendation we may give in product literature is accurate and correct. However, because we have no control over where and how products are applied, we cannot accept any liability arising from the use of the products.

www.dcp-int.com

DCP Building Excellence