

Cempatch Rapid Repair Mortar

Rapid hardening cementitious repair mortar



DESCRIPTION

Cempatch Rapid Repair Mortar is a pre-packed single component cementitious repair mortar suitable for repairing and making good internal floors, stairs and steps and for general repairs to cracks and holes.

APPLICATIONS

Cempatch Rapid Repair Mortar can be applied to rigid sound surfaces – sand/cement screed or concrete bases, asphalt, granolithic, terrazzo, ceramic and quarry tiles, epoxy and polyurethane coatings.

ADVANTAGES

- » Fast setting with high early strength development which facilitates quick return to service.
- » Easy to apply, single component, require only addition of water.
- » Exhibits good mechanical properties.
- » Suitable for vertical applications, No cracks or sagging.
- » Durable.
- » Cost effective.

STANDARDS

Cempatch Rapid Repair Mortar complies with the requirements of BS EN 13813, Class CT-C35-F4.

METHOD OF USE

SUBSTRATE PREPARATION

It is not usually necessary to prime absorbent surfaces. However, to ensure satisfactory bonding, the prepared surface should be dampened down to minimise suction. Ensure that the surface is in a saturated surface dry condition prior to application of Cempatch Rapid Repair Mortar, i.e. no visible surface water.

PRIMING

Absorbent surfaces should be dampened with clean water. Very absorbent surfaces must be primed with dilute Neoprene Primer.

Non absorbent surfaces must be primed with neat Neoprene Primer. The primer should be used in accordance with the instructions printed on the Product Data Sheet and must be allowed to dry before applying the repair mortar.

TECHNICAL PROPERTIES. W/P RATIO = 0.23:

Fresh wet density:	2.05 ± 0.10 g/cm ³
Working time:	10 - 15 min
Walk on hardness time:	20 - 30 min @ 20°C
Ready for overcoating after:	1½ hr @ 2 mm
Compressive strength: BS EN 13892-2	> 20 MPa @ 1 day > 30 MPa @ 7 days > 35 MPa @ 28 days
Flexural strength: BS EN 13892-2	> 2 MPa @ 1 day > 3 MPa @ 7 days > 4 MPa @ 28 days
Consumption per mm thickness:	1.65 kg/m ²
Application thickness:	
Unfilled	2 - 20 mm
Filled	20 - 50 mm

MIXING

To ensure proper mixing, a mechanically powered mixer or drill fitted with suitable paddle should be used. 4.6 – 5.5 litres of clean water should be added to clean container.

The powder is then added slowly to the water while mixing continuously with low speed mixer/drill (400 - 600 rpm). Mixing should be continued for 3 minutes until a uniform smooth, slump-free consistency is obtained. Only mix enough mortar that can be applied before the product begins to set (approx. 10 – 15 minutes).

Cempatch Rapid Repair Mortar can be applied up to a thickness of 20 mm. For increased economy, the mortar can be bulked out by adding up to an equal volume of graded aggregate. Small localised repairs over 20 mm, but not exceeding 50 mm, should be bulked out with an equal weight of graded aggregate.

The working time will be extended at low temperatures and reduced at higher temperatures.

Don Construction Products Ltd.

Helions Bumpstead Road, Haverhill CB9
United Kingdom
info.uk@dcp-int.com; info@dcp-int.co.uk
www.dcp-int.com



Cempatch Rapid Repair Mortar

PLACING AND FINISHING

For best results over large areas, apply the mortar with a steel trowel at a thickness of 2 – 3 mm. To produce a smooth repair surface ready to receive floor coverings, finish with a wet smoothing trowel before the mortar has fully set, i.e. 15 - 20 minutes.

To ensure a level surface when filling holes and cracks, trowel the mortar into the area and apply pressure to ensure the mortar covers the repair surface.

Fill the repair leaving the mortar proud of the surrounding area, then float or grind to the required level after approximately 20 minutes. Overcoating can commence after approximately 1½ hours at 20°C @ 2 mm.

CLEANING

All tools should be cleaned immediately after use with fresh clean water. Hardened materials should be cleaned mechanically.

PACKAGING

Cempatch Rapid Repair Mortar is available in 22 kg bags.

THICKNESSES AND SIZE LIMITATIONS

Unfilled Cempatch Rapid Repair Mortar can be applied at thicknesses between 2 - 20 mm.

Filled Cempatch Rapid Repair Mortar can be applied at thicknesses between 20 - 50 mm.

YIELD

Approximately 13.2 litre per 22 kg bag.

STORAGE

Cempatch Rapid Repair Mortar has a shelf life of 12 months from the date of manufacture if stored at temperatures between 2°C and 50°C.

If these conditions are exceeded, DCP Technical Department should be contacted for advise.

CAUTIONS

HEALTH AND SAFETY

Since Cempatch Rapid Repair Mortar contains Portland cement and sand, Cempatch Rapid Repair Mortar may cause irritation to skin or eyes.

In case of accidental contact with eyes, immediately flush with plenty of water for at least 10 minutes and seek medical advise.

For further information refer to the Material Safety Data Sheet.

FIRE

Cempatch Rapid Repair Mortar is nonflammable.

MORE FROM DON CONSTRUCTION PRODUCTS

A wide range of construction chemical products are manufactured by DCP which include:

- » Concrete admixtures.
- » Surface treatments
- » Grouts and anchors.
- » Concrete repair.
- » Flooring systems.
- » Protective coatings.
- » Sealants.
- » Waterproofing.
- » Adhesives.
- » Tile adhesives and grouts.
- » Building products.
- » Structural strengthening.

Don Construction Products Ltd.

Helions Bumpstead Road, Haverhill CB9

United Kingdom

info.uk@dcp-int.com; info@dcp-int.co.uk

www.dcp-int.com

Note:

We endeavour to ensure that any information, advice or recommendation we may give in product literature is accurate and correct. However, because we have no control over where and how products are applied, we cannot accept any liability arising from the use of the products.

www.dcp-int.com

DCP Building Excellence