

Cempatch SBR250

Liquid polymer bonding agent for cement containing mixes



DESCRIPTION

Cempatch SBR250 is a one component styrene butadiene rubber latex bonding agent. Cempatch SBR250 is designed to improve the physical properties of cement mixes and slurries.

APPLICATIONS

Cempatch SBR250 is ideally designed for use in the following applications:

- » Bonding of new to old concrete when used as a slurry coat.
- » To produce various traditional cement/sand adhesive mortars such as block mortar, plaster/render and tile adhesive.
- » To produce a mechanical key prior to rendering of various plaster mixes on concrete, brick and block surfaces.

ADVANTAGES

- » Successfully increases the bonding/adhesion of cement mixes.
- » Effective plasticiser giving improved workability and cohesion.
- » Improved mechanical and physical properties by increasing tensile, flexural and adhesive strengths.
- » Good freeze/thaw resistance.
- » Chloride free.
- » Non-toxic, can be used for concrete in contact with potable water.

STANDARDS

Cempatch SBR250 complies with:

- » ASTM C1059-99, Type 1, when tested in accordance with test method ASTM C1042.
- » ASTM C932, for bond strength.

METHOD OF USE

SUBSTRATE PREPARATION

The substrate should be sound, clean and free from contamination. Surface laitance should be removed by acid etching.

Exposed steel reinforcements should be grit blasted or wired brushed to a bright finish to insure it is clean of all surface contaminations.

TECHNICAL PROPERTIES @ 25°C:

Colour:	White
Specific gravity:	Around 1.0
Slant shear strength: ASTM C1042-99 Type I (dry)	≥ 5.0 MPa
Tensile bond strength: ASTM C932 (wet condition)	≥ 1250 KPa

For patch repair, cut back the edges of the repair areas to a minimum of 10 mm depth to avoid thin repair thicknesses. Presoak substrates with water prior to commencing the repair.

MIXING

In general, Cempatch SBR250 should be added and mixed with the clean water prior to dry materials for better dispersion.

1) As a bonding agent slurry:

The recommended mix to produce slurry consistency can be achieved by mixing 2 Cempatch SBR250 : 3 OPC cement by volume.

2) As a bonding and waterproofing additive for site mixed cement/sand adhesive mortar:

The following table shows the mix design proposed to improve the adhesion of traditional cement/sand mortars such as block mortar, plaster/render and tile adhesive.

Component	QTY by Volume
Cement	3
Sand	6
Water*	1 - 3
Cempatch SBR250	1

*Based on type of sand and humidity.



Cempatch SBR250

APPLICATION

1) As a bonding agent slurry:

Use a stiff brush to apply a thick coat to presoaked surfaces. Application of the subsequent render, mortar or screed should take place while the bond coat is still wet (tacky). DO NOT apply on dry bond coats. (If bond coat dries before subsequent application, roughen the dry coat before applying a further coat of Cempatch SBR250 slurry.)

2) As a bonding and waterproofing additive for site mixed cement/sand adhesive mortar:

Apply workable site mixed cement/sand adhesive mortar prepared with Cempatch SBR250 based on best practices method of application for purpose required.

CLEANING

All tools should be cleaned immediately after use with fresh clean water. Hardened materials should be cleaned mechanically.

PACKAGING

Cempatch SBR250 is available in 5 and 25 litre drums.

STORAGE

Cempatch SBR250 has a shelf life of 12 months from date of manufacture if stored at temperatures between 5°C and 35°C in closed packaging.

If these conditions are exceeded, DCP Technical Department should be contacted for advice.

CAUTIONS

HEALTH AND SAFETY

Cempatch SBR250 is nontoxic. Avoid skin and eye contact. Gloves and eye protection should be worn. The use of barrier cream is recommended on exposed areas of the skin.

In case of accidental contact with eyes, immediately flush with plenty of water for at least 10 minutes and seek medical advice.

For further information refer to the Material Safety Data Sheet.

FIRE

Cempatch SBR250 is nonflammable.

MORE FROM DON CONSTRUCTION PRODUCTS

A wide range of construction chemical products are manufactured by DCP which include:

- » Concrete admixtures.
- » Surface treatments
- » Grouts and anchors.
- » Concrete repair.
- » Flooring systems.
- » Protective coatings.
- » Sealants.
- » Waterproofing.
- » Adhesives.
- » Tile adhesives and grouts.
- » Building products.
- » Structural strengthening.

Note:

We endeavour to ensure that any information, advice or recommendation we may give in product literature is accurate and correct. However, because we have no control over where and how products are applied, we cannot accept any liability arising from the use of the products.