

Cempatch SE

One component high strength fiber reinforced cementitious repair mortar



DESCRIPTION

Cempatch SE is a one component fiber reinforced cementitious repair mortar. Cempatch SE is a blend of dry powders and selected aggregates when mixed with water produces a thixotropic mortar suitable for vertical and overhead application.

APPLICATIONS

- » Repair of all types of structural concrete where high strength and extremely low shrinkage properties are required.
- » For the repair of vertical and overhead elements.
- » As a repair mortar for all structural elements in buildings, water retaining structures, industrial plants, bridges, etc.

ADVANTAGES

- » Shrinkage controlled cementitious repair mortar.
- » Easy to apply, single component, requires only addition of water.
- » Extremely low permeability to water, providing excellent protection to steel reinforcements and host concrete.
- » Thixotropic properties allowing extra high build for vertical and overhead applications.
- » Suitable for internal and external application. Water vapor permeable.
- » Cost effective, hand applied no formwork is required..

METHOD OF USE

SUBSTRATE PREPARATION

All damaged and weak concrete should be cut back to reach sound concrete and/or to a minimum depth of at least 10 mm.

Corroded steel reinforcement should be grit blasted to remove all rust traces. In case of significant loss in the steel reinforcement cross section, the steel should be replaced. Remove all concrete form around exposed steel reinforcements by 10 mm thickness.

The perimeters of the repair area should be saw cut to a minimum depth of 10 mm. The prepared area should be cleaned thoroughly by brush and/or compressed air.

TECHNICAL PROPERTIES. W/P = 0.18:

Fresh wet density:	2.2 ± 0.05 g/cm ³
Compressive strength: ASTM C109/109M-02 EN 12190	≥ 45 MPa @ 28 days
Tensile strength: ASTM C307	≥ 2.5 MPa @ 28 days
Flexural strength: ASTM C348	≥ 6 MPa @ 28 days
Mixing ratio:	4.5 litre of water for 25 kg bag of Cempatch SE
Reaction to fire: EN 1504-3, Clause 5.5	Class A1
Chloride content: EN 1015-17	≤ 0.05%
Dangerous substances: EN 1504-3	Complies with 5.4
VOC: ASTM D2369	< 10 g/ltr

PRIMING

All grit blasted steel reinforcements should be primed within 2 - 4 hours with one or two coats of zinc rich epoxy coating Repcoat ZR.

Areas to be repaired with Cempatch SE should be soaked with clean water before applying the repair mortar. All excess water should be removed prior to applying Cempatch SE.

MIXING

To ensure proper mixing, a mechanically powered mixer or drill fitted with suitable paddle should be used. 4.5 litre of clean water should be added to clean container. The powder is then added slowly to the water while mixing continuously with low speed mixer/drill (400 - 600 rpm).

Mixing time should be continued for 5 minutes until a uniform consistency is obtained.

DCP Saudi Co.

Sulay, Industrial Area, Istanbul St., Riyadh
Industrial City 3, Jeddah
Saudi Arabia
info.saudi@dcp-int.com
www.dcp-int.com





Cempatch SE

PLACING AND FINISHING

Cempatch SE can be applied by trowel or hand. The mixed mortar should be applied using firm pressure to fully compact the mortar and ensure good adhesion with the steel reinforcement and substrate.

Finishing and leveling should be carried out initially by wooden or plastic float. Final finishing should be carried out using steel float.

CURING

As Cempatch SE is a cementitious based material, it should be cured in a similar method to concrete. Curing can be conducted by using Setseal A or by wet Hessian sheets covered with polyethylene sheets.

CLEANING

All tools should be cleaned immediately after application using fresh water. Hardened materials must be cleaned mechanically.

PACKAGING

Cempatch SE is available in 25 kg bags.

THICKNESSES AND SIZE LIMITATIONS

Cempatch SE can be applied in a single application for sections up to 30 mm thick in overhead applications and 50 mm thick in vertical applications. Thickness should not be less than 10 mm deep in all applications.

Cempatch SE repair area should not exceed 2.5 m² in single application.

YIELD

13.4 litre per 25 kg bag.

STORAGE

Cempatch SE has a shelf life of 12 months from date of manufacture if stored at temperatures between 2°C and 50°C in original unopened bags.

If these conditions are exceeded, DCP Technical Department should be contacted for advise.

CAUTIONS

HEALTH AND SAFETY

Cempatch SE may cause irritation on to skin or eyes. In case of accidental contact with eyes, immediately flush with plenty of water for at least 10 minutes and seek medical advise if necessary.

For further information refer to the Material Safety Data Sheet.

FIRE

Cempatch SE is nonflammable.

MORE FROM DON CONSTRUCTION PRODUCTS

A wide range of construction chemical products are manufactured by DCP which include:

- » Concrete admixtures.
- » Surface treatments
- » Grouts and anchors.
- » Concrete repair.
- » Flooring systems.
- » Protective coatings.
- » Sealants.
- » Waterproofing.
- » Adhesives.
- » Tile adhesives and grouts.
- » Building products.
- » Structural strengthening.

DCP Saudi Co.

Sulay, Industrial Area, Istanbul St., Riyadh
Industrial City 3, Jeddah
Saudi Arabia
info.saudi@dcp-int.com
www.dcp-int.com

Note:

We endeavour to ensure that any information, advice or recommendation we may give in product literature is accurate and correct. However, because we have no control over where and how products are applied, we cannot accept any liability arising from the use of the products.

www.dcp-int.com

DCP Building Excellence



04-0054-A-2023