

Donplast PC270A

High early strength, high range water reducing admixture for precast concrete
(Formerly known as Hyperplast PC270A)



Description

Donplast PC270A is a unique combination of the latest generation of polycarboxylate polymers specifically developed for the precast concrete industry coupling superior high range water reducing capabilities and early strength requirements.

Applications

- ▲ Precast / pre-stressed concrete.
- ▲ Increase productivity/ reduction in cycle time.
- ▲ Achieve high early strengths.
- ▲ Production of high strength and high-performance concrete.
- ▲ Production of high-quality concrete with improved durability and watertightness.

Advantages

- ▲ Optimizes cement utilization.
- ▲ Higher early and ultimate strengths.
- ▲ Improves the water impermeability characteristics of concrete mix.
- ▲ Increases the durability and resistance to aggressive atmospheric conditions.
- ▲ Improved finishability.
- ▲ Minimizes segregation and bleeding problems by improving the cohesion of concrete mixes.

Compatibility

Donplast PC270A is suitable to use with all types of Portland cement and cement replacement materials. Donplast PC270A should not be used in conjunction with other admixtures unless DCP's Technical Department approval is obtained.

Standards

Donplast PC270A complies with the requirements of Specification for Chemical Admixture for Concrete ASTM C494 as a Type A, E & F admixture, depending on dosage used.

Technical Properties @ 77°F (25°C):

Colour:	Light brown liquid
Specific gravity:	1.13 ± 0.03
pH:	5 - 7
Chloride content:	Chloride-free

Method of Use

Donplast PC270A should be added to the concrete with the mixing water to achieve optimum performance.

An automatic dispenser should be used to dispense the correct quantity of Donplast PC270A to the concrete mix.

Dosage

The recommended dosage of Donplast PC270A is 8 to 31 fl oz/100 lb (520 - 2,015 ml/100 kg) of cement or cementitious materials in the mix including GGBFS, PFA or micro-silica.

Representative trials should first be conducted to determine the optimum dosage of Donplast PC270A to meet the performance requirements by using the materials and conditions in actual use.

Effects of Over Dosage

Overdosage of Donplast PC270A will cause the following:

- ▲ Increase in workability.

Ultimate concrete strength will not be adversely affected and will generally be increased provided that proper concrete curing is maintained.

Cleaning

Clean Donplast PC270A with fresh cold water.

Donplast PC270A

Packaging

Donplast PC270A is available in 5 gal (19 litre) containers as well as 275 gal (1,041 litre) and 330 gal (1,249 litre) IBC totes. Bulk supply in tanker trucks is also available upon request.

Storage

Donplast PC270A has a shelf life of 12 months from date of manufacture if stored at temperatures between 35°F and 122°F (2°C and 50°C).

If these conditions are exceeded, contact DCP Technical Department for advice.

Cautions

Health and Safety

Donplast PC270A is not classified as a hazardous material. Donplast PC270A should not come into contact with skin and eyes.

In case of contact with eyes, immediately flush with plenty of water and seek medical attention.

For further information, refer to the Material Safety Data Sheet.

Fire

Donplast PC270A is nonflammable.

More from Don Construction Products

A wide range of construction chemical products are manufactured by DCP which include:

- ▲ Concrete admixtures.
- ▲ Surface treatments
- ▲ Grouts and anchors.
- ▲ Concrete repair.
- ▲ Flooring systems.
- ▲ Protective coatings.
- ▲ Sealants.
- ▲ Waterproofing.
- ▲ Adhesives.
- ▲ Tile adhesives and grouts.
- ▲ Building products.
- ▲ Structural strengthening.

Don Construction Products Inc.
2826 Lineberger Industrial Dr.
Lancaster, SC 2970
USA

Note:

We endeavour to ensure that any information, advice or recommendation we may give in product literature is accurate and correct. However, because we have no control over where and how products are applied, we cannot accept any liability arising from the use of the products.

