

## EVA-CON Method Statement (Evaporation control compound for concrete)

### Section A : General Comments

#### Equipment

It is suggested that the following list of equipment is adopted as a minimum requirement:

<i>Protective clothing</i>	:	<i>Good quality gloves, goggles and face mask</i>
<i>Mixing equipment</i>	:	<i>Spray nozzle</i>

### Section B : Application

#### 1.0 Dilution

1.1 Mix 1 volume of the material with 10 volumes of clean cool water until a uniform solution is obtained.

*Note: Stir the material before dilution.*

1.2 **Immediately** and after bull floating, spray EVA-Con.

1.3 The spray nozzle should be held approximately 450 mm from the concrete surfaces.

#### 2.0 Cleaning

2.1 Tools and equipment (especially spraying nozzle) should be cleaned with soaped water when wet.

2.2 Dried EVA-CON should be removed with **DCP Solvent**.

### Section C : Approval and variations

This method statement is offered by DCP as a 'standard proposal' for the application of **EVA-CON**. It remains the responsibility of the Engineer to determine the correct method for any given application. Where alternative methods are to be used, these must be submitted to DCP for approval, in writing, prior to commencement of any work. DCP will not accept responsibility or liability for variations to the above method statement under any other condition.

