

Flo-Grout EP280

High strength fast flow epoxy resin grout



Description

Flo-Grout EP280 is a three component, high strength, free fast flowing, epoxy resin grout. Flo-Grout EP280 is suitable for grouting gaps with thicknesses between 10 - 40 mm at ambient temperatures between 10 to 40°C.

Applications

Flo-Grout EP280 is ideally designed for use in the following applications:

- ▲ Machine base plates.
- ▲ Heavy crane rails.
- ▲ Pile top waterproofing.
- ▲ Bearing plinths.
- ▲ High speed turbines.
- ▲ Grouting areas where occasional chemical spillage may occur.

Advantages

- ▲ Resistant to dynamic loading.
- ▲ Non-shrink and low creep characteristics under continuous loading.
- ▲ Exceptionally high compressive, flexural and tensile strengths.
- ▲ Extremely dense.
- ▲ Exceptional bond to concrete and steel surfaces.
- ▲ Good chemical resistance.
- ▲ High early strength development allowing for rapid installation.

Standards

Flo-Grout EP280 complies with EN 1504, Part 3, Class R4 as concrete structural and non-structural repair material (based on epoxy resin).

Method of Use

Substrate Preparation

The Substrate should be sound, clean and free from contamination. Surface laitance should be removed by scabbling or grit blasting.

Steel surfaces should be grit blasted to remove all rust and scale. Concrete surfaces should be dry.

Holes drilled for anchor bolts should be thoroughly cleaned from dust and loose debris using suitable brush or compressed air.

Mixing

To ensure proper mixing, a mechanically powered mixer or drill fitted with suitable paddle should be used.

The entire content of the Hardener pack should be added to the Base pack. Care should be taken to ensure that the bottom and the product sides are thoroughly scraped and used. Mix the two components for 2 minutes. The filler should be gradually added while mixing. Mixing should continue for 3 minutes or until a uniform consistency obtained.

Placing and Finishing

Under Base plate:

Enough materials should be available to achieve continuous fill and to complete the work. Pouring of the mixed grout should be started from one side only to avoid air entrapment.

To obtain maximum flow distance, a side shutter feed 100 mm height should be erected and used to build the required head. At 100 mm of head, a flow distance of 500 mm and 1800 mm can be achieved at gap thicknesses of 10 mm to 40 mm respectively @ 25°C ambient temperatures.

Formwork:

As the mixed grout possesses high fluid characteristics, all formwork and shutters should be water tight. This can be achieved by sealing underneath the formwork and at the joints by using an appropriate mastic.

Notes:

- ▲ If application is done under high temperatures, care should be done because the working time will be reduced significantly.
- ▲ To reduce the effect of this problem, try to store the unmixed materials in a cool environment, avoiding the direct sunlight. Also, try not to make the application in the middle of the day or direct sunlight.



Flo-Grout EP280



Property	EN 1504-3, Class R4 requirements	Test results
Compressive strength: EN 12190:1991 ASTM C579	≥ 45 MPa @ 7 days	≥ 90 MPa @ 7 days
Adhesive bond: EN 1542:1999	≥ 2.0 MPa	≥ 4 MPa
Restrained shrinkage: EN 12617-4:2002	≥ 2.0 MPa	≥ 4 MPa
Chloride ion content: EN 1015-17:2000	≤ 0.05%	0%
Capillary absorption: EN 13057:2002	≤ 0.5 kg/m ² . h ^{-0.5}	≤ 3 x 10 ⁻³ kg/m ² . h ^{-0.5}
Flexural strength: ASTM C580	-	≥ 28 MPa
Tensile strength: ASTM C307	-	≥ 12 MPa
Peak exothermic temperature: ASTM D2471	-	47°C @40°C
Working time:	-	100 - 130 min @25°C
VOC: ASTM D2369	-	< 10 g/ltr (complies with LEED)

Cleaning

All tools should be cleaned immediately after finishing using a suitable epoxy thinner. Hardened materials should be cleaned mechanically.

Packaging

Flo-Grout EP280 is available in 20 kg packs.

Thicknesses and Size Limitations

Flo-Grout EP280 can be applied in a single layer at thicknesses between 10 - 40 mm. For thicknesses greater than 40 mm, multiple layers can be applied after initial curing of the previous layer.

Yield

Approximately 10.25 litre/20 kg pack.

Storage

Flo-Grout EP280 has a shelf life of 12 months from date of manufacture if stored at temperatures between 5°C and 35°C.

If these conditions are exceeded, DCP Technical Department should be contacted for advise.

Cautions

Health and Safety

Flo-Grout EP280 is irritant to the eyes, skin and respiratory system. Wear suitable gloves and eye protection.

For further information refer to the Material Safety Data Sheet.

Don Construction Products Qatar W.L.L
New Industrial Area, Street 21,
Zone 81, bldg. # 9
Doha - Qatar



Flo-Grout EP280

Fire

Flo-Grout EP280 is nonflammable.

More from Don Construction Products

A wide range of construction chemical products are manufactured by DCP which include:

- ▲ Concrete admixtures.
- ▲ Surface treatments
- ▲ Grouts and anchors.
- ▲ Concrete repair.
- ▲ Flooring systems.
- ▲ Protective coatings.
- ▲ Sealants.
- ▲ Waterproofing.
- ▲ Adhesives.
- ▲ Tile adhesives and grouts.
- ▲ Building products.
- ▲ Structural strengthening.

Don Construction Products Qatar W.L.L


New Industrial Area, Street 21,
Zone 81, bldg. # 9
Doha - Qatar

Flo-Grout EP280

Don Construction Products Qatar W.L.L
New Industrial Area, Street 21,
Zone 81, bldg. # 9
Doha - Qatar

Note:

We endeavor to ensure that any advice, recommendation or information we may give in product literature is accurate and correct. However, due to the fact that we have no direct or continuous control over where or how the products are applied, DCP cannot accept any liability either directly or indirectly arising from the use of DCP products, whether or not in accordance with any advice, specification, recommendation or information given by us.

 expertise

 quality

 full range

www.dcp-int.com

