

Flo-Grout EP340

High strength pourable epoxy resin grout



Description

Flo-Grout EP340 is a three component, high strength, and free flowing epoxy resin grout. Flo-Grout EP340 is suitable for grouting large gaps from 10 to 400 mm at high ambient temperatures of up to 55°C.

Applications

Flo-Grout EP340 is ideally designed for use in the following applications:

- ▲ Machine base plates.
- ▲ Heavy crane rails.
- ▲ Bearing plinths.
- ▲ Anchoring of steel fixings.
- ▲ High speed turbines.
- ▲ Grouting areas where occasional chemical spillage may occur.

Advantages

- ▲ Resistant to dynamic loading.
- ▲ Non-shrink and low creep characteristics under continuous loading.
- ▲ Exceptional high compressive, flexural and tensile strengths.
- ▲ Extremely dense.
- ▲ Exceptional bond to concrete and steel surfaces.
- ▲ Good chemical resistance.
- ▲ High ultimate and early strengths.

Method of Use

Substrate Preparation

- ▲ The Substrate should be sound, clean and free from contamination. Surface laitance should be removed by scabbling or grit blasting.
- ▲ Steel surfaces should be grit blasted to remove all rust and scale.
- ▲ Concrete surfaces should be dry.
- ▲ Holes drilled for anchor bolts should be thoroughly cleaned from dust and loose debris using suitable brush or compressed air.

Technical Properties:

Mixed density:	2.00 ± 0.1 g/cm ³
Working life:	80 ± 10 min @ 25°C 40 ± 10 min @ 40°C
Compressive strength: ASTM C579	@ 1 day ≥ 50 MPa @ 25°C ≥ 75 MPa @ 40°C @ 3 days ≥ 70 MPa @ 25°C ≥ 85 MPa @ 40°C @ 7 days ≥ 85 MPa @ 25°C ≥ 95 MPa @ 40°C
Flexural strength: EN 13892-2	@ 7 days ≥ 35 MPa @ 40°C
Tensile strength: BS 6319-7	@ 7 days ≥ 15 MPa @ 40°C
Recommended working ambient temperature:	15 - 55°C
Crack formation temperature @ 400 mm:	No cracks or bleeding
Peak exothermic temperature: ASTM D2471	55 ± 2°C @ 40°C 66 ± 2°C @ 55°C
Peak exothermic time: ASTM D2471	35 ± 5 min @ 40°C 25 ± 5 min @ 55°C
Water absorption: ASTM C413	≤ 0.15%
Flow (using 200 ml cone):	200 ± 10 mm
VOC: ASTM D2369	≤ 10 g/ltr (complies with LEED)



Flo-Grout EP340

Mixing

To ensure proper mixing, a mechanically powered mixer or drill fitted with helix type paddle should be used. The entire content of the Hardener pack should be added to the Base pack.

Care should be taken to ensure that the bottom and the product sides are thoroughly scraped and used. Mix the two components for 2 minutes. The filler should be gradually added while mixing. Mixing should continue for 3 minutes or until a uniform consistency obtained.

Placing and Finishing

Under Base plate:

Enough material should be available to achieve a continuous fill and to complete the work. Pouring of the mixed grout should be started from one side only to avoid air entrapment. To obtain maximum flow distance, a side shutter feed with 100 mm side height should be erected and used to build the required head. At 100 mm of head, a flow distance of 2100 mm can be achieved at gap thicknesses of 100 mm @ 25°C ambient temperatures.

Formwork:

As the mixed grout possesses high fluid characteristics, all formwork and shutters should be water tight. This can be achieved by sealing underneath the formwork and at the joints by using an appropriate mastic.

Notes:

If temperatures are less than 20°C, the cure rate will be slow, but eventually will go to completion if the temperatures remain above 15°C.

Cleaning

All tools should be cleaned immediately after finishing using a suitable epoxy thinner. Hardened materials should be cleaned mechanically.

Packaging

Flo-Grout EP340 is available in 30 kg packs (15 litre).

Thicknesses and Size Limitations

Flo-Grout EP 340 is suitable for grouting large gaps from 10 to 400 mm. For greater thicknesses, multiple layers can be applied after initial curing of the previous layer.

Storage

Flo-Grout EP340 has a shelf life of 12 months from date of manufacture if stored at temperatures between 5°C and 35°C.

If these conditions are exceeded, DCP Technical Department should be contacted for advise.

Cautions

Health and Safety

Flo-Grout EP340 is irritant to the eyes, skin and respiratory system. Wear suitable gloves and eye protection.

For further information refer to the Material Safety Data Sheet.

Fire

Flo-Grout EP340 is nonflammable.

More from Don Construction Products

A wide range of construction chemical products are manufactured by DCP which include:

- ▲ Concrete admixtures.
- ▲ Surface treatments
- ▲ Grouts and anchors.
- ▲ Concrete repair.
- ▲ Flooring systems.
- ▲ Protective coatings.
- ▲ Sealants.
- ▲ Waterproofing.
- ▲ Adhesives.
- ▲ Tile adhesives and grouts.
- ▲ Building products.
- ▲ Structural strengthening.

Note:

We endeavor to ensure that any advice, recommendation or information we may give in product literature is accurate and correct. However, due to the fact that we have no direct or continuous control over where or how the products are applied, DCP cannot accept any liability either directly or indirectly arising from the use of DCP products, whether or not in accordance with any advice, specification, recommendation or information given by us.

