



# **DESCRIPTION**

Flo-Grout EPCG is a high strength, non-shrink, pourable epoxy resin grout suitable for grouting gaps with thicknesses up to 300 mm.

Flo-Grout EPCG is a three component system having base and hardener as the resin part with the blended ready filler part. And based on actual installation conditions, adjusting the quantity of the filler part can be done with maintaining the needed properties.

#### **APPLICATIONS**

Flo-Grout EPCG is ideally designed for use in the following applications:

- Machine base plates.
- Heavy crane rails.
- » Pile top waterproofing.
- » Bearing plinths.
- » High speed turbines.
- >> Grouting areas where occasional chemical spillage may occur.

#### **ADVANTAGES**

- » Resistant to dynamic loading.
- » Non-shrink and low creep characteristics under continuous loading.
- Exceptionally high compressive, flexural and tensile strengths.
- » Extremely dense with crack resistance.
- » Exceptional bond to concrete and steel surfaces.
- >> Good chemical resistance.
- » High early strength development allowing for rapid installation.

# **TECHNICAL PROPERTIES @ 25°C:**

Mixed density: 2.1 ± 0.1 g/cm<sup>3</sup>

Compressive

strength\*:

≥ 85 MPa @ 7 days ASTM C579-82,

Method B

Flexural strength\*: ≥ 30 MPa @ 7 days ASTM C580-74

Tensile strength\*: ≥ 12 MPa @ 7 days ASTM C307-83

Shrinkage\*: ≤ 0.08% ASTM C531

≥ 15 GPa @ 20°C Modulus of elasticity\*: ASTM C580-74 ≥ 13 GPa @ 40°C

Co-efficient of thermal

expansion:

25 x 10<sup>-6</sup>/°C **ASTM C531-81** 

(mortar consistency)

Water absorption\*: ≤ 0.1% ASTM C413

Initial curing: 24 hr @ 25°C

Crack formation (fill

#1):

No cracks or bleeding @ 300 mm thickness

& 35°C

40 to 70 min @ 25°C Working life:

25 to 45 min @ 35°C

Recommended

working temperature:

15 to 35°C

VOC: ≤ 10 g/ltr **ASTM D2369** (comply with LEED)

\*For all fill options.



# **RESIN FILLER RATIO**

As the foundation situation will vary for each installation project, the quantity of the filler part can be adjusted to obtain the proper flow and the continuous fill as required.

The following table indicates the three different situations in relation to the resin:filler ratio.

(Note 1: It is always preferable to use the maximum amount of filler part that will give the proper installation, and the highest results in strength).

(Note 2: At temperatures ≤ 25°C, the flow properties will be reduced. So reducing the filler part will help in adjusting it.

TEMPERATURE @25°C			
	High fill of filler for thick pours Fill #1	Moderate fill of filler for medium pours Fill #2	Low fill of filler for thin pours Fill #3
Mixing ratio:	Base + Hardener + 4 filler bags Total: 106.5 kg	Base + Hardener + 3.5 filler bags Total: 95.3 kg	Base + Hardener + 3 filler bags Total: 84.1 kg
Flow using flow cone with 200 ml volume: BS 890	15 - 16 cm	16 - 17 cm	18 - 19cm
Bulk density of the filler:	1.8 g/cm <sup>3</sup>		

It is important NOT to remove more than 1 filler bag.

# **METHOD OF USE**

#### SUBSTRATE PREPARATION

The Substrate should be sound, clean and free from contamination. Surface laitance should be removed by scabbling or grit blasting. Steel surfaces should be grit blasted to remove all rust and scale.

Concrete surfaces should be dry. Holes drilled for anchor bolts should be thoroughly cleaned from dust and lose debris using suitable brush or compressed air.

### **MIXING**

To ensure proper mixing, a mechanically powered mixer or drill fitted with suitable paddle should be used.

The entire content of the Hardener pack should be added to the Base pack. Care should be taken to ensure that the bottom and the product sides are thoroughly scraped and used. Mix the two components for 2 minutes. The filler should be gradually added while mixing.

Mixing should continue for 3 minutes or until a uniform consistency obtained.

# **PLACING AND FINISHING**

# Under Base plate:

Enough materials should be available to achieve continuous fill and to complete the work. Pouring of the mixed grout should be started from one side only to avoid air entrapment.

To obtain maximum flow distance, a side shutter feed 100 mm height should be erected and used to build the required head.

# Formwork:

As the mixed grout possesses fluid characteristics, all formwork and shutters should be water tight. This can be achieved by sealing underneath the formwork and at the joints by using an appropriate mastic.

### DCP Saudi Co.

Sulay, Industrial Area, Istanbul St., Riyadh Industrial City 3, Jeddah Saudi Arabia info.saudi@dcp-int.com www.dcp-int.com

#### Notes:

- » If application is done under high temperatures, care should be done because the working time will be reduced significantly.
- To reduce the effect of this problem, try to store the unmixed materials in a cool environment, avoiding the direct sunlight. Also, try not to make the application in the middle of the day or direct sunlight.

#### **CLEANING**

All tools should be cleaned immediately after finishing using a suitable epoxy thinner. Hardened materials should be cleaned mechanically.

#### **PACKAGING**

The full unit of Flo-Grout EPCG is with 106.5 kg consisting of Base, Hardener & 4 filler bags.

# THICKNESSES AND SIZE LIMITATIONS

Flo-Grout EPCG can be applied in a single layer at thicknesses between 10 - 300 mm. For thicknesses greater than 300 mm:

Multiple layers can be applied after initial curing of the previous layer.

# **YIELD**

Approximately 50.5 litre for the full unit.

# STORAGE

Flo-Grout EPCG has a shelf life of 12 months from date of manufacture if stored at temperatures between 5°C and 35°C.

If these conditions are exceeded, contact DCP Technical Department for advice.

**CAUTIONS** 

# **HEALTH AND SAFETY**

Flo-Grout EPCG is irritant to the eyes, skin and respiratory system. Wear suitable gloves and eye protection.

For further information, refer to the Material Safety Data Sheet.

#### **FIRE**

Flo-Grout EPCG is nonflammable.

# DCP Saudi Co.



# MORE FROM DON CONSTRUCTION PRODUCTS

A wide range of construction chemicals products are manufactured by DCP which include:

- » Concrete admixtures.
- » Surface treatments
- » Grouts and anchors.
- » Concrete repair.
- » Flooring systems.
- » Protective coatings.
- » Sealants.
- » Waterproofing.
- » Adhesives.
- » Tile adhesives and grouts.
- » Building products.
- » Structural strengthening.

# DCP Saudi Co.

Sulay, Industrial Area, Istanbul St., Riyadh Industrial City 3, Jeddah Saudi Arabia info.saudi@dcp-int.com www.dcp-int.com



#### Note:

We endeavour to ensure that any information, advice or recommendation we may give in product literature is accurate and correct. However, because we have no control over where and how products are applied, we cannot accept any liability arising from the use of the products.