# Flo-Grout FL70

High flow general purpose non-shrink cementitious grout



## Description

Flo-Grout FL70 is pre-mixed, high flow and chloride free cementitious grout. It contains cement, selected additives, well graded and non-reactive aggregates which when mixed with water provides a precision non-shrink grout with excellent flow, frost resistance and high compressive strength characteristics.

## **Applications**

Flo-Grout FL70 is ideally designed for use in the following applications:

- ▲ Machine beds.
- ▲ Stanchion bases, struts, railings, and guardrail assemblies.
- ▲ Filling of shutter tie rod openings.
- ▲ Anchoring of tie bars, and bolts.
- ▲ Pile top re-profi ling.

## **Advantages**

- ▲ High flow characteristics, can be poured or pumped into variable gap widths.
- ▲ Excellent flow retention characteristics.
- Non-shrink characteristics.
- ▲ High early strength development rate allowing for rapid installations.
- ▲ Easy to apply, single component which requires only addition of water.
- ▲ Chloride free.

### Method of Use

#### Substrate Preparation

- ▲ The Substrate should be sound, clean and free from contamination. Surface Laitance should be removed by acid etching.
- ▲ All surfaces should be soaked with water enough to reach saturated surfaces prior to grouting.
- ▲ A water tight formwork should be erected to avoid any grout loss.

## Mixing

To ensure proper mixing, a mechanically powered mixer or drill fitted with suitable paddle should be used.

# Technical Properties @ 25°C:

Colour: Grey

Fresh wet density:  $2.3 \pm 0.1 \text{ g/cm}^3$ 

Compressive strength: ASTM C109/109M-02

≥ 35 MPa @ 1 day
≥ 60 MPa @ 7 days
≥ 70 MPa @ 28 days

Pre-hardening volume

change:

Up to +3.0%

ASTM C940

Bleeding:

Nil

ASTM C940

Flow characteristics: ASTM C1437

Initial After 30 min (remix) 280 - 290 mm 200 - 220 mm

Application tempera-

ture:

5 to 40°C

VOC:

**ASTM D2369** 

< 5 g/ltr

#### Notes:

Typical properties @ 4.0 litre per 25 kg bag. Compressive strength specimens @ 1 day should be kept under sufficient restrain.

Compressive strength specimens @ 7 and 25 days are under wet cure conditions.

Flow characteristics were tested using the conical mold only without the table.

4.0 litre of clean water for each 25 kg bag should be added to clean container (i.e. water-to-powder ratio = 0.16), then the powder should be added slowly to the water while mixing continuously with low speed mixer/drill (400 - 600 rpm). Mixing time should be continued for 3 minutes until uniform consistency is obtained.

## Placing and Finishing

#### Under Base plate:

Enough material should be available to achieve continuous fill and to complete the work. Pouring of the mixed grout should be started from one side only to avoid air entrapment. To obtain maximum flow distance, a side shutter feed between 100 - 250 mm high should be erected and used to build the required head.



# Flo-Grout FL70

#### Formwork:

As the mixed grout posses high fluidity characteristics, all formwork and shutters should be water tight. This can be obtained by sealing underneath the formwork and at the joints by using an appropriate mastic.

The unrestrained areas should be kept to a minimum due to the expansive nature of Flo-Grout FL70.

#### Curing

Since Flo-Grout FL70 is a cementitious based material, it should be treated in a manner similar to concrete. Curing can be conducted by either using concrete curing compound such as Setseal 22 or by using wet hessian and polyethylene.

#### Notes:

- ▲ At low temperatures (below 8°C), warm water is recommended to achieve the early strength. And the formwork is recommended to be kept longer time.
- ▲ At high temperatures (35°C and above), cold water (less than 20°C) must be used for mixing.

#### Cleaning

All tools should be cleaned immediately after finishing by clean water. Hardened materials should be cleaned mechanically.

## **Packaging**

Flo-Grout FL70 is available in 25 kg packs.

#### Thicknesses and Size Limitations

Flo-Grout FL70 can be applied in a single layer at thickness between 10 - 100 mm. For greater thickness, an 8 - 12 mm washed aggregate should be added at a ratio between 50 - 70% of Flo-Grout FL70.

#### Yield

Approximately 12 - 13 litre per 25 kg bag depending on consistency.

### Storage

Flo-Grout FL70 has a shelf life of 12 months from date of manufacture if stored at temperatures between 2°C and 50°C.

If these conditions are exceeded, DCP Technical Department should be contacted for advise.

#### Cautions

#### Health and Safety

Since it is powder containing Portland cement and sand, Flo-Grout FL70 may cause irritation to skin or eyes. In case of accidental contact with eyes, immediately flush with plenty of water for at least 10 minutes and seek medical advise.

For further information refer to the Material Safety Data Sheet

#### Fire

Flo-Grout FL70 is nonflammable.

## More from Don Construction Products

A wide range of construction chemical products are manufactured by DCP which include:

- ▲ Concrete admixtures.
- ▲ Surface treatments
- ▲ Grouts and anchors.
- ▲ Concrete repair.
- ▲ Flooring systems.
- ▲ Protective coatings.
- ▲ Sealants.
- ▲ Waterproofing.
- ▲ Adhesives.
- ▲ Tile adhesives and grouts.
- ▲ Building products.
- Structural strengthening.



Note:

We endeavour to ensure that any information, advice or recommendation we may give in product literature is accurate and correct. However, because we have no control over where and how products are applied, we cannot accept any liability arising from the use of the products.



