

Flocrete RP150

Retarding and water reducing admixture



Description

Flocrete RP150 is formulated from selected polymers specially designed to enable the water content of the concrete to perform more effectively. This effect can be used to improve workability, to increase ultimate strengths or to facilitate a reduction in the cement content while sustaining mix properties.

Flocrete RP150 has retarding property, this effect can be used to overcome transportation delay problems and where long setting time is required.

Applications

- ▲ Long concrete deliveries.
- ▲ Hot weather concreting.
- ▲ Where high workability retention and retardation are required.
- ▲ To produce high quality concrete of improved durability and water tightness.
- ▲ To improve cohesion in concrete mixes.

Advantages

- ▲ Improved workability reduces placing and compaction problems.
- ▲ Cold joints can be avoided by extending initial and final concrete setting time.
- ▲ Higher strength with same cement content.
- ▲ Cement saving without affecting strength.
- ▲ More durable concrete as a result of reduction in permeability and lower water to cement ratio.

Compatibility

Flocrete RP150 can be used with all types of Portland cement and cement replacement materials. Flocrete RP150 is compatible with other DCP admixtures used in the same concrete mix.

If more than one type of admixture is to be used in concrete mix, they must be dispensed to the concrete separately.

Standards

Flocrete RP150 complies with ASTM C494, Type B and D and with BS5075, Part 1.

Technical Properties @ 25 °C:

Color:	Brown liquid
Freezing point:	-2°C
Specific gravity:	1.1 ± 0.05
Chloride content: BS5075	Nil
Air entrainment:	Typically less than 2% additional air is entrained above control mix at normal dosages

Method of Use

Flocrete RP150 should be added to the concrete with the mixing water to achieve optimum performance.

Automatic dispenser should be used to dispense the correct quantity of Flocrete RP150 to the concrete mix.

Dosage

The guidance dosage of Flocrete RP150 is 0.20 - 1.2 litres/ 100 kg of cementitious materials in the mix, including GGBFS, PFA or microsilica.

Representative trials should be conducted to determine the optimum dosage of Flocrete RP150 to meet the performance requirements by using the materials and conditions in actual use.

Effects of Over Dosage

Overdosing of Flocrete RP150 over dosage will cause the following:

- Significant increase in retardation.
- Increase in workability.

Ultimate concrete strength will not be adversely affected and will generally be increased provided that proper concrete curing is maintained.

Flocrete RP150

Setting Time

Although the setting time is dependent on the dosage of Flocrete RP150, the following factors should be considered:

- i. Retardation is increased with lower levels of tricalcium in the cement.
- ii. Lower temperatures will delay the setting time.
- iii. SRC cement gives higher retardation level than ordinary cement.
- iv. Using more than one type of admixture in the same concrete mix could affect the setting time.
- v. Retardation level is increased when cement replacement materials are used in the concrete mix.

Cleaning

Flocrete RP150 can be washed with fresh cold water.

Packaging

Flocrete RP150 is available in 25 litres pails, 210 litres drums and 1000 litres bulks supply.

Storage

Flocrete RP150 shelf life is 12 months if stored at temperatures between 2°C and 50°C.

If these conditions are exceeded, DCP Technical Department should be contacted for advice.

Cautions

Health and Safety

Flocrete RP150 is not classified as hazardous material. Flocrete RP150 should not come into contact with skin and eyes.

In case of contact with eyes wash immediately with plenty of water and seek medical advice promptly.

For further information refer to the Material Safety Data sheet.

Fire

Flocrete RP150 is non-flammable.

More from Don Construction Products

A wide range of construction chemicals products are manufactured by DCP which include:

- ▲ Concrete admixtures.
- ▲ Grouts and chemical fixings.
- ▲ Concrete repairs.
- ▲ Industrial floorings.
- ▲ Structural protection.
- ▲ Waterproofing.

Note:

We endeavor to ensure that any advice, recommendation or information we may give in product literature is accurate and correct. However, due to the fact that we have no direct or continuous control over where or how the products are applied, DCP cannot accept any liability either directly or indirectly arising from the use of DCP products, whether or not in accordance with any advice, specification, recommendation or information given by us.

