

# Flocrete RP150M

Retarding and water reducing admixture



## Description

Flocrete RP150M is formulated from selected polymers specially designed to enable the water content of the concrete to perform more effectively.

This effect can be used to improve workability, to increase ultimate strengths or to facilitate a reduction in the cement content while sustaining mix properties.

Flocrete RP150M has retarding property, this effect can be used to overcome transportation delay problems and where long setting time is required.

## Applications

- ▲ Long concrete deliveries.
- ▲ Hot weather concreting.
- ▲ Where high workability retention and retardation are required.
- ▲ To produce high quality concrete of improved durability and water tightness.
- ▲ To improve cohesion in concrete mixes.

## Advantages

- ▲ Improved workability reduces placing and compaction problems.
- ▲ Cold joints can be avoided by extending initial and final concrete setting time.
- ▲ Higher strength with same cement content.
- ▲ Cement saving without affecting strength.
- ▲ More durable concrete as a result of reduction in permeability and lower water to cement ratio.

## Compatibility

Flocrete RP150M is suitable to use with all types of Portland cement and cement replacement materials. Flocrete RP150M is compatible with other DCP admixtures used in the same concrete mix.

If more than one type of admixture is to be used in the concrete mix, they must be dispensed to the concrete separately.

## Technical Properties @ 25 °C:

Colour:	Dark brown liquid
Freezing point:	-2°C
Specific gravity:	1.07 ± 0.03
Chloride content: BS5075	Nil
pH:	6.0
Air entrainment:	Typically less than 2% additional air is entrained above control mix at normal dosages

## Standards

Flocrete RP150M complies with ASTM C494, Type B and D and with BS 5075, Part 1.

## Method of Use

Flocrete RP150M should be added to the concrete with the mixing water to achieve optimum performance.

An automatic dispenser should be used to dispense the correct quantity of Flocrete RP150M to the concrete mix.

## Dosage

The recommended dosage of Flocrete RP150M is 0.2 - 1.2 litre per 100 kg of cementitious materials in the mix, including GGBFS, PFA or microsilica.

Representative trials should be conducted to determine the optimum dosage of Flocrete RP150M to meet the performance requirements by using the materials and conditions in actual use.

**DCP Saudi Co.**

Sulay industrial area,  
Riyadh, Saudi Arabia

[info.ksa@dcp-int.com](mailto:info.ksa@dcp-int.com)

# Flocrete RP150M

## Effects of Over Dosage

Overdosage of Flocrete RP150M over dosage will cause the following:

- ▲ Significant increase in retardation.
- ▲ Increase in workability.

Ultimate concrete strength will not be adversely affected and will generally be increased provided that proper concrete curing is maintained.

## Setting Time

Although the setting time is dependent on the dosage of Flocrete RP150M, the following factors should be considered:

- Retardation is increased with lower levels of tricalcium in the cement.
- Lower temperatures will delay the setting time.
- SRC cement gives higher retardation level than ordinary cement.
- Using more than one type of admixture in the same concrete mix could affect the setting time.
- Retardation level is increased when cement replacement materials are used in the concrete mix.

## Cleaning

Clean Flocrete RP150M with fresh cold water.

## Packaging

Flocrete RP150M is available in 25 litre pails, 210 litre drums and 1000 litre bulk supply.

## Storage

Flocrete RP150M has a shelf life of 12 months from date of manufacture if stored at temperatures between 2°C and 50°C.

If these conditions are exceeded, contact DCP Technical Department for advice.

## Cautions

### Health and Safety

Flocrete RP150M is not classified as a hazardous material. Flocrete RP150M should not come into contact with skin and eyes.

In case of contact with eyes, immediately flush with plenty of water and seek medical attention.

For further information, refer to the Material Safety Data Sheet.

### Fire

Flocrete RP150M is nonflammable.

## More from Don Construction Products

A wide range of construction chemical products are manufactured by DCP which include:

- ▲ Concrete admixtures.
- ▲ Surface treatments
- ▲ Grouts and anchors.
- ▲ Concrete repair.
- ▲ Flooring systems.
- ▲ Protective coatings.
- ▲ Sealants.
- ▲ Waterproofing.
- ▲ Adhesives.
- ▲ Tile adhesives and grouts.
- ▲ Building products.
- ▲ Structural strengthening.

### DCP Saudi Co.

Sulay industrial area,  
Riyadh, Saudi Arabia

[info.ksa@dcp-int.com](mailto:info.ksa@dcp-int.com)

#### Note:

We endeavour to ensure that any information, advice or recommendation we may give in product literature is accurate and correct. However, because we have no control over where and how products are applied, we cannot accept any liability arising from the use of the products.