

Flocrete RP30

Retarding and water reducing admixture



DESCRIPTION

Flocrete RP30 is formulated from selected polymers specially designed to enable the water content of the concrete to perform more effectively. This effect can be used to improve workability, to increase ultimate strengths or to facilitate a reduction in the cement content while sustaining and improving mix properties.

Flocrete RP30 has retarding properties; this effect can be used in concrete where high cement content or high temperatures are involved, or where extended setting time is required.

APPLICATIONS

- » Roller compacted concrete (RCC).
- » Hot weather concreting.
- » Where workability retention or retardation are required.
- » To produce high quality concrete of improved durability and water tightness.

ADVANTAGES

- » Improved workability reduces placing and compaction problems.
- » Workability retention for long distance concreting.
- » Cold joints can be avoided by extending initial and final concrete setting time.
- » Higher strength with same cement content.
- » Cement saving without affecting strength.
- » More durable concrete as a result of reduction in permeability and lower water to cement ratio.

COMPATIBILITY

Flocrete RP30 is suitable to use with all types of Portland cement and cement replacement materials. Flocrete RP30 is compatible with other DCP admixtures used in the same concrete mix.

If more than one type of admixture is to be used in concrete mix, they must be dispensed to the concrete separately.

STANDARDS

Flocrete RP30 complies with ASTM C494, Type B & D and with BS 5075, Part 1.

METHOD OF USE

Flocrete RP30 should be added to the concrete with the mixing water to achieve optimum performance.

An automatic dispenser should be used to dispense the correct quantity of Flocrete RP30 to the concrete mix.

TECHNICAL PROPERTIES @ 25°C:

Colour:	Brown liquid
Freezing point:	-2°C
Specific gravity:	1.09 ± 0.02
Chloride content: BS 5075	Nil
Air entrainment:	Typically less than 2% additional air is entrained above control mix at normal dosages

DOSAGE

The recommended dosage of Flocrete RP30 is 0.20 - 1.20 litre per 100 kg of cementitious materials in the mix, including GGBFS, PFA or microsilica.

Representative trials should be conducted to determine the optimum dosage of Flocrete RP30 to meet the performance requirements by using the materials and conditions in actual use.

EFFECTS OF OVERDOSAGE

Overdosage of Flocrete RP30 will cause the following:

- » Significant increase in retardation.
- » Increase in workability.

Ultimate concrete strength will not be adversely affected and will generally be increased provided that proper concrete curing is maintained.

SETTING TIME

Although the setting time is dependent on the dosage of Flocrete RP30, the following factors should be considered:

- Retardation is increased with a lower level of tri-calcium in the cement.
- Lower temperatures will delay the setting time.
- SRC cement gives higher retardation level than ordinary cement.
- Using more than one type of admixture in the same concrete mix could affect the setting time.
- Retardation level is increased when cement replacement materials are used in the concrete mix.

CLEANING

Clean Flocrete RP30 with fresh cold water.



Flocrete RP30

Table 1: Initial Setting Time for Normal Concrete

PROPERTIES	ASTM CODE	CONTROL MIX*	FLOCRETE RP30					
Flocrete RP30 Dosage (kg/m ³)		0.0	0.2	0.3	0.4	0.6	0.8	0.9
Flow/Slump (mm)	ASTM C143	200	200	210	190	205	200	190
Air Content by pressure method	ASTM C231	2.6	2.8	2.9	2.9	2.8	3.0	3.2
Initial set (@ 500 lb/in ²) (hr:min) @ 25°C	ASTM C403	5.5	6.5	7.0	8.25	10.5	14.5	18.5

*320 kg/ m³, CEM I 42.5 R, concrete temperature 20°C.

Table 2: Initial Setting Time for Roller Compacted Concrete (RCC)

PROPERTIES	ASTM CODE	CONTROL MIX*	FLOCRETE RP30			
Flocrete RP30 Dosage (kg/m ³)		0.0	0.8	1.0	1.2	1.4
Flow/Slump (mm)	ASTM C143	35	45	45	50	60
Air Content by pressure method	ASTM C231	2.9	3.2	3.1	3.0	3.1
Initial set (@ 500 lb/in ²) (hr:min) @ 25°C	ASTM C403	6.0	13.0	18.0	28.0	34.0

*125 kg/ m³, CEM 42.5, concrete temperature 20°C.

PACKAGING

Flocrete RP30 is available in 25 litre pails, 210 litre drums and 1000 litre bulks supply.

STORAGE

Flocrete RP30 has a shelf life of 12 months from date of manufacture if stored at temperatures between 2°C and 50°C.

If these conditions are exceeded, contact DCP Technical Department for advice.

CAUTIONS

HEALTH AND SAFETY

Flocrete RP30 is not classified as a hazardous material. Flocrete RP30 should not come into contact with skin and eyes.

In case of contact with eyes, immediately flush with plenty of water and seek medical attention.

For further information, refer to the Material Safety Data Sheet.

Abidjan Marcory Zone 4A
Rue Thomos Edison Résidence Foua
Ivory Coast
info.ivory.coast@dcp-int.com
www.dcp-int.com

FIRE

Flocrete RP30 is nonflammable.

MORE FROM DON CONSTRUCTION PRODUCTS

A wide range of construction chemical products are manufactured by DCP which include:

- » Concrete admixtures.
- » Surface treatments
- » Grouts and anchors.
- » Concrete repair.
- » Flooring systems.
- » Protective coatings.
- » Sealants.
- » Waterproofing.
- » Adhesives.
- » Tile adhesives and grouts.
- » Building products.
- » Structural strengthening.

Note:

We endeavour to ensure that any information, advice or recommendation we may give in product literature is accurate and correct. However, because we have no control over where and how products are applied, we cannot accept any liability arising from the use of the products.

www.dcp-int.com

DCP Building Excellence