

Flocrete RPC7

Retarding and water reducing admixture



DESCRIPTION

Flocrete RPC7 is formulated from selected polymers specially designed to enable the water content of the concrete to perform more effectively.

This effect can be used to improve workability, to increase ultimate strengths or to facilitate a reduction in the cement content while sustaining mix properties.

Flocrete RPC7 has retarding property, this effect can be used overcome transportation delay problems and where long setting time is required.

APPLICATIONS

- » Long concrete deliveries.
- » Hot weather concreting.
- » Where high workability retention and retardation are required.
- » To produce high quality concrete of improved durability and water tightness.
- » To improve cohesion in concrete mixes.

ADVANTAGES

- » Improved workability, reduces placing and compaction problems.
- » Cold joints can be avoided by extending initial and final concrete setting time.
- » Higher strength with same cement content.
- » Cement saving without affecting strength.
- » More durable concrete as a result of reduction in permeability and lower water to cement ratio.

COMPATIBILITY

Flocrete RPC7 can be used with all types of Portland cement and cement replacement materials. Flocrete RPC7 is compatible with other DCP admixtures used in the same concrete mix.

If more than one type of admixture is to be used in concrete mix, they must be dispensed to the concrete separately.

STANDARDS

Flocrete RPC7 complies with ASTM C494, Type B and D, with BS 5075, Part 1 and ASTM C1017, Type II.

TECHNICAL PROPERTIES @ 25°C:

Colour:	Clear to yellowish liquid
Freezing point:	≈ -1°C
Specific gravity:	1.04 ± 0.02
Chloride content: EN 934-2	Chloride-free

METHOD OF USE

Flocrete RPC7 should be added to the concrete with the mixing water to achieve optimum performance.

An automatic dispenser should be used to dispense the correct quantity of Flocrete RPC7 to the concrete mix.

DOSAGE

The recommended dosage of Flocrete RPC7 is 0.2 - 1.2 liters per 100 kg of cementitious materials in the mix, including GGBFS, PFA or microsilica.

EFFECTS OF OVERDOSAGE

Overdosage of Flocrete RPC7 over dosage will cause the following:

- » Significant increase in retardation.
- » Increase in workability.

Ultimate concrete strength will not be adversely affected and will generally be increased provided that proper concrete curing is maintained.

SETTING TIME

Although the setting time is dependent on the dosage of Flocrete RPC7, the following factors should be considered:

- » Retardation is increased with lower levels of tricalcium in the cement.
- » Lower temperatures will delay the setting time.
- » SRC cement gives higher retardation level than ordinary cement.
- » Using more than one type of admixture in the same concrete mix could affect the setting time.
- » Retardation level is increased when cement replacement materials are used in the concrete mix.

DCP Saudi Co.

Sulay, Industrial Area, Istanbul St., Riyadh
Industrial City 3, Jeddah
Saudi Arabia
info.saudi@dcp-int.com
www.dcp-int.com



Flocrete RPC7

CLEANING

Clean Flocrete RPC7 with fresh cold water.

PACKAGING

Flocrete RPC7 is available in 25 litre jerrycan, 210 litre drums and 1000 litre bulks supply.

STORAGE

Flocrete RPC7 has a shelf life of 12 months from date of manufacture if stored at temperatures between 2°C and 50°C.

If these conditions are exceeded, contact DCP Technical Department for advice.

CAUTIONS

HEALTH AND SAFETY

Flocrete RPC7 is not classified as a hazardous material. Flocrete RPC7 should not come into contact with skin and eyes.

In case of contact with eyes, immediately flush with plenty of water and seek medical attention.

For further information, refer to the Material Safety Data sheet.

FIRE

Flocrete RPC7 is nonflammable.

MORE FROM DON CONSTRUCTION PRODUCTS

A wide range of construction chemical products are manufactured by DCP which include:

- » Concrete admixtures.
- » Surface treatments
- » Grouts and anchors.
- » Concrete repair.
- » Flooring systems.
- » Protective coatings.
- » Sealants.
- » Waterproofing.
- » Adhesives.
- » Tile adhesives and grouts.
- » Building products.
- » Structural strengthening.

DCP Saudi Co.

Sulay, Industrial Area, Istanbul St., Riyadh

Industrial City 3, Jeddah

Saudi Arabia

info.saudi@dcp-int.com

www.dcp-int.com

Note:

We endeavour to ensure that any information, advice or recommendation we may give in product literature is accurate and correct. However, because we have no control over where and how products are applied, we cannot accept any liability arising from the use of the products.

www.dcp-int.com

DCP Building Excellence