

# Flocrete SP100

High performance water reducing admixture for HSC



## Description

Flocrete SP100 is high performance superplasticising admixture formulated from selected polymers specially designed to enable the water content of the concrete to perform more effectively.

This effect can be used in high strength concrete mixes to improve workability, to increase ultimate strengths or to facilitate a reduction in the cement content while sustaining and improving mix properties.

## Applications

- ▲ Recommended for high strength concrete mixes.
- ▲ Improved cohesion allows for use in mass concrete pours and filing.
- ▲ To produce high quality concrete of improved durability and water tightness.

## Advantages

- ▲ Allowing for high strength concrete production without excessive cement contents.
- ▲ Improved workability reduces placing and compaction problems.
- ▲ Cement saving without affecting strength.
- ▲ Minimising segregation and bleeding problems by improving cohesion.
- ▲ More durable concrete as a result of reduction in permeability and lower water to cement ratio.

## Compatibility

Flocrete SP100 can be used with all types of Portland cement and cement replacement materials. Flocrete SP100 is compatible with other DCP admixtures used in the same concrete mix. If more than one type of admixture is to be used in the concrete mix, they must be dispensed to the concrete separately.

## Standards

Flocrete SP100 complies with BS EN 934-2 : 1998 and ASTM C494, Type G.

## Method of Use

Flocrete SP100 should be added to the concrete with the mixing water to achieve optimum performance.

## Technical Properties @ 25°C:

Colour:	Brown liquid
Freezing point:	≈ -1°C
Specific gravity:	1.21 ± 0.02
Chloride content: BS 5075	Nil
Air entrainment:	Typically less than 2% additional air is entrained above control mix at normal dosages

An automatic dispenser should be used to dispense the correct quantity of Flocrete SP100 to the concrete mix.

## Dosage

The guidance dosage of Flocrete SP100 is 1.0 - 2.8 litre per 100 kg of cementitious materials in the mix, including GGBFS, PFA or microsilica.

Representative trials should be conducted to determine the optimum dosage of Flocrete SP100 to meet the performance requirements by using the materials and conditions in actual use.

## Effects of Over Dosage

Overdosing of Flocrete SP100 will cause the following:

- ▲ Significant increase in retardation.
- ▲ Increase in workability.

Ultimate concrete strength will not be adversely affected and will generally be increased provided that proper concrete curing is maintained.

## Setting Time

Although the setting time is dependent on the dosage of Flocrete SP100, the following factors should be considered:

- Retardation is increased with lower levels of tri-calcium in the cement.
- Lower temperatures will delay the setting time.
- SRC cement gives higher retardation level than ordinary cement.

# Flocrete SP100

- iv. Using more than one type of admixture in the same concrete mix could affect the setting time.
- v. Retardation level is increased when cement replacement materials are used in the concrete mix.

## Cleaning

Flocrete SP100 can be washed with fresh cold water.

## Packaging

Flocrete SP100 is available in 25 litre pails, 210 litre drums and 1000 litre bulks supply.

## Storage

Flocrete SP100 has a shelf life of 12 months from date of manufacture if stored at temperatures between 2°C and 50°C.

If these conditions are exceeded, DCP Technical Department should be contacted for advice.

## Cautions

### Health and Safety

Flocrete SP100 is not classified as hazardous material. Flocrete SP100 should not come into contact with skin and eyes.

In case of contact with eyes wash immediately with plenty of water and seek medical advice promptly.

For further information refer to the Material Safety Data Sheet.

### Fire

Flocrete SP100 is nonflammable.

## More from Don Construction Products

A wide range of construction chemical products are manufactured by DCP which include:

- ▲ Concrete admixtures.
- ▲ Surface treatments
- ▲ Grouts and anchors.
- ▲ Concrete repair.
- ▲ Flooring systems.
- ▲ Protective coatings.
- ▲ Sealants.
- ▲ Waterproofing.
- ▲ Adhesives.
- ▲ Tile adhesives and grouts.
- ▲ Building products.
- ▲ Structural strengthening.

#### Note:

We endeavor to ensure that any advice, recommendation or information we may give in product literature is accurate and correct. However, due to the fact that we have no direct or continuous control over where or how the products are applied, DCP cannot accept any liability either directly or indirectly arising from the use of DCP products, whether or not in accordance with any advice, specification, recommendation or information given by us.

[www.dcp-int.com](http://www.dcp-int.com)



expertise



quality



full range