

Flocrete SP124M1

High performance water reducing admixture for HSC



Description

Flocrete SP124M1 is high performance superplasticising admixture formulated from selected polymers specially designed to enable the water content of the concrete to perform more effectively.

This effect can be used in high strength concrete mixes to improve workability, to increase ultimate strengths or to facilitate a reduction in the cement content while sustaining and improving mix properties.

Applications

- ▲ To produce high quality concrete of improved durability and water tightness.
- ▲ Recommended for high strength concrete mixes.
- ▲ Improved cohesion allows for use in mass concrete pours and piling.

Advantages

- ▲ Improved workability reduces placing and compaction problems.
- ▲ Allowing for high strength concrete production without excessive cement contents.
- ▲ Cement saving without affecting strength.
- ▲ Minimising segregation and bleeding problems by improving cohesion.
- ▲ More durable concrete as a result of reduction in permeability and lower water to cement ratio.

Compatibility

Flocrete SP124M1 is suitable to use with all types of Portland cement and cement replacement materials. Flocrete SP124M1 is compatible with other DCP admixtures used in the same concrete mix.

If more than one type of admixture is to be used in the concrete mix, they must be dispensed to the concrete separately.

Standards

Flocrete SP124M1 complies with ASTM C494, Type F & G depending on the dosage.

Technical Properties @ 25°C:

Colour:	Brown liquid
Freezing point:	≈ -1°C
Specific gravity:	1.25 ± 0.02
Air entrainment:	Less than 2% at normal dosage
Chloride content:	Nil

Method of Use

Flocrete SP124M1 should be added to the concrete with the mixing water to achieve optimum performance.

An automatic dispenser should be used to dispense the correct quantity of Flocrete SP124M1 to the concrete mix.

Dosage

The recommended dosage of Flocrete SP124M1 is 1.0 to 3.00 litre per 100 kg of cementitious materials in the mix, including GGBFS, PFA or microsilica.

Representative trials should be conducted to determine the optimum dosage of Flocrete SP124M1 to meet the performance requirements by using the materials and conditions in actual use.

Effects of Over Dosage

Overdosage of Flocrete SP124M1 will cause the following:

- ▲ Significant increase in retardation.
- ▲ Increase in workability.

Ultimate concrete strength will not be adversely affected and will generally be increased provided that proper concrete curing is maintained.

Setting Time

Although the setting time is dependent on the dosage of Flocrete SP124M1, the following factors should be considered:

Flocrete SP124M1

- i. Retardation is increased with lower levels of tri-calcium in the cement.
- ii. Lower temperatures will delay the setting time.
- iii. SRC cement gives higher retardation level than ordinary cement.
- iv. Retardation level is increased when cement replacement materials are used in the concrete mix.

Cleaning

Clean Flocrete SP124M1 with fresh cold water.

Packaging

Flocrete SP124M1 is available in 210 litre drums and 1000 litre bulks supply.

Storage

Flocrete SP124M1 has a shelf life of 12 months from date of manufacture if stored at temperatures between 2°C and 50°C.

If these conditions are exceeded, contact DCP Technical Department for advice.

Cautions

Health and Safety

Flocrete SP124M1 is not classified as a hazardous material. Flocrete SP124M1 should not come into contact with skin and eyes.

In case of contact with eyes, immediately flush with plenty of water and seek medical attention.

For further information, refer to the Material Safety Data Sheet.

Fire

Flocrete SP124M1 is nonflammable.

More from Don Construction Products

A wide range of construction chemical products are manufactured by DCP which include:

- ▲ Concrete admixtures.
- ▲ Surface treatments
- ▲ Grouts and anchors.
- ▲ Concrete repair.
- ▲ Flooring systems.
- ▲ Protective coatings.
- ▲ Sealants.
- ▲ Waterproofing.
- ▲ Adhesives.
- ▲ Tile adhesives and grouts.
- ▲ Building products.
- ▲ Structural strengthening.

DCP Saudi Co.

Sulay industrial area,
Riyadh, Saudi Arabia

info.ksa@dcp-int.com

Note:

We endeavour to ensure that any information, advice or recommendation we may give in product literature is accurate and correct. However, because we have no control over where and how products are applied, we cannot accept any liability arising from the use of the products.

