

Flocrete SP47

High range water reducing superplasticiser admixture



DESCRIPTION

Flocrete SP47 is superplasticising admixture formulated from selected polymers specially designed to enable the water content of the concrete to perform more effectively.

This effect can be used to improve workability, to increase ultimate strengths or to facilitate a reduction in the cement content while sustaining mix properties.

APPLICATIONS

- » Low water cement ratio, high strength concrete.
- » To accelerate early strength development.
- » To produce high quality concrete of improved durability and water tightness.
- » Precast concrete.

ADVANTAGES

- » High strength increase with same cement content.
- » Earlier formwork stripping by increasing early strength.
- » Improved workability, reduces placing and compaction problems.
- » Cement saving without affecting concrete strength and workability.
- » Minimising segregation and bleeding problems by improving cohesion.
- » More durable concrete as a result of reduction in permeability and lower water to cement ratio.

COMPATIBILITY

Flocrete SP47 is suitable to use with all types of Portland cement and cement replacement materials. Flocrete SP47 is compatible with other DCP admixtures used in the same concrete mix.

If more than one type of admixture is to be used in the concrete mix, they must be dispensed to the concrete separately.

STANDARDS

Flocrete SP47 complies with ASTM C494, Type A and F and BS 5075, Part 3.

METHOD OF USE

Flocrete SP47 should be added to the concrete with the mixing water to achieve optimum performance.

An automatic dispenser should be used to dispense the correct quantity of Flocrete SP47 to the concrete mix.

TECHNICAL PROPERTIES @ 25°C:

Colour:	Brown liquid
Freezing point:	≈ -2°C
Specific gravity:	1.13 ± 0.02
Chloride content: BS 5075	Nil
Air entrainment:	Typically less than 2% additional air is entrained above control mix at normal dosages

DOSAGE

The recommended dosage of Flocrete SP47 is 0.80 - 2.80 litre per 100 kg of cementitious materials in the mix, including GGBFS, PFA or microsilica.

Representative trials should be conducted to determine the optimum dosage of Flocrete SP47 to meet the performance requirements by using the materials and conditions in actual use.

Dosages outside the typical ranges mentioned above can be used to meet particular requirements depending on the materials and conditions. Contact DCP technical service department for advice.

EFFECTS OF OVER DOSAGE

Overdosage of Flocrete SP47 will cause the following:

- » Significant increase in retardation.
- » Increase in workability.

Ultimate concrete strength will not be adversely affected and will generally be increased provided that proper concrete curing is maintained.

SETTING TIME

Although the setting time is dependent on the dosage of Flocrete SP47, the following factors should be considered:

- Retardation is increased with lower levels of tri-calcium in the cement.
- Lower temperatures will delay the setting time.
- SRC cement gives higher retardation levels than ordinary cement.
- Using more than one type of admixture in the same concrete mix could affect the setting time.
- Retardation level is increased when cement replacement materials are used in the concrete mix.

DCP Saudi Co.

Sulay, Industrial Area, Istanbul St., Riyadh
Industrial City 3, Jeddah
Saudi Arabia
info.saudi@dcp-int.com
www.dcp-int.com



Flocrete SP47

CLEANING

Clean Flocrete SP47 with fresh cold water.

PACKAGING

Flocrete SP47 is available in 25 litre pails, 210 litre drums and 1000 litre bulks supply.

STORAGE

Flocrete SP47 has a shelf life of 12 months from date of manufacture if stored at temperatures between 2°C and 50°C.

If these conditions are exceeded, contact DCP Technical Department for advice.

CAUTIONS

HEALTH AND SAFETY

Flocrete SP47 is not classified as a hazardous material. Flocrete SP47 should not come into contact with skin and eyes.

In case of contact with eyes, immediately flush with plenty of water and seek medical attention.

For further information, refer to the Material Safety Data Sheet.

FIRE

Flocrete SP47 is nonflammable.

MORE FROM DON CONSTRUCTION PRODUCTS

A wide range of construction chemical products are manufactured by DCP which include:

- » Concrete admixtures.
- » Surface treatments
- » Grouts and anchors.
- » Concrete repair.
- » Flooring systems.
- » Protective coatings.
- » Sealants.
- » Waterproofing.
- » Adhesives.
- » Tile adhesives and grouts.
- » Building products.
- » Structural strengthening.

DCP Saudi Co.

Sulay, Industrial Area, Istanbul St., Riyadh
Industrial City 3, Jeddah
Saudi Arabia
info.saudi@dcp-int.com
www.dcp-int.com

Note:

We endeavour to ensure that any information, advice or recommendation we may give in product literature is accurate and correct. However, because we have no control over where and how products are applied, we cannot accept any liability arising from the use of the products.