

Flocrete SP5000M

Cold weather concreting admixture



DESCRIPTION

Flocrete SP5000M is a multi-component, high performance concrete additive in liquid form for producing high quality concrete at very low temperatures. Flocrete SP5000M is chloride free.

APPLICATIONS

Flocrete SP5000M is recommended for use in conditions such as:

- » Concrete casting at low temperatures
- » Expected overnight frost.
- » Early concrete strength requirements
- » High strength concrete
- » Can be used as a sole additive to achieve required concrete performance at very low temperatures.

ADVANTAGES

Flocrete SP5000M provides for the following:

- » Improved workability without increased water content.
- » High reduction in water without loss of workability.
- » Increased frost resistance.
- » Improved early and long term strengths.
- » Chloride free - does not attack reinforcement.

COMPATIBILITY

Flocrete SP5000M is compatible with other DCP admixtures used in the same concrete mix. If more than one type of admixture will be used in the concrete mix, they must be dispensed to the concrete separately.

STANDARDS

Flocrete SP5000M complies with the following specifications:

- » EN 934-2, Table 12 and Table 7.
- » BS 5075.
- » ASTM C494, Type C and E.

METHOD OF USE

Flocrete SP5000M can be added to the mixing water prior to its addition to the concrete mix, or dispensed separately after the addition of mixing water.

TECHNICAL PROPERTIES @ 25°C:

Colour:	Clear yellowish
Freezing point:	-9°C
Specific gravity:	1.16 ± 0.03
Chloride content: BS5075	Nil
Air entrainment:	Typically less than 2% additional air is entrained above control mix at normal dosages

DOSAGE

Dosage of Flocrete SP5000M will vary depending on cement content and outside temperature. Required dosage should be determined for each case.

Typical dosage is between 0.3 - 1.5 kg/100 cement. Dosages outside the typical range given above may be used to meet particular requirements.

Consult Don Technical Department for further advice.

CLEANING

Flocrete SP5000M spillage should be collected by a suitable absorbent such as sand or vermiculite and transferred by a suitable container.

Flocrete SP5000M should not be allowed to enter sewers or open bodies of water. Dispose of in accordance with local environmental regulations.

PACKAGING

Flocrete SP5000M is available in 1000 litre.

STORAGE

Store in dry conditions. Flocrete SP5000M has a minimum shelf life of 12 months from date of manufacture if stored properly in its original unopened packing.

If these conditions are exceeded, contact DCP Technical Department for advice.

Don Construction Products

Str. Dârzei II, no. 235D, Village Mănăstirea
Crevedia, County Dâmbovița
Romania

info.romania@dcp-int.com; officeromania@dcp-int.com
www.dcp-int.com



Flocrete SP5000M

CAUTIONS

HEALTH AND SAFETY

Flocrete SP5000M is classified as a hazardous material. Flocrete SP5000M should not come into contact with skin and eyes.

In case of contact with eyes, immediately flush with plenty of water and seek medical attention.

For further information, refer to the Material Safety Data Sheet.

FIRE

Flocrete SP5000M is water based and is nonflammable.

MORE FROM DON CONSTRUCTION PRODUCTS

A wide range of construction chemical products are manufactured by DCP which include:

- » Concrete admixtures.
- » Surface treatments
- » Grouts and anchors.
- » Concrete repair.
- » Flooring systems.
- » Protective coatings.
- » Sealants.
- » Waterproofing.
- » Adhesives.
- » Tile adhesives and grouts.
- » Building products.
- » Structural strengthening.

Don Construction Products

Str. Dârzei II, no. 235D, Village Mănăstirea

Crevedia, County Dâmbovița

Romania

info.romania@dcp-int.com; officeromania@dcp-int.com

www.dcp-int.com

Note:

We endeavour to ensure that any information, advice or recommendation we may give in product literature is accurate and correct. However, because we have no control over where and how products are applied, we cannot accept any liability arising from the use of the products.

www.dcp-int.com

DCP Building Excellence