Flocrete® SP5000MW

Cold weather concreting admixture



DESCRIPTION

Flocrete SP5000MW is a multi-component, high performance concrete additive in liquid form for producing high quality concrete at very low temperatures. Flocrete SP5000MW is chloride free.

APPLICATIONS

Flocrete SP5000MW is recommended for use in conditions such as:

- » Concrete casting at low temperatures
- Expected overnight frost.
- Early concrete strength requirements
- > High strength concrete
- Can be used as a sole additive to achieve required concrete performance at very low temperatures.

ADVANTAGES

Flocrete SP5000MW provides for the following:

- > Improved workability without increased water content.
- » High reduction in water without loss of workability.
- > Increased frost resistance.
- » Improved early and long term strengths.
- » Chloride free does not attack reinforcement.

COMPATIBILITY

Flocrete SP5000MW is compatible with other DCP admixtures used in the same concrete mix. If more than one type of admixture will be used in the concrete mix, they must be dispensed to the concrete separately.

STANDARDS

Flocrete SP5000MW complies with ASTM C494, Type E, EN 934-2, Table 3.1, 3.2 & 7 and BS 5075.

METHOD OF USE

Flocrete SP5000MW can be added to the mixing water prior to its addition to the concrete mix, or dispensed separately after the addition of mixing water.

TECHNICAL PROPERTIES @ 25°C:

Colour: Yellowish to brownish liquid

Freezing point: -9°C

Specific gravity: 1.155 ± 0.03

Chloride content:

BS5075

Nil

Typically less than 2%

Air entrainment: additional air is entrained above control mix at normal

dosages

DOSAGE

Dosage of Flocrete SP5000MW will vary depending on cement content and outside temperature. Required dosage should be determined for each case.

Typical dosage is between 0.3 - 1.5 kg per 100 cement. Dosages outside the typical range given above may be used to meet particular requirements.

Consult DCP Technical Department for further advice.

CLEANING

Flocrete SP5000MW spillage should be collected by a suitable absorbent such as sand or vermiculite and transfered by a suitable container.

Flocrete SP5000MW should not be allowed to enter sewers or open bodies of water. Dispose of in accordance with local environmental regulations.

PACKAGING

Flocrete SP5000MW is available in 1000 litre.

STORAGE

Store in dry conditions. Flocrete SP5000MW has a minimum shelf life of 12 months from date of manufacture if stored properly in its original unopened packing.

If these conditions are exceeded, contact DCP Technical Department for advice.

Str. Dârzei II, no. 235D, Village Mănăstirea Crevedia, County Dâmbovița Romania info.romania@dcp-int.com; officeromania@dcp-int.com www.dcp-int.com



CAUTIONS

HEALTH AND SAFETY

Flocrete SP5000MW is classified as a hazardous material. Flocrete SP5000MW should not come into contact with skin and eyes.

In case of contact with eyes, immediately flush with plenty of water and seek medical attention.

For further information, refer to the Material Safety Data Sheet.

FIRE

Flocrete SP5000MW is water based and is nonflammable.

Flocrete® SP5000MW

MORE FROM DON CONSTRUCTION PRODUCTS

A wide range of construction chemical products are manufactured by DCP which include:

- Concrete admixtures.
- » Surface treatments
- Souts and anchors.
- Concrete repair.
- » Flooring systems.
- » Protective coatings.
- » Sealants.
- » Waterproofing.
- » Adhesives.
- » Tile adhesives and grouts.
- » Building products.
- » Structural strengthening.

Don Construction Products

Str. Dârzei II, no. 235D, Village Mănăstirea Crevedia, County Dâmbovița Romania info.romania@dcp-int.com; officeromania@dcp-int.com www.dcp-int.com

Note:

We endeavour to ensure that any information, advice or recommendation we may give in product literature is accurate and correct. However, because we have no control over where and how products are applied, we cannot accept any liability arising from the use of the products.