

Flocrete W55

Integral waterproofing admixture



Description

Flocrete W55 is liquid concrete waterproofing admixture formulated from selected polymers specially designed to reduce the concrete water permeability by reducing capillary voids within the concrete, which will last for the life of the concrete.

Applications

- ▲ To produce concrete with lower permeability.
- ▲ For water retaining structures and concrete substructures.

Advantages

- ▲ Minimizing segregation problems by improving cohesion.
- ▲ Improved workability reduces placing and compaction problems.
- ▲ More durable concrete due to lower permeability.

Compatibility

Flocrete W55 can be used with all types of Portland cement and cement replacement materials. Flocrete W55 is compatible with other DCP admixtures used in the same concrete mix. If more than one type of admixture is to be used in concrete mix, they must be dispensed to the concrete separately.

Standards

Flocrete W55 complies with ASTM C494, Type A.

Method of Use

Flocrete W55 should be added to the concrete with the mixing water to achieve optimum performance.

Automatic dispenser should be used to dispense the correct quantity of Flocrete W55 to the concrete mix.

Dosage

The guidance dosage of Flocrete W55 is 0.50 - 0.80 litres/ 100 kg of cementitious materials in the mix, including GGBFS, PFA or microsilica.

Technical Properties @ 25°C:

Color:	Brown liquid
Freezing point:	≈ -2°C
Specific gravity:	1.18 ± 0.01
Chloride content: BS5075	Nil
Air entrainment:	Typically less than 2% additional air is entrained above control mix at normal dosages

Representative trials should be conducted to determine the optimum dosage of Flocrete W55 to meet the performance requirements by using the materials and conditions in actual use.

Effects of Over Dosage

Over dosing of Flocrete W55 will cause the following:

- Significant increase in retardation.
- Increase in workability.

Ultimate concrete strength will not be adversely affected and will generally be increased provided that proper concrete curing is maintained.

Points to be considered in waterproof concrete

- Lower water to cement ratio gives lower permeability concrete.
- Good concrete placing and compaction are very important to produce waterproof concrete.
- Fresh concrete should be protected against rapid drying and cured properly.
- Cold joints must be avoided.

Cleaning

Flocrete W55 can be washed with fresh cold water.

Packaging

Flocrete W55 is available in 25 litres pails, 210 litres drums and 1000 litres bulks supply.

Flocrete W55

Storage

Flocrete W55 shelf life is 12 months if stored at temperatures between 2°C and 50°C.

If these conditions are exceeded, DCP Technical Department should be contacted for advice.

Cautions

Health and Safety

Flocrete W55 is not classified as hazardous material. Flocrete W55 should not come into contact with skin and eyes.

In case of contact with eyes wash immediately with plenty of water and seek medical advice promptly.

For further information refer to the Material Safety Data sheet.

Fire

Flocrete W55 is non-flammable.

More from Don Construction Products

A wide range of construction chemicals products are manufactured by DCP which include:

- ▲ Concrete admixtures.
- ▲ Grouts and chemical fixings.
- ▲ Concrete repairs.
- ▲ Industrial floorings.
- ▲ Structural protection.
- ▲ Waterproofing.

Note:

We endeavor to ensure that any advice, recommendation or information we may give in product literature is accurate and correct. However, due to the fact that we have no direct or continuous control over where or how the products are applied, DCP cannot accept any liability either directly or indirectly arising from the use of DCP products, whether or not in accordance with any advice, specification, recommendation or information given by us.

www.dcp-int.com



expertise



quality



full range