

Griptop® HD

Heavy-duty polyurethane floor screed



DESCRIPTION

Griptop HD is a three-pack water based polyurethane topping that provides floor surfaces with a seamless, hygienic, slip resistant and cosmetically attractive finish. It is designed for food and chemical processing areas and heavy-duty engineering areas, dairies, breweries etc.

Griptop HD can be steam cleaned and is resistant to boiling water and process liquids up to 120°C when applied at 9 mm or above. Griptop HD is applied by trowel and can be laid to falls. It has very good durability towards pedestrian and vehicular traffic. It also has very good resistance to many of the chemicals commonly found in an industrial environment (consult our Technical Department for further details).

Griptop HD can be supplied in a variety of colours (consult our Sales Department for further details).

ADVANTAGES

- » Hard wearing and excellent impact resistance.
- » Resistant to thermal shock and to temperatures -40°C to 120°C at 9 mm thickness; -40°C to 70°C at 6 mm thickness.
- » Provides hygienic floor.
- » Easy to clean.
- » Resistant to a wide range of chemicals (consult DCP Technical Department for more details).
- » Slip resistant.

STANDARDS

Griptop HD complies with EN 13813, SR-B2.0-AR0.5-IR10.

CHEMICAL RESISTANCE

Griptop HD provides resistance to a wide range of chemicals commonly encountered in the food and pharmaceutical industries, these chemicals include:

- » Acetic Acid (50%): found in spirit vinegar
- » Lactic Acid (10%) @ 60°C: found in milk & dairy products
- » Oleic Acid (100%) @ 60°C: used in food processing as an emulsifier
- » Citric Acid (25%): found in fruits
- » Methanol (100%): representative of alcohols & a range of solvents used in pharmaceuticals.

Griptop HD is also resistant to a wide range of inorganic acids, mineral oils, fats, fuels and solvents. Please contact DCP Technical Department for advice.

TECHNICAL PROPERTIES @ 25°C:

Mixed density:	2.0 ± 0.1 g/cm ³
Pot life:	20 - 30 min
Bond strength**: ASTM D4541	≥ 2 MPa @ 28 days (concrete failure)
Compressive strength*: BS 6319-2	≥ 50 MPa @ 28 days
Flexural strength*: BS 6319-3	≥ 14 MPa @ 28 days
Tensile strength*: BS 6319-7	≥ 5 MPa @ 28 days
Impact resistance: EN 13813	10 N.m
Taber abrasion: ASTM D4060 (1000 g, 1000 cycle) H22 wheel	950 milligram
Shore D hardness: ASTM D2240	≥ 80
Temperature resistance:	-40°C to 120°C @ 9 mm thickness -40°C to 70°C @ 6 mm thickness

* Tested at a density of 2.1 g/cm³.

**Primed concrete substrate.

Note: Some staining and discoloration may occur upon contact with certain chemicals, depending on the exposure time, nature and housekeeping regime employed. This will not adversely affect the performance of the product.

METHOD OF USE

SURFACE PREPARATION

The surface must be clean, dry (less than 75% RH measured by hygrometer) and free of laitance (see the DCP Guide to Surface Preparation for further details).

To ensure a good bond to the substrate, a 20 mm deep x 8 mm wide rebate must be cut around the edges of the floor, 150 mm from the walls, doorways, finished edges, plinths, etc and running parallel to them.

For treatment of surfaces containing expansion joints, consult our Technical Department.

Don Construction Chemicals India Private Limited

Kaveripettai, Thiruvallur Dist., Chennai, Tamil Nadu

RIICO Industrial Area, Manda Chomu, Jaipur

India

info.india@dcp-int.com; marketing.india@dcp-int.com

www.dcp-int.com

Griptop® HD

PRIMING

Scratch coat of Griptop HD; by mixing the Base Pack + Hardener Pack + 1/2 Filler Pack, should be applied by trowel at 0.5 - 1.0 mm prior to the application of the product itself as floor topping in order to provide a mechanical key between the substrate and the floor coating.

Follow the mixing procedure shown below to prepare the scratch coat layer of Griptop HD and apply it over clean prepared substrate.

The scratch coat should be left for 24 - 48 hours to cure before the application of Griptop HD. If the scratch coat is left for more than 48 hours, it is recommended to abrade the coat and apply a fresh coat.

For surfaces with RH between 75 and 85%, prime with one coat of Strongcoat DPM and allow to dry prior to application of the scratch coat. For surfaces with RH greater than 86%, prime with 2 coats of Strongcoat DPM and allow the second coat to dry before priming with scratch coat.

Consult DCP's technical department for further details about the priming procedure.

Note: Surfaces may also be primed with Strongcoat Primer on which 0.7 – 1.2 mm dry quartz aggregate is scattered at approximately 0.5 kg/m². (see Strongcoat Primer data sheet for further details).

MIXING

Taking care to ensure that the bottom and sides are thoroughly scraped, transfer the entire contents of the Griptop HD Hardener container into the Resin container and, using a Jiffy-type mixer attached to a slow running electric drill, mix for approximately two minutes.

Once the Griptop HD Hardener and Resin have been mixed, transfer all the mixed material into a Casco or Creteangle-type mixer, taking care to ensure that the bottom and sides are thoroughly scraped. Start the mixer and transfer to it the entire contents of the Griptop HD Filler container, taking care to ensure that these are completely dry and lump-free. Continue mixing for approximately two minutes.

Note: Never mix Griptop HD by hand as this could lead to areas of uncured material.

CHEMICAL RESISTANCE

Occasional spillage after full cure (28 days @ 25°C), ASTM D1308 (Spot - test @ 1 hr)

Organic Acids

Oleic Acid sat.	R
Citric Acid 25%	R
Acetic Acid 10%	R
Lactic Acid 10%	R
Tartaric Acid 10%	R

Inorganic Bases

Sodium Hydroxide 40%	R
Ammonia Solution 10%	R
Potassium Hydroxide 50%	R

Aqueous Solutions

Sodium Chloride sat	R
Chlorinated Water	R

Solvents

White Spirit	R
Xylene	R

Fuels

Petrol	R
Diesel	R
Engine Oil	R
Hydraulic Oil	R
Brake Fluid	R

Inorganic Acids

Hydrochloric Acid 10%	R
Nitric Acid 10%	R
Phosphoric Acid 20%	R
Sulphuric Acid 25%	R

Sugar Flavourings

Sugar solution sat.	R
Glucose syrup sat.	R

Carbonated beverages

Pepsi/Coca Cola	R
Mirinda/Fanta	R
7UP	R

Don Construction Chemicals India Private Limited

Kaveripettai, Thiruvallur Dist., Chennai, Tamil Nadu
RIICO Industrial Area, Manda Chomu, Jaipur
India

info.india@dcp-int.com; marketing.india@dcp-int.com
www.dcp-int.com

Griptop® HD

APPLICATION

Once mixing is complete, transfer the Griptop HD to the primed surface and, using a straight-edged steel trowel, apply it evenly.

When applying each kit of Griptop HD, leave approximately 200 mm of the closest working edge untrowelled as this will help the blending in of the next kit.

Take care not to excessively trowel the Griptop HD as this will lead to burnish marks on its surface.

Note: Griptop HD is not colour stable and may discolour on ageing and exposure to UV light, especially with light colours. This will not adversely affect the performance of the product.

WORKING TIME

Griptop HD has a working time of approximately 20 minutes at 25°C.

Note: Never leave the mixed Griptop HD kit to stand for any length of time before application, as this will considerably shorten its working time.

WORKING CONDITIONS

Griptop HD should not be applied at temperatures less than 5°C.

CURING TIME

At 25°C, Griptop HD can be opened to pedestrian traffic after 12 hours and heavy wheeled traffic after 24 hours.

At the same temperature, it should be allowed to cure for seven days before exposing it to chemical contamination (consult our Technical Department for details of curing times at other temperatures).

CLEANING AND HYGIENE

In order to enhance and maintain life expectancy, slip resistance and aesthetic properties, regular cleaning should be done using industry standard cleaning chemicals and equipment. Please contact DCP technical department for advice. Griptop HD can be steam cleaned at 9 mm.

CLEANING

Once mixing, application and finishing are complete, tools can be cleaned with Quickmast Solvent.

CHEMICAL RESISTANCE

Occasional spillage after full cure (28 days @ 25°C), ASTM D1308 (Spot - test @ 1 hr)

Electrochemical solutions

Copper Sulphate 1M	R
Zinc Sulphate 1M	R

Fruit juices

Orange juice	R
Apple juice	R
Lemon juice	R

Fats

Vegetable Oil	R
---------------	---

Cleaning Aids

Dishwashing liquid	R
--------------------	---

PACKAGING

Griptop HD is available in 30 kg (15 litre).

THICKNESS RANGE

6 - 9 mm.

COVERAGE

Approximately 2.5 m² per kit at 6 mm thickness.

STORAGE

Store at temperatures between 5°C and 30°C.

SHELF LIFE

Griptop HD have a shelf life of 9 months from date of manufacture if stored in unopened containers and under good conditions.

If these conditions are exceeded, DCP Technical Department should be contacted for advise.

CAUTIONS

HEALTH AND SAFETY

Consult the appropriate Material Safety Data Sheet prior to using each product.

Don Construction Chemicals India Private Limited

Kaveripettai, Thiruvallur Dist., Chennai, Tamil Nadu
RIICO Industrial Area, Manda Chomu, Jaipur
India

info.india@dcp-int.com; marketing.india@dcp-int.com
www.dcp-int.com



Griptop[®] HD

MORE FROM DON CONSTRUCTION PRODUCTS

A wide range of construction chemical products are manufactured by DCP which include:

- » Concrete admixtures.
- » Surface treatments
- » Grouts and anchors.
- » Concrete repair.
- » Flooring systems.
- » Protective coatings.
- » Sealants.
- » Waterproofing.
- » Adhesives.
- » Tile adhesives and grouts.
- » Building products.
- » Structural strengthening.

Don Construction Chemicals India Private Limited

Kaveripettai, Thiruvallur Dist., Chennai, Tamil Nadu
RIICO Industrial Area, Manda Chomu, Jaipur
India

info.india@dcp-int.com; marketing.india@dcp-int.com
www.dcp-int.com

Note:

We endeavour to ensure that any information, advice or recommendation we may give in product literature is accurate and correct. However, because we have no control over where and how products are applied, we cannot accept any liability arising from the use of the products.

www.dcp-int.com

DCP Building Excellence