

Griptop[®] MD

Medium to heavy duty flow applied polyurethane topping



DESCRIPTION

Griptop MD is a three-pack water based polyurethane topping that provides floor surfaces with a seamless, hygienic and cosmetically attractive matt finish. It is designed for medium to heavy duty food and chemical processing areas, dairies, breweries, etc.

Griptop MD is flow applied to horizontal surfaces and has very good durability towards pedestrian and vehicular traffic. It also has very good resistance to many of the chemicals commonly found in an industrial environment.

Griptop MD can be supplied in a variety of colours (consult our Sales Department for further details).

ADVANTAGES

- › Resistant to thermal shock and temperatures between -25°C to 80°C @ 6 mm thickness and -15°C to 60°C @ 4 mm thickness.
- › Easy to clean.
- › Resistant to a wide range of chemicals.
- › Hard wearing and good impact resistance.
- › Slip resistant.

STANDARDS

Griptop MD complies with EN13813, Class SR-B2.0-AR0.5-IR10.

CHEMICAL RESISTANCE

Griptop MD provides resistance to a wide range of chemicals commonly encountered in the food and pharmaceutical industries, these chemicals include:

- › Acetic Acid (50%): found in spirit vinegar
- › Lactic Acid (10%) @ 60°C: found in milk and dairy products
- › Oleic Acid (100%) @ 60°C: used in food processing as an emulsifier
- › Citric Acid (25%): found in fruits
- › Methanol (100%): representative of alcohols and a range of solvents used in pharmaceuticals.

Griptop MD is also resistant to a wide range of inorganic acids, mineral oils, fats, fuels and solvents. Please contact DCP Technical Department for advice.

Note: Some staining and discoloration may occur upon contact with certain chemicals, depending on the exposure time, nature and housekeeping regime employed. This will not adversely affect the performance of the product.

TECHNICAL PROPERTIES @ 25°C:

Mixed density:	1.90 ± 0.05 g/cm ³
Pot life:	20 - 30 min
Bond strength: ASTM D4541	≥ 2 MPa (concrete failure)
Compressive strength: BS 6319-2	≥ 48 MPa @ 28 days
Flexural strength: BS 6319-3	≥ 15 MPa @ 28 days
Tensile strength: BS 6319-7	≥ 6 MPa @ 28 days
Taber Abrasion: ASTM D4060 (1000 g, 1000 cycle) H22 Wheel CS17 Wheel	1200 milligram 75 milligram
Shore D hardness: ASTM D2240	≥ 80
Temperature resistance:	-15°C to 60°C @ 4 mm thickness -25°C to 80°C @ 6 mm thickness
Coefficient of thermal expansion: ASTM C531	4.5 x 10 ⁻⁵ /°C
Water absorption:	Nil

The above data was developed under controlled laboratory conditions. Properties in the field may vary. Expect reasonable variations from these results, depending on material and ambient temperature, jobsite and test conditions.

Don Construction Chemicals India Private Limited

Kaveripettai, Thiruvallur Dist., Chennai, Tamil Nadu

RIICO Industrial Area, Manda Chomu, Jaipur

India

info.india@dcp-int.com; marketing.india@dcp-int.com

www.dcp-int.com

METHOD OF USE

SURFACE PREPARATION

The surface must be clean, dry (less than 75% RH measured by hygrometer) and free of laitance (see the Guide to Surface Preparation for further details). To ensure a good bond to the substrate, saw cut grooves that are twice as wide and twice as deep as the screed thickness. The grooves must be opened at a distance of 5 to 10 cm from coves and walls, running parallel to them.

At all wall-to-floor junctions, a coving system shall be installed prior to the application of the floor screed to ensure a seamless and hygienic transition. The coving shall be formed using Griptop Cove Pack and sealed with Griptop Cove Pack Seal, applied to achieve a smooth, concave profile between the vertical and horizontal surfaces.

For treatment of surfaces containing expansion joints, consult DCP Technical Department.

PRIMING

For optimal performance, surfaces should be primed using Strongcoat Primer prior to the application of Griptop MD. The primer should be applied in accordance with its technical data sheet to ensure proper adhesion to the prepared substrate.

Where elevated substrate moisture is present, priming must be carried out using Strongcoat DPM. For surfaces with relative humidity (RH) between 75% and 85%, apply one coat and allow it to dry prior to subsequent application. For RH levels greater than 85%, apply two coats, ensuring the second coat is fully cured before proceeding.

As an alternative, where site conditions necessitate, a scratch coat of Griptop MD may be used as a priming layer. This should be applied by trowel at a thickness of 0.5 – 1.0 mm to provide a mechanical key between the substrate and the subsequent floor topping.

The scratch coat must be prepared following the prescribed mixing procedure and applied onto a clean, properly prepared substrate. It should be allowed to cure for 24 – 48 hours prior to the application of the main Griptop MD layer. If this interval is exceeded, the surface must be mechanically abraded and a fresh scratch coat applied.

The use of a scratch coat as a primer should be carefully assessed based on site conditions and is recommended only where appropriate.

CHEMICAL RESISTANCE

Occasional spillage, after full cure (28 days @ 25°C), ASTM D1308 (Spot - test @ 1 hr)

Organic Acids

Oleic Acid sat.	R
Citric Acid 25%	R
Acetic Acid 10%	R
Lactic Acid 10%	R
Tartaric Acid 10%	R

Inorganic Bases

Sodium Hydroxide 40%	R
Ammonia Solution 10%	R
Potassium Hydroxide 50%	R

Aqueous Solutions

Sodium Chloride sat.	R
Chlorinated Water	R

Solvents

White Spirit	R
Xylene	R

Fuels

Petrol	R
Diesel	R
Engine Oil	R
Hydraulic Oil	R
Brake Fluid	R

Inorganic Acids

Hydrochloric Acid 10%	R
Nitric Acid 10%	R
Phosphoric Acid 20%	R
Sulphuric Acid 25%	R

Sugar Flavourings

Sugar solution sat.	R
Glucose syrup sat.	R

Carbonated beverages

Pepsi/Coca Cola	R
Mirinda/Fanta	R
7UP	R

Griptop[®] MD

MIXING

Prior to mixing, stir the individual components to disperse any settlement. Transfer the entire contents of the hardener component to the resin component and using a Jiffy-type mixer attached to a slow running electric drill, or the rotary drum mixer, mix for approximately two minutes until a lump-free consistency is obtained. It is important to use a slow speed mixer, operating at 300 - 400 rpm, to ensure that there is no entrapped air and achieve a smooth mixture.

Once the Griptop MD hardener and resin components have been mixed, transfer all the mixed material into a Casco or Creteangletype mixer, taking care to ensure that the bottom and sides are thoroughly scraped. Start the mixer and gradually add the contents of the filler component. Continue mixing for approximately two minutes until a uniform, lump-free mix is obtained.

Note: Never mix Griptop MD by hand as this could lead to areas of uncured material.

APPLICATION

Once mixing is complete, transfer the mixed Griptop MD to the primed surface and spread it evenly using a pin rake set to the required thickness or a notched trowel. Immediately after spreading, use a spiked roller to roll the surface and release any entrapped air. Avoid repeating this rolling process later.

WORKING TIME

Griptop MD has a working time of approximately 20 minutes at 25°C.

Note: Never leave the mixed Griptop MD kit to stand for any length of time prior to application as this will considerably shorten its working time.

WORKING CONDITIONS

Griptop MD should not be applied at temperatures less than 10°C.

CURING TIME

At 25°C, Griptop MD can be opened to heavy wheeled traffic after 24 hours.

At the same temperature, it should be allowed to cure for seven days before exposing it to chemical contamination (consult our Technical Department for details of curing times at other temperatures).

CHEMICAL RESISTANCE

Occasional spillage, after full cure (28 days @ 25°C), ASTM D1308 (Spot - test @ 1 hr)

Electrochemical solutions

Copper Sulphate 1M	R
Zinc Sulphate 1M	R

Fruit juices

Orange juice	R
Apple juice	R
Lemon juice	R

Fats

Vegetable Oil	R
---------------	---

Cleaning Aids

Dishwashing liquid	R
--------------------	---

R: Resistant

SLIP RESISTANT FINISHES

For advice on slip resistant surfaces please consult our technical department.

LIMITATIONS

- » Ensure good ventilation in the application area to prevent excessive ambient humidity, which could affect the product's performance.
- » To minimise colour fading and the effect of efflorescence, protect the installed floor from damp, condensation, and water for 4 to 5 days.
- » The substrate and uncured floor must be kept at least 3°C above the dew point to reduce the risk of condensation or blooming on the surface.
- » In areas of exposure to direct UV light, Griptop MD is susceptible to some yellowing with time, especially with light Griptop MD colours. This will not adversely affect the performance of the product.

CLEANING

Once mixing, application and finishing are complete, tools can be cleaned with DCP Solvent.

PACKAGING

Griptop MD is available in 19 kg (10 litre).

THICKNESS RANGE

4 - 6 mm.

Don Construction Chemicals India Private Limited

Kaveripettai, Thiruvallur Dist., Chennai, Tamil Nadu

RIICO Industrial Area, Manda Chomu, Jaipur

India

info.india@dcp-int.com; marketing.india@dcp-int.com

www.dcp-int.com



Griptom[®] MD

COVERAGE

Approximately 2.5 m²/kit at 4 mm thickness.

STORAGE

Griptom MD has a shelf life of 6 months from date of manufacture if stored in unopened containers and under good conditions at temperatures between 5°C and 30°C.

If these conditions are exceeded, contact DCP Technical Department for advice.

CAUTIONS

HEALTH AND SAFETY

Griptom MD should not come in contact with skin or eyes. Goggles and gloves should be used.

In case of accidental contact with eyes, immediately flush with plenty of water for at least 10 minutes and seek medical advice if necessary.

For further information, refer to the Material Safety Data sheet.

MORE FROM DON CONSTRUCTION PRODUCTS

A wide range of construction chemical products are manufactured by DCP which include:

- » Concrete admixtures.
- » Surface treatments
- » Grouts and anchors.
- » Concrete repair.
- » Flooring systems.
- » Protective coatings.
- » Sealants.
- » Waterproofing.
- » Adhesives.
- » Tile adhesives and grouts.
- » Building products.
- » Structural strengthening.

Don Construction Chemicals India Private Limited

Kaveripettai, Thiruvallur Dist., Chennai, Tamil Nadu
RIICO Industrial Area, Manda Chomu, Jaipur
India

info.india@dcp-int.com; marketing.india@dcp-int.com

www.dcp-int.com

Note:

We endeavour to ensure that any information, advice or recommendation we may give in product literature is accurate and correct. However, because we have no control over where and how products are applied, we cannot accept any liability arising from the use of the products.

www.dcp-int.com

DCP Building Excellence