

# Grundix® BetonContact

Contact primer for gypsum plasters



## DESCRIPTION

Grundix BetonContact is a ready to use, solvent free acrylic based primer that improves the adhesion between the gypsum plaster and smooth concrete surfaces.

## APPLICATIONS

Grundix BetonContact provides adhesion between all types of smooth concrete surfaces with minimal water absorption and gypsum machine plasters. Contains organic binders and selected quartz sand, which make an excellent bond between the plaster and surface.

Recommended for:

- » Smooth concrete.
- » Ceilings of finished concrete elements.
- » Precast concrete elements.

## ADVANTAGES

- » Excellent adhesion to the concrete.
- » One-component, ready to use material.
- » Easy application.
- » Exterior and interior use.
- » Prevent water loss from the plaster to the surface.
- » Improves the mortar workability in its application.

## METHOD OF USE

### SURFACE PREPARATION

Surfaces should be clean, sound, dry. As well as free from oil, grease, dirt and loose particles.

### APPLICATION

Stir well Grundix BetonContact with slow-speed paddle. Grundix BetonContact is applied by brush, roller or spray machine. Do not dilute the material.

Leave to dry for 2 hours, depending on the specific conditions. In cool, damp weather drying may last longer. The surface must be completely dry and not sticky to touch before applying gypsum coverage.

Notes:

- » Grundix BetonContact is used only at temperatures of the surface, air and material itself above 5°C.
- » Not apply on wet, frozen or covered with condensation surfaces.

## TECHNICAL PROPERTIES:

Appearance:	Thick liquid
Density:	1.5 ± 0.05 g/cm <sup>3</sup>
Solid content:	63 ± 2%
Adhesion on substrate:	1.0 N/mm <sup>2</sup> @ 2 hr
Drying/Overcoating time:	2 hr
pH:	8.5 - 9.5
VOC:	≤ 20 g/ltr (comply with LEED)

## CLEANING

All tools should be cleaned immediately after finishing by clean water. Hardened materials can be cleaned mechanically.

## PACKAGING

Grundix BetonContact is available in 1.2, 5, and 20 kg packs.

## COVERAGE

Approximately 0.20 - 0.40 kg/m<sup>2</sup>, depending on substrate.

## STORAGE

Grundix BetonContact has a shelf life of 12 months from date of manufacture if stored in proper conditions, at temperatures range between 5°C and 35°C in its original unopened packing.

If these conditions are exceeded, contact DCP Technical Department for advice.

## Don Construction Products

Str. Dârzei II, no. 235D, Village Mănăstirea  
Crevedia, County Dâmbovița  
Romania

info.romania@dcp-int.com; officeromania@dcp-int.com  
www.dcp-int.com





# Grundix® BetonContact

## CAUTIONS

### HEALTH AND SAFETY

Grundix BetonContact does not fall within the list of dangerous substances according to current regulations. Avoid contact with skin and eyes. Sprayed places on the skin should immediately be washed with water. In case of contact with eyes wash immediately with plenty of water and seek medical advice.

For further information refer to the Material Safety Data Sheet.

### FIRE

Grundix BetonContact is nonflammable.

## MORE FROM DON CONSTRUCTION PRODUCTS

A wide range of construction chemical products are manufactured by DCP which include:

- » Concrete admixtures.
- » Surface treatments
- » Grouts and anchors.
- » Concrete repair.
- » Flooring systems.
- » Protective coatings.
- » Sealants.
- » Waterproofing.
- » Adhesives.
- » Tile adhesives and grouts.
- » Building products.
- » Structural strengthening.

### Don Construction Products

Str. Dârzei II, no. 235D, Village Mănăstirea  
Crevedia, County Dâmbovița

Romania

*info.romania@dcp-int.com; officeromania@dcp-int.com*

*www.dcp-int.com*

#### Note:

We endeavour to ensure that any information, advice or recommendation we may give in product literature is accurate and correct. However, because we have no control over where and how products are applied, we cannot accept any liability arising from the use of the products.

[www.dcp-int.com](http://www.dcp-int.com)

DCP Building Excellence



11-0018-RO-A-2026