# Hyperplast ES925

High performance early strength concrete hyperplasticiser



#### **DESCRIPTION**

Hyperplast ES925 is a high performance early strength concrete hyperplasticising admixture based on polycarboxylic polymers with long chains specially designed to enable the water content of the concrete to perform more effectively.

This effect can be used in high strength concrete and flowable concrete mixes, to achieve highest concrete durability and performance.

# **APPLICATIONS**

- » High strength and high performance concrete.
- » Structures with congested reinforcement.
- » Pre-cast concrete.
- >> Improved cohesion allowing for use in mass concrete pours and piling.
- » Self compacting concrete.
- » For the production of durable concrete.

#### **ADVANTAGES**

- » Optimises cement utilization.
- » High density and impermeable concrete through extreme water reduction.
- » Improves shrinkage and creep behaviors.
- » Minimises segregation and bleeding problems by improving cohesion.
- » Higher early and ultimate compressive strengths.
- Increases durability and resistance to aggressive atmospheric conditions thorough reduced permeability.

# **COMPATIBILITY**

Hyperplast ES925 can be used with all types of Portland cement and cement replacement materials. Hyperplast ES925 should not be used in conjunction with other admixtures unless DCP technical department approval is obtained.

#### **STANDARDS**

Hyperplast ES925 complies with ASTM C494, Type F.

# **METHOD OF USE**

Hyperplast ES925 should be added to the concrete with the mixing water to achieve optimum performance.

An automatic dispenser should be used to dispense the correct quantity of Hyperplast ES925 to the concrete mix.

# **TECHNICAL PROPERTIES @ 25°C:**

Colour: Brownish liquid

Specific gravity:  $1.04 \pm 0.03$ 

Typically less than 2% additional air is entrained

above control mix at normal

dosages

### **DOSAGE**

Air entrainment:

The recommended dosage of Hyperplast ES925 is 0.5 to 3.0% of cementitious materials in the mix, including GGBFS, PFA or microsilica.

Trials should be conducted to determine the optimum dosage of Hyperplast ES925 to meet the performance requirements by using the materials and conditions in actual use.

# **EFFECTS OF OVER DOSAGE**

Overdosage of Hyperplast ES925 will cause the following:

» Significant increase in retardation.

Ultimate concrete strength will not be adversely affected and will generally be increased provided that proper concrete curing is maintained.

#### **CLEANING**

Clean Hyperplast ES925 with fresh cold water.

# **PACKAGING**

Hyperplast ES925 is available in 25 litre pails, 210 litre drums and 1000 litre bulks supply.

# **STORAGE**

Hyperplast ES925 has a shelf life of 12 months from date of manufacture if stored at temperatures between 2°C and 50°C.

If these conditions are exceeded, contact DCP Technical Department for advice.



# **CAUTIONS**

# **HEALTH AND SAFETY**

Hyperplast ES925 is not classified as a hazardous material. Hyperplast ES925 should not come into contact with skin and eyes.

In case of contact with eyes, immediately flush with plenty of water and seek medical attention.

For further information, refer to the Material Safety Data Sheet

# **FIRE**

Hyperplast ES925 is nonflammable.

# Hyperplast ES925

# MORE FROM DON CONSTRUCTION PRODUCTS

A wide range of construction chemical products are manufactured by DCP which include:

- » Concrete admixtures.
- » Surface treatments
- >> Grouts and anchors.
- » Concrete repair.
- » Flooring systems.
- » Protective coatings.
- » Sealants.
- » Waterproofing.
- » Adhesives.
- » Tile adhesives and grouts.
- » Building products.
- » Structural strengthening.

# DCP Saudi Co.

Sulay, Industrial Area, Istanbul St., Riyadh Industrial City 3, Jeddah Saudi Arabia info.saudi@dcp-int.com www.dcp-int.com

#### Note:

We endeavour to ensure that any information, advice or recommendation we may give in product literature is accurate and correct. However, because we have no control over where and how products are applied, we cannot accept any liability arising from the use of the products.