

# Hyperplast PC119J

High performance concrete superplasticiser



## Description

Hyperplast PC119J is a high performance super plasticising admixture based on polycarboxylic polymers with long chains specially designed to enable the water content of the concrete to perform more effectively.

This effect can be used in high strength concrete and flowable concrete mixes, to achieve highest concrete durability and performance.

## Applications

- ▲ High strength and high performance concrete.
- ▲ Structures with congested reinforcement.
- ▲ Pre-cast concrete.
- ▲ Improved cohesion allow for use in mass concrete pours and piling.
- ▲ Self compacting concrete.

## Advantages

- ▲ Optimises cement utilization.
- ▲ High density and impermeable concrete through very high water reduction.
- ▲ Improves shrinkage and creep behaviors.
- ▲ Minimises segregation and bleeding problems by improving cohesion.
- ▲ Higher early and ultimate compressive strengths.
- ▲ Increases durability and resistance to aggressive atmospheric conditions thorough reduced permeability.

## Compatibility

Hyperplast PC119J is suitable to use with all types of Portland cement and cement replacement materials. Hyperplast PC119J should not be used in conjunction with other admixtures unless DCP Technical Department approval is obtained.

## Standards

Hyperplast PC119J complies with ASTM C494, Type G.

## Technical Properties @ 25°C:

Colour:	Brownish liquid
Freezing point:	≈ -1°C
Specific gravity:	1.04 ± 0.02
Air entrainment:	Typically less than 2% additional air is entrained above control mix at normal dosages

## Method of Use

Hyperplast PC119J should be added to the concrete with the mixing water to achieve optimum performance.

An automatic dispenser should be used to dispense the correct quantity of Hyperplast PC119J to the concrete mix.

## Dosage

The recommended dosage of Hyperplast PC119J is 0.9 - 3.0 litre per 100 kg of cementitious materials in the mix, including GGBFS, PFA or microsilica.

Representative trials should be conducted to determine the optimum dosage of Hyperplast PC119J to meet the performance requirements by using the materials and conditions in actual use.

## Effects of Over Dosage

Overdosage of Hyperplast PC119J will cause the following:

- ▲ Significant increase in retardation.
- ▲ Increase in workability.

Ultimate concrete strength will not be adversely affected and will generally be increased provided that proper concrete curing is maintained.

## Cleaning

Clean Hyperplast PC119J with fresh cold water.

# Hyperplast PC119J

## Packaging

Hyperplast PC119J is available in 25 litre pails, 210 litre drums and 1000 litre bulks supply.

## Storage

Hyperplast PC119J has a shelf life of 12 months from date of manufacture if stored at temperatures between 2°C and 50°C.

If these conditions are exceeded, contact DCP Technical Department for advice.

## Cautions

### Health and Safety

Hyperplast PC119J is not classified as a hazardous material. Hyperplast PC119J should not come into contact with skin and eyes.

In case of contact with eyes, immediately flush with plenty of water and seek medical attention.

For further information, refer to the Material Safety Data Sheet.

## Fire

Hyperplast PC119J is nonflammable.

## More from Don Construction Products

A wide range of construction chemical products are manufactured by DCP which include:

- ▲ Concrete admixtures.
- ▲ Surface treatments
- ▲ Grouts and anchors.
- ▲ Concrete repair.
- ▲ Flooring systems.
- ▲ Protective coatings.
- ▲ Sealants.
- ▲ Waterproofing.
- ▲ Adhesives.
- ▲ Tile adhesives and grouts.
- ▲ Building products.
- ▲ Structural strengthening.

### DCP Saudi Co.

Sulay industrial area,  
Riyadh, Saudi Arabia

[info.ksa@dcp-int.com](mailto:info.ksa@dcp-int.com)

#### Note:

We endeavor to ensure that any advice, recommendation or information we may give in product literature is accurate and correct. However, due to the fact that we have no direct or continuous control over where or how the products are applied, DCP cannot accept any liability either directly or indirectly arising from the use of DCP products, whether or not in accordance with any advice, specification, recommendation or information given by us.



[www.dcp-int.com](http://www.dcp-int.com)