

# Hyperplast PC173

High performance polycarboxylic ether based superplasticiser



## DESCRIPTION

Hyperplast PC173 is a high performance superplasticising admixture based on polycarboxylic ether polymers with long chains specially designed to enable the water content of the concrete to perform more effectively.

This effect can be used in high strength concrete and flowable concrete mixes, to achieve highest concrete durability and performance.

## APPLICATIONS

- » High strength and high performance concrete.
- » Structures with congested reinforcement.
- » Improved cohesion allow for use in mass concrete pours and piling.

## ADVANTAGES

- » Optimises cement utilization.
- » Improves shrinkage and creep behaviors.
- » High density and impermeable concrete through very high water reduction.
- » Higher early and ultimate compressive strengths.
- » Minimizes segregation and bleeding problems by improving cohesion.
- » Increases durability and resistance to aggressive atmospheric conditions thorough reduced permeability.

## COMPATIBILITY

Hyperplast PC173 is suitable to use with all types of Portland cement and cement replacement materials. Hyperplast PC173 should not be used in conjunction with other admixtures unless DCP Technical Department approval is obtained.

## STANDARDS

Hyperplast PC173 complies with ASTM C494, Type G, ASTM C1017 Type II and BS EN 934-2, Table 11.1/11.2.

## METHOD OF USE

Hyperplast PC173 should be added to the concrete with the mixing water to achieve optimum performance.

An automatic dispenser should be used to dispense the correct quantity of Hyperplast PC173 to the concrete mix.

## TECHNICAL PROPERTIES @ 25°C:

Colour:	Yellowish to brownish liquid
Specific gravity:	1.055 ± 0.02
Freezing point:	≈ -1°C
Air entrainment:	Typically less than 2% additional air is entrained above control mix at normal dosages

## DOSAGE

The recommended dosage of Hyperplast PC173 is 1.0 - 2.5 litre per 100 kg of cementitious materials in the mix, including GGBFS, PFA or microsilica.

Representative trials should be conducted to determine the optimum dosage of Hyperplast PC173 to meet the performance requirements by using the materials and conditions in actual use.

## EFFECTS OF OVERDOSAGE

Overdosage of Hyperplast PC173 will cause the following:

- » Significant increase in retardation.
- » Increase in workability.

Ultimate concrete strength will not be adversely affected and will generally be increased provided that proper concrete curing is maintained.

## CLEANING

Clean Hyperplast PC173 with fresh cold water.

## PACKAGING

Hyperplast PC173 is available in 25 litre pails, 210 litre drums and 1000 litre bulks supply.

## STORAGE

Hyperplast PC173 has a shelf life of 12 months from date of manufacture if stored at temperatures between 2°C and 50°C.

If these conditions are exceeded, contact DCP Technical Department for advice.



# Hyperplast PC173

## CAUTIONS

### HEALTH AND SAFETY

Hyperplast PC173 is not classified as a hazardous material. Hyperplast PC173 should not come into contact with skin and eyes.

In case of contact with eyes, immediately flush with plenty of water and seek medical attention.

For further information, refer to the Material Safety Data sheet.

### FIRE

Hyperplast PC173 is nonflammable.

## MORE FROM DON CONSTRUCTION PRODUCTS

A wide range of construction chemical products are manufactured by DCP which include:

- » Concrete admixtures.
- » Surface treatments
- » Grouts and anchors.
- » Concrete repair.
- » Flooring systems.
- » Protective coatings.
- » Sealants.
- » Waterproofing.
- » Adhesives.
- » Tile adhesives and grouts.
- » Building products.
- » Structural strengthening.

### Ayla for Building Materials Industry & Trade

Mosel Road, Erbil

Oweirj Industrial, Baghdad

[info.iraq@dcp-int.com](mailto:info.iraq@dcp-int.com)

[www.dcp-int.com](http://www.dcp-int.com)

Note:

We endeavour to ensure that any information, advice or recommendation we give in product literature is accurate and correct. However, because we have no control over where and how products are applied, we cannot accept any liability arising from the use of the products.

[www.dcp-int.com](http://www.dcp-int.com)

DCP Building Excellence