

Hyperplast PC185

High range water reducing admixture with workability retention properties



Description

Hyperplast PC185 is a high performance super plasticising admixture based on polycarboxylic polymers with long chains specially designed to enable the water content of the concrete to perform more effectively.

This effect can be used in high strength concrete and flowable concrete mixes, to achieve highest concrete durability and performance.

Applications

- ▲ Structures with congested reinforcement.
- ▲ High strength and high performance concrete.
- ▲ Improved cohesion allows for use in mass concrete pours and piling.

Advantages

- ▲ Optimises cement utilisation.
- ▲ Higher early and ultimate compressive strengths.
- ▲ Increases durability and resistance to aggressive atmospheric conditions thorough reduced permeability.
- ▲ High density and impermeable concrete through very high water reduction.
- ▲ Minimises segregation and bleeding problems by improving cohesion.
- ▲ Improves shrinkage and creep behaviours.

Standards

Hyperplast PC185 complies with ASTM C494, Type F & G, depending on dosage used.

Compatibility

Hyperplast PC185 can be used with all types of Portland cement and cement replacement materials.

Hyperplast PC185 should not be used in conjunction with other admixtures unless DCP technical department approval is obtained.

Method of Use

Hyperplast PC185 should be added to the concrete with the mixing water to achieve optimum performance.

Technical Properties @ 25°C

Colour:	Yellowish liquid
pH:	6 ± 1.0
Specific gravity:	1.07 ± 0.02
Chloride content:	Nil

Automatic dispenser should be used to dispense the correct quantity of Hyperplast PC185 to the concrete mix.

Dosage

The guidance dosage of Hyperplast PC185 is 0.40 - 2.50 liters/ 100 kg of cementitious materials in the mix, including GGBFS, PFA or microsilica.

Representative trials should be conducted to determine the optimum dosage of Hyperplast PC185 to meet the performance requirements by using the materials and conditions in actual use.

Effects of over dosage

Over dosing of Hyperplast PC185 will cause the following:

- Significant increase in retardation.
- Increase in workability.

Ultimate concrete strength will not be adversely affected and will generally be increased provided that proper concrete curing is maintained.

Cleaning

Hyperplast PC185 can be washed with fresh cold water.

Packaging

Hyperplast PC185 is available in 25 liters pails, 210 liters drums and 1000 liters bulks supply.

Storage

Hyperplast PC185 shelf life is 12 months if stored at temperatures between 2°C and 50°C.

Hyperplast PC185

If these conditions are exceeded, DCP Technical Department should be contacted for advice.

Cautions

Health and Safety

Hyperplast PC185 is not classified as hazardous material. Hyperplast PC185 should not come into contact with skin and eyes.

In case of contact with eyes wash immediately with plenty of water and seek medical advice promptly.

For further information refer to the Material Safety Data sheet.

Fire

Hyperplast PC185 is non flammable.

More from Don Construction Products


A wide range of construction chemical products are manufactured by DCP which include:

- ▲ Concrete admixtures.
- ▲ Surface treatments
- ▲ Grouts and anchors.
- ▲ Concrete repair.
- ▲ Flooring systems.
- ▲ Protective coatings.
- ▲ Sealants.
- ▲ Waterproofing.
- ▲ Adhesives.
- ▲ Tile adhesives and grouts.
- ▲ Building products.
- ▲ Structural strengthening.

Note:

We endeavor to ensure that any advice, recommendation or information we may give in product literature is accurate and correct. However, due to the fact that we have no direct or continuous control over where or how the products are applied, DCP cannot accept any liability either directly or indirectly arising from the use of DCP products, whether or not in accordance with any advice, specification, recommendation or information given by us.

 expertise

 quality

 full range

www.dcp-int.com