

# Hyperplast PC190

High performance early strength concrete hyperplasticiser



## Description

Hyperplast PC190 is a high performance early strength concrete hyperplasticising admixture based on polycarboxylic ether polymers with long chains specially designed to enable the water content of the concrete to perform more effectively.

This effect can be used in high strength concrete and flowable concrete mixes, to achieve highest concrete durability and performance.

## Applications

- ▲ High strength and high performance concrete.
- ▲ Structures with congested reinforcement.
- ▲ Pre-cast concrete.
- ▲ Improved cohesion allowing for use in mass concrete pours and piling.
- ▲ Self compacting concrete.

## Advantages

- ▲ Optimises cement utilisation.
- ▲ High density and impermeable concrete through extreme water reduction.
- ▲ Improves shrinkage and creep behaviours.
- ▲ Minimises segregation and bleeding problems by improving cohesion.
- ▲ Higher early and ultimate compressive strengths.
- ▲ Increases durability and resistance to aggressive atmospheric conditions thorough reduced permeability.

## Compatibility

Hyperplast PC190 can be used with all types of Portland cement and cement replacement materials. Hyperplast PC190 should not be used in conjunction with other admixtures unless DCP technical department approval is obtained.

## Standards

Hyperplast PC190 complies with ASTM C494 Type F and EN 934, Part2, Table 3.1 and 3.2, depending on dosage used.

### Technical Properties @ 25°C:

Color:	Yellowish to brownish liquid
Freezing point:	≈ -2°C
Specific gravity: ASTM C494/494M	1.04 ± 0.02
Sulphate content as SO <sub>3</sub> (% by weight): Gravimetry	0.01
Total Alkalies as Na <sub>2</sub> O equivalent (% by weight): BS EN480-12	0.95
Chloride content:	Nil
Air entrainment:	Typically less than 2% additional air is entrained above control mix at normal dosages

## Method of Use

Hyperplast PC190 should be added to the concrete with the mixing water to achieve optimum performance.

Automatic dispenser should be used to dispense the correct quantity of Hyperplast PC190 to the concrete mix.

## Dosage

The guidance dosage of Hyperplast PC190 is 0.5 - 3.0 litre per 100 kg of cementitious materials in the mix, including GGBFS, PFA or microsilica.

Trials should be conducted to determine the optimum dosage of Hyperplast PC190 to meet the performance requirements by using the materials and conditions in actual use.

## Effects of Over Dosage

Over dosing of Hyperplast PC190 will cause the following:

- ▲ Significant increase in retardation.

# Hyperplast PC190

Ultimate concrete strength will not be adversely affected and will generally be increased provided that proper concrete curing is maintained.

## Cleaning

Hyperplast PC190 can be washed with fresh cold water.

## Packaging

Hyperplast PC190 is available in 25 litre pails, 210 litre drums and 1000 litre bulks supply.

## Storage

Hyperplast PC190 has a shelf life of 12 months from date of manufacture if stored at temperatures between 2°C and 50°C.

If these conditions are exceeded, DCP Technical Department should be contacted for advice.

## Cautions

### Health and Safety

Hyperplast PC190 is not classified as hazardous material. Hyperplast PC190 should not come into contact with skin and eyes.

In case of contact with eyes wash immediately with plenty of water and seek medical advice promptly.

For further information refer to the Material Safety Data sheet.

### Fire

Hyperplast PC190 is nonflammable.

## More from Don Construction Products

A wide range of construction chemical products are manufactured by DCP which include:

- ▲ Concrete admixtures.
- ▲ Surface treatments
- ▲ Grouts and anchors.
- ▲ Concrete repair.
- ▲ Flooring systems.
- ▲ Protective coatings.
- ▲ Sealants.
- ▲ Waterproofing.
- ▲ Adhesives.
- ▲ Tile adhesives and grouts.
- ▲ Building products.
- ▲ Structural strengthening.

### Don Construction Products Qatar W.L.L

New Industrial Area, Street 21,  
Zone 81, bldg. # 9  
Doha - Qatar


#### Note:

We endeavor to ensure that any advice, recommendation or information we may give in product literature is accurate and correct. However, due to the fact that we have no direct or continuous control over where or how the products are applied, DCP cannot accept any liability either directly or indirectly arising from the use of DCP products, whether or not in accordance with any advice, specification, recommendation or information given by us.

[www.dcp-int.com](http://www.dcp-int.com)

 expertise

 quality

 full range