

Hyperplast PC203

High performance concrete superplasticiser



DESCRIPTION

Hyperplast PC203 is a high performance concrete superplasticizer admixture based on polycarboxylic polymers with long chains specially designed to enable the water content of the concrete to perform more effectively.

This effect can be used in high strength concrete and flowable concrete mixes, to achieve highest concrete durability and performance.

APPLICATIONS

- » High strength and high performance concrete.
- » Structures with congested reinforcement.
- » Precast concrete.
- » Improved cohesion allows for use in mass concrete pours and piling.
- » Self compacting concrete.

ADVANTAGES

- » Optimises cement utilisation.
- » High density and impermeable concrete through extreme water reduction.
- » Improves shrinkage and creep behaviours.
- » Minimizes segregation and bleeding problems by improving cohesion.
- » Higher early and ultimate compressive strengths.
- » Increases durability and resistance to aggressive atmospheric conditions through reduced permeability.

COMPATIBILITY

Hyperplast PC203 is suitable to use with all types of Portland cement and cement replacement materials. Hyperplast PC203 should not be used in conjunction with other admixtures unless DCP Technical Department approval is obtained.

STANDARDS

Hyperplast PC203 complies with EN 934-2:T3.1, T11.1, and ASTM C494, Type F and G, depending on dosage used.

TECHNICAL PROPERTIES @ 25°C:

Colour:	Brownish liquid
Freezing point:	-1°C
Specific gravity:	1.05 ± 0.02
pH:	5.5 - 6.5
Chloride content:	Nil
Air entrainment:	Typically less than 2% additional air is entrained above control mix at normal dosages

METHOD OF USE

Hyperplast PC203 should be added to the concrete with the mixing water to achieve optimum performance.

An automatic dispenser should be used to dispense the correct quantity of Hyperplast PC203 to the concrete mix.

DOSAGE

The recommended dosage of Hyperplast PC203 is 0.4 - 3.0 litres per 100 kg of cementitious materials in the mix, including GGBFS, PFA or microsilica.

Representative trials should be conducted to determine the optimum dosage of Hyperplast PC203 to meet the performance requirements by using the materials and conditions in actual use.

EFFECTS OF OVERDOSAGE

Overdosage of Hyperplast PC203 will cause the following:

- » Significant increase in retardation.

Ultimate concrete strength will not be adversely affected and will generally be increased provided that proper concrete curing is maintained.

CLEANING

Clean Hyperplast PC203 with fresh cold water.

DCP Saudi Co.

Sulay, Industrial Area, Istanbul St., Riyadh
Industrial City 3, Jeddah
Saudi Arabia
info.saudi@dcp-int.com
www.dcp-int.com



Hyperplast PC203

PACKAGING

Hyperplast PC203 is available in 25 litre pails, 210 litre drums and 1000 litre bulks supply.

STORAGE

Hyperplast PC203 has a shelf life of 12 months from date of manufacture if stored at temperatures between 2°C and 50°C.

If these conditions are exceeded, contact DCP Technical Department for advice.

CAUTIONS

HEALTH AND SAFETY

Hyperplast PC203 is not classified as a hazardous material. Hyperplast PC203 should not come into contact with skin and eyes.

In case of contact with eyes, immediately flush with plenty of water and seek medical attention.

For further information, refer to the Material Safety Data sheet.

FIRE

Hyperplast PC203 is nonflammable.

MORE FROM DON CONSTRUCTION PRODUCTS

A wide range of construction chemical products are manufactured by DCP which include:

- » Concrete admixtures.
- » Surface treatments
- » Grouts and anchors.
- » Concrete repair.
- » Flooring systems.
- » Protective coatings.
- » Sealants.
- » Waterproofing.
- » Adhesives.
- » Tile adhesives and grouts.
- » Building products.
- » Structural strengthening.

DCP Saudi Co.

Sulay, Industrial Area, Istanbul St., Riyadh
Industrial City 3, Jeddah
Saudi Arabia
info.saudi@dcp-int.com
www.dcp-int.com

Note:

We endeavour to ensure that any information, advice or recommendation we may give in product literature is accurate and correct. However, because we have no control over where and how products are applied, we cannot accept any liability arising from the use of the products.

www.dcp-int.com

DCP Building Excellence