

# Hyperplast PC230

High performance concrete admixture based on polycarboxylic polymers (Formerly known as Flocrete PC230)



## Description

Hyperplast PC230 is a high performance super plasticising admixture based on polycarboxylic polymers with long chains specially designed to enable the water content of the concrete to perform more effectively.

This effect can be used in high strength concrete and flowable concrete mixes, to achieve highest concrete durability and performance.

## Applications

- ▲ Structures with congested reinforcement.
- ▲ High strength and high performance concrete.
- ▲ Self compacting concrete.
- ▲ Pre-cast concrete.
- ▲ Improved cohesion allow for use in mass concrete pours and piling.

## Advantages

- ▲ Optimises cement utilization.
- ▲ High density and impermeable concrete through very high water reduction.
- ▲ Improves shrinkage and creep behaviors.
- ▲ Minimises segregation and bleeding problems by improving cohesion.
- ▲ Higher early and ultimate compressive strengths.
- ▲ Increases durability and resistance to aggressive atmospheric conditions thorough reduced permeability.

## Compatibility

Hyperplast PC230 can be used with all types of Portland cement and cement replacement materials.

Hyperplast PC230 should not be used in conjunction with other admixtures unless DCP Technical Department approval is obtained.

## Standards

Hyperplast PC230 complies with ASTM C494, Type G.

## Method of Use

Hyperplast PC230 should be added to the concrete with the mixing water to achieve optimum performance.

### Technical Properties @ 25°C:

Colour:	Yellowish to brownish liquid
Freezing point:	≈ -3°C
Specific gravity:	1.11
Air entrainment:	Typically less than 2% additional air is entrained above control mix at normal dosages

An automatic dispenser should be used to dispense the correct quantity of Hyperplast PC230 to the concrete mix.

## Dosage

The guidance dosage of Hyperplast PC230 is 0.5 - 2.5 litre per 100 kg of cementitious materials in the mix, including GGBFS, PFA or microsilica.

Representative trials should be conducted to determine the optimum dosage of Hyperplast PC230 to meet the performance requirements by using the materials and conditions in actual use.

## Effects of Over Dosage

Over dosing of Hyperplast PC230 will cause the following:

- ▲ Significant increase in retardation.
- ▲ Increase in workability.

Ultimate concrete strength will not be adversely affected and will generally be increased provided that proper concrete curing is maintained.

## Cleaning

Hyperplast PC230 can be washed with fresh cold water.

## Packaging

Hyperplast PC230 is available in 25 litre pails, 210 litre drums and 1000 litre bulks supply.

# Hyperplast PC230

## Storage

Hyperplast PC230 has a shelf life of 12 months from date of manufacture if stored at temperatures between 2°C and 50°C.

If these conditions are exceeded, DCP Technical Department should be contacted for advice.

## Cautions

### Health and Safety

Hyperplast PC230 is not classified as hazardous material. Hyperplast PC230 should not come into contact with skin and eyes.

In case of contact with eyes wash immediately with plenty of water and seek medical advice promptly.

For further information refer to the Material Safety Data Sheet.

## Fire

Hyperplast PC230 is nonflammable.

## More from Don Construction Products

A wide range of construction chemical products are manufactured by DCP which include:

- ▲ Concrete admixtures.
- ▲ Surface treatments
- ▲ Grouts and anchors.
- ▲ Concrete repair.
- ▲ Flooring systems.
- ▲ Protective coatings.
- ▲ Sealants.
- ▲ Waterproofing.
- ▲ Adhesives.
- ▲ Tile adhesives and grouts.
- ▲ Building products.
- ▲ Structural strengthening.

### Note:

We endeavor to ensure that any advice, recommendation or information we may give in product literature is accurate and correct. However, due to the fact that we have no direct or continuous control over where or how the products are applied, DCP cannot accept any liability either directly or indirectly arising from the use of DCP products, whether or not in accordance with any advice, specification, recommendation or information given by us.

[www.dcp-int.com](http://www.dcp-int.com)

