

Hyperplast PC262

High performance polycarboxylic ether based superplasticiser



Description

Hyperplast PC262 is a high performance superplasticising admixture based on polycarboxylic ether polymers with long chains specially designed to enable the water content of the concrete to perform more effectively.

This effect can be used in high strength concrete and flowable concrete mixes, to achieve highest concrete durability and performance.

Applications

- ▲ High strength and high performance concrete.
- ▲ Structures with congested reinforcement.
- ▲ Improved cohesion allow for use in mass concrete pours and piling.

Advantages

- ▲ Optimises cement utilization.
- ▲ Improves shrinkage and creep behaviors.
- ▲ High density and impermeable concrete through very high water reduction.
- ▲ Higher early and ultimate compressive strengths.
- ▲ Minimizes segregation and bleeding problems by improving cohesion.
- ▲ Increases durability and resistance to aggressive atmospheric conditions thorough reduced permeability.

Compatibility

Hyperplast PC262 suitable to use with all types of Portland cement and cement replacement materials. Hyperplast PC262 should not be used in conjunction with other admixtures unless DCP Technical Department approval is obtained.

Standards

Hyperplast PC262 complies with ASTM C494, Type G.

Technical Properties @ 25°C:

Colour:	Brownish liquid
Specific gravity:	1.06 ± 0.02
Freezing point:	≈ -1°C
Chloride content: EN 934-2	Chloride-free

Method of Use

Hyperplast PC262 should be added to the concrete with the mixing water to achieve optimum performance.

An automatic dispenser should be used to dispense the correct quantity of Hyperplast PC262 to the concrete mix.

Dosage

The recommended dosage of Hyperplast PC262 is 0.5 - 2.5 litre per 100 kg of cementitious materials in the mix, including GGBFS, PFA or microsilica.

Representative trials should be conducted to determine the optimum dosage of Hyperplast PC262 to meet the performance requirements by using the materials and conditions in actual use.

Effects of Over Dosage

Overdosage of Hyperplast PC262 will cause the following:

- ▲ Significant increase in retardation.
- ▲ Increase in workability.

Ultimate concrete strength will not be adversely affected and will generally be increased provided that proper concrete curing is maintained.

Cleaning

Clean Hyperplast PC262 with fresh cold water.

DCP Saudi Co.

Riyadh Offices:

Exit 9, Al Izdehar, Beside ACDelco Petrol Station

Jeddah Offices:

Al-Henaki Business Center, Tower C

Hyperplast PC262

Packaging

Hyperplast PC262 is available in 25 litre jerrycan, 210 litre drums and 1000 litre bulks supply.

Storage

Hyperplast PC262 has a shelf life of 12 months from the date of manufacture if stored at temperatures between 2°C and 50°C.

If these conditions are exceeded, contact DCP Technical Department for advice.

Cautions

Health and safety

Hyperplast PC262 is not classified as a hazardous material. Hyperplast PC262 should not come into contact with skin and eyes.

In case of contact with eyes, immediately flush with plenty of water and seek medical attention.

For further information, refer to the Material Safety Data sheet.

Fire

Hyperplast PC262 is nonflammable.

More from Don Construction Products

A wide range of construction chemical products are manufactured by DCP which include:

- ▲ Concrete admixtures.
- ▲ Surface treatments
- ▲ Grouts and anchors.
- ▲ Concrete repair.
- ▲ Flooring systems.
- ▲ Protective coatings.
- ▲ Sealants.
- ▲ Waterproofing.
- ▲ Adhesives.
- ▲ Tile adhesives and grouts.
- ▲ Building products.
- ▲ Structural strengthening.

DCP Saudi Co.

Riyadh Offices:


Exit 9, Al Izdehar, Beside ACDelco Petrol Station


Jeddah Offices:

Al-Henaki Business Center, Tower C

Note:

We endeavor to ensure that any advice, recommendation or information we may give in product literature is accurate and correct. However, due to the fact that we have no direct or continuous control over where or how the products are applied, DCP cannot accept any liability either directly or indirectly arising from the use of DCP products, whether or not in accordance with any advice, specification, recommendation or information given by us.

 expertise

 quality

 full range

www.dcp-int.com