Hyperplast PC340



High performance concrete admixture based on polycarboxylic polymers

DESCRIPTION

Hyperplast PC340 is a high performance super plasticising admixture based on polycarboxylic polymers with long chains specially designed to enable the water content of the concrete to perform more effectively.

This effect can be used in high strength concrete and flowable concrete mixes, to achieve highest concrete durability and performance.

APPLICATIONS

- » To produce high quality concrete of improved durability and water tightness.
- High strength and high performance concrete.
- » Improved cohesion allow for use in mass concrete pours and piling.

ADVANTAGES

- Optimises cement utilization.
- » High density and impermeable concrete through very high water reduction.
- » Improves shrinkage and creep behaviors.
- » Minimises segregation and bleeding problems by improving cohesion.
- » Higher early and ultimate compressive strengths.
- Increases durability and resistance to aggressive atmospheric conditions thorough reduced permeability.

COMPATIBILITY

Hyperplast PC340 is suitable to use with all types of Portland cement and cement replacement materials. Hyperplast PC340 should not be used in conjunction with other admixtures unless DCP Technical Department approval is obtained.

STANDARDS

Hyperplast PC340 complies with ASTM C494, Type F and G, depending on the dosage.

METHOD OF USE

Hyperplast PC340 should be added to the concrete with the mixing water to achieve optimum performance.

An automatic dispenser should be used to dispense the correct quantity of Hyperplast PC340 to the concrete mix.

TECHNICAL PROPERTIES @ 25°C:

Colour: Yellowish to brownish liquid

Freezing point: ≈ -3°C

Specific gravity: 1.06 ± 0.02

Chloride content:

Typically less than 2% additional air is entrained above control mix at normal

dosages

DOSAGE

Air entrainment:

The recommended dosage of Hyperplast PC340 is 0.5 -2.5 litre per 100 kg of cementitious materials in the mix, including GGBFS, PFA or microsilica.

Representative trials should be conducted to determine the optimum dosage of Hyperplast PC340 to meet the performance requirements by using the materials and conditions in actual use.

EFFECTS OF OVERDOSAGE

Overdosage of Hyperplast PC340 will cause the following:

- » Significant increase in retardation.
- » Increase in workability.

Ultimate concrete strength will not be adversely affected and will generally be increased provided that proper concrete curing is maintained.

CLEANING

Clean Hyperplast PC340 with fresh cold water.

PACKAGING

Hyperplast PC340 is available in 25 litre pails, 210 litre drums and 1000 litre bulks supply.



STORAGE

Hyperplast PC340 has a shelf life of 12 months from date of manufacture if stored at temperatures between 2°C and 50°C.

If these conditions are exceeded, contact DCP Technical Department for advice.

CAUTIONS

HEALTH AND SAFETY

Hyperplast PC340 is not classified as a hazardous material. Hyperplast PC340 should not come into contact with skin and eyes.

In case of contact with eyes, immediately flush with plenty of water and seek medical attention.

For further information, refer to the Material Safety Data Sheet.

FIRE

Hyperplast PC340 is nonflammable.

Hyperplast PC340

MORE FROM DON CONSTRUCTION PRODUCTS

A wide range of construction chemical products are manufactured by DCP which include:

- » Concrete admixtures.
- » Surface treatments
- Grouts and anchors.
- » Concrete repair.
- » Flooring systems.
- » Protective coatings.
- » Sealants.
- Waterproofing.
- » Adhesives.
- » Tile adhesives and grouts.
- » Building products.
- » Structural strengthening.

Don Construction Products Qatar W.L.L

New Industrial Area, Doha, Qatar info.qatar@dcp-int.com www.dcp-int.com

Note:

We endeavour to ensure that any information, advice or recommendation we may give in product literature is accurate and correct. However, because we have no control over where and how products are applied, we cannot accept any liability arising from the use of the products.