

# Hyperplast PC356-A

High performance concrete admixture based on polycarboxylic polymers



## DESCRIPTION

Hyperplast PC356-A is a high performance super plasticising admixture based on polycarboxylic polymers with long chains specially designed to enable the water content of the concrete to perform more effectively.

This effect can be used in high strength concrete and flowable concrete mixes, to achieve highest concrete durability and performance.

## APPLICATIONS

- » To produce high quality concrete of improved durability and water tightness.
- » High strength and high performance concrete.
- » Improved cohesion allow for use in mass concrete pours and piling.

## ADVANTAGES

- » Optimises cement utilization.
- » High density and impermeable concrete through very high water reduction.
- » Improves shrinkage and creep behaviors.
- » Minimises segregation and bleeding problems by improving cohesion.
- » Higher early and ultimate compressive strengths.
- » Increases durability and resistance to aggressive atmospheric conditions thorough reduced permeability.

## COMPATIBILITY

Hyperplast PC356-A can be used with all types of Portland cement and cement replacement materials. Hyperplast PC356-A should not be used in conjunction with other admixtures unless DCP Technical Department approval is obtained.

## STANDARDS

Hyperplast PC356-A complies with ASTM C494, Type G.

## METHOD OF USE

Hyperplast PC356-A should be added to the concrete with the mixing water to achieve optimum performance.

An automatic dispenser should be used to dispense the correct quantity of Hyperplast PC356-A to the concrete mix.

## TECHNICAL PROPERTIES @ 25°C:

Colour:	Yellowish to brownish liquid
Freezing point:	≈ -3°C
Specific gravity:	1.06 ± 0.02
Chloride content:	Nil
Air entrainment:	Typically less than 2% additional air is entrained above control mix at normal dosages

## DOSAGE

The recommended dosage of Hyperplast PC356-A is 0.5 - 2.5 litre per 100 kg of cementitious materials in the mix, including GGBFS, PFA or microsilica.

Representative trials should be conducted to determine the optimum dosage of Hyperplast PC356-A to meet the performance requirements by using the materials and conditions in actual use.

## EFFECTS OF OVERDOSAGE

Overdosage of Hyperplast PC356-A will cause the following:

- » Significant increase in retardation.
- » Increase in workability.

Ultimate concrete strength will not be adversely affected and will generally be increased provided that proper concrete curing is maintained.

## CLEANING

Clean Hyperplast PC356-A with fresh cold water.

## PACKAGING

Hyperplast PC356-A is available in 25 litre jerrycan, 210 litre drums and 1000 litre bulks supply.



# Hyperplast PC356-A

## STORAGE

Hyperplast PC356-A has a shelf life of 12 months from date of manufacture if stored at temperatures between 2°C and 50°C.

If these conditions are exceeded, contact DCP Technical Department for advice.

## CAUTIONS

## HEALTH AND SAFETY

Hyperplast PC356-A is not classified as a hazardous material. Hyperplast PC356-A should not come into contact with skin and eyes.

In case of contact with eyes, immediately flush with plenty of water and seek medical attention.

For further information, refer to the Material Safety Data Sheet.

## FIRE

Hyperplast PC356-A is nonflammable.

## MORE FROM DON CONSTRUCTION PRODUCTS

A wide range of construction chemical products are manufactured by DCP which include:

- » Concrete admixtures.
- » Surface treatments
- » Grouts and anchors.
- » Concrete repair.
- » Flooring systems.
- » Protective coatings.
- » Sealants.
- » Waterproofing.
- » Adhesives.
- » Tile adhesives and grouts.
- » Building products.
- » Structural strengthening.

### Note:

We endeavour to ensure that any information, advice or recommendation we may give in product literature is accurate and correct. However, because we have no control over where and how products are applied, we cannot accept any liability arising from the use of the products.