# Hyperplast PC570

High performance polycarboxilic based, concrete superplasticiser



# Description

Hyperplast PC570 is a high performance superplasticising admixture based on polycarboxylic polymers with long chains specially designed to enable the water content of the concrete to perform more effectively.

This effect can be used in high strength, low w/c ratio and flowable concrete mixes, to achieve highest concrete durability and performance in the readymix and precast concrete industries.

## Applications

- ▲ High strength and high performance concrete.
- ▲ Pre-cast concrete.
- Improved cohesion allow for use in mass concrete pours and piling.
- ▲ High durability concrete.
- ▲ Structures with congested reinforcement.
- ▲ Self compacting concrete.

## Advantages

- ▲ Optimises cement utilisation.
- ▲ Improves shrinkage and creep behaviors.
- High density and impermeable concrete through very high water reduction.
- Increases durability and resistance to aggressive atmospheric conditions thorough reduced permeability.
- Minimises segregation and bleeding problems by improving cohesion.
- ▲ Higher early and ultimate compressive strengths.

## Compatibility

Hyperplast PC570 can be used with all types of Portland cement and cement replacement materials. Hyperplast PC570 should not be used in conjunction with other admixtures unless DCP Technical Department approval is obtained.

# Standards

Hyperplast PC570 complies with BS EN 934-2 : Table 3.1, Table 3.2 and ASTM C494, Type F.

### Technical Properties @ 25°C:

Color:	Yellowish to brownish liquid
Freezing point:	-1°C
Specific gravity:	1.07 ± 0.02
Chloride content: BS5075	Nil
Air entrainment:	Typically less than 2% at normal dosages

# Method of Use

Hyperplast PC570 should be added to the concrete with the mixing water to achieve optimum performance.

Automatic dispenser should be used to dispense the correct quantity of Hyperplast PC570 to the concrete mix.

### Dosage

The guidance dosage of Hyperplast PC570 is 0.5 - 2.5 liters per 100 kg of cementitious materials in the mix, including GGBFS, PFA or microsilica.

Representative trials should be conducted to determine the optimum dosage of Hyperplast PC570 to meet the performance requirements by using the materials and conditions in actual use.

## Effects of Over Dosage

Over dosing of Hyperplast PC570 will cause the following:

- ▲ Significant increase in retardation.
- ▲ Increase in workability.

Ultimate concrete strength will not be adversely affected and will generally be increased provided that proper concrete curing is maintained.

# Cleaning

Hyperplast PC570 can be washed with fresh cold water.

**Don Construction Products Qatar W.L.L** New Industrial Area, Street 21, Zone 81, bldg. # 9 Doha - Qatar

# Hyperplast PC570

## Packaging

Hyperplast PC570 is available in 25 litre pails, 210 litre drums and 1000 litre bulks supply.

### Storage

Hyperplast PC570 has a shelf life of 12 months from date of manufacture if stored at temperatures between  $2^{\circ}C$  and  $50^{\circ}C$ .

If these conditions are exceeded, DCP Technical Department should be contacted for advice.

## Cautions

### Health and Safety

Hyperplast PC570 is not classified as hazardous material. Hyperplast PC570 should not come into contact with skin and eyes.

In case of contact with eyes wash immediately with plenty of water and seek medical advice promptly.

For further information refer to the Material Safety Data sheet.

### Fire

Hyperplast PC570 is nonflammable.

## More from Don Construction Products

A wide range of construction chemical products are manufactured by DCP which include:

- ▲ Concrete admixtures.
- ▲ Surface treatments
- ▲ Grouts and anchors.
- ▲ Concrete repair.
- ▲ Flooring systems.
- ▲ Protective coatings.
- ▲ Sealants.
- ▲ Waterproofing.
- ▲ Adhesives.
- ★ Tile adhesives and grouts.
- ▲ Building products.
- ▲ Structural strengthening.

### **Don Construction Products Qatar W.L.L** New Industrial Area, Street 21, Zone 81, bldg. # 9 Doha - Qatar

#### Note:

We endeavor to ensure that any advice, recommendation or information we may give in product literature is accurate and correct. However, due to the fact that we have no direct or continuous control over where or how the products are applied, DCP cannot accept any liability either directly or indirectly arising from the use of DCP products, whether or not in accordance with any advice, specification, recommendation or information given by us.

## www.dcp-int.com

🗑 expertise

 $\langle \mathfrak{I} \rangle$  full range

01-0176-A-2019