

# Hyperplast PC602

High performance polycarboxylic based, concrete superplasticiser



## DESCRIPTION

Hyperplast PC602 is a high performance super plasticising admixture based on polycarboxylic polymers with long chains specially designed to enable the water content of the concrete to perform more effectively.

This effect can be used in high strength, low W/C ratio and flowable concrete mixes, to achieve highest concrete durability and performance in the readymix and precast concrete industries.

## APPLICATIONS

- » High strength and high performance concrete.
- » Pre-cast concrete.
- » Improved cohesion allow for use in mass concrete pours and piling.
- » High durability concrete.
- » Structures with congested reinforcement.
- » For high levels concrete pumping.
- » Self compacting concrete.

## ADVANTAGES

- » Optimises cement utilization.
- » Improves shrinkage and creep behaviors.
- » High density and impermeable concrete through very high water reduction.
- » Increases durability and resistance to aggressive atmospheric conditions thorough reduced permeability.
- » Minimizes segregation and bleeding problems by improving cohesion.
- » Higher early and ultimate compressive strengths.

## COMPATIBILITY

Hyperplast PC602 is suitable to use with all types of Portland cement and cement replacement materials. Hyperplast PC602 should not be used in conjunction with other admixtures unless DCP Technical Department approval is obtained.

## STANDARDS

Hyperplast PC602 complies with BS 5075, Part 3 and with ASTM C494 as Type F and G, depending on dosage used.

## METHOD OF USE

Hyperplast PC602 should be added to the concrete with the mixing water to achieve optimum performance.

An automatic dispenser should be used to dispense the correct quantity of Hyperplast PC602 to the concrete mix.

## TECHNICAL PROPERTIES @ 25°C:

Colour:	Yellowish to brownish liquid
Freezing point:	-1°C
Specific gravity:	1.07 ± 0.02
pH:	5 - 7
Chloride content: BS 5075	Nil
Air entrainment:	Typically less than 2% at normal dosages

## DOSAGE

The recommended dosage of Hyperplast PC602 is 0.5 - 2.5 litre per 100 kg of cementitious materials in the mix, including GGBFS, PFA or microsilica.

Representative trials should be conducted to determine the optimum dosage of Hyperplast PC602 to meet the performance requirements by using the materials and conditions in actual use.

## EFFECTS OF OVER DOSAGE

Overdosage of Hyperplast PC602 will cause the following:

- » Significant increase in retardation.
- » Increase in workability.

Ultimate concrete strength will not be adversely affected and will generally be increased provided that proper concrete curing is maintained.

## CLEANING

Clean Hyperplast PC602 with fresh cold water.

## PACKAGING

Hyperplast PC602 is available in 25 litre pails, 210 litre drums and 1000 litre bulks supply.

## STORAGE

Hyperplast PC602 has a shelf life of 12 months from date of manufacture if stored at temperatures between 2°C and 50°C.

If these conditions are exceeded, contact DCP Technical Department for advice.

## DCP Saudi Co.

Sulay, Industrial Area, Istanbul St., Riyadh  
Industrial City 3, Jeddah  
Saudi Arabia  
[info.saudi@dcp-int.com](mailto:info.saudi@dcp-int.com)  
[www.dcp-int.com](http://www.dcp-int.com)



# Hyperplast PC602

## CAUTIONS

### HEALTH AND SAFETY

Hyperplast PC602 is not classified as a hazardous material. Hyperplast PC602 should not come into contact with skin and eyes.

In case of contact with eyes, immediately flush with plenty of water and seek medical attention.

For further information, refer to the Material Safety Data sheet.

### FIRE

Hyperplast PC602 is nonflammable.

## MORE FROM DON CONSTRUCTION PRODUCTS

A wide range of construction chemical products are manufactured by DCP which include:

- » Concrete admixtures.
- » Surface treatments
- » Grouts and anchors.
- » Concrete repair.
- » Flooring systems.
- » Protective coatings.
- » Sealants.
- » Waterproofing.
- » Adhesives.
- » Tile adhesives and grouts.
- » Building products.
- » Structural strengthening.

### DCP Saudi Co.

Sulay, Industrial Area, Istanbul St., Riyadh

Industrial City 3, Jeddah

Saudi Arabia

[info.saudi@dcp-int.com](mailto:info.saudi@dcp-int.com)

[www.dcp-int.com](http://www.dcp-int.com)

#### Note:

We endeavour to ensure that any information, advice or recommendation we may give in product literature is accurate and correct. However, because we have no control over where and how products are applied, we cannot accept any liability arising from the use of the products.

[www.dcp-int.com](http://www.dcp-int.com)

DCP Building Excellence