

# Hyperplast PC808

High performance polycarboxylic based, concrete superplasticiser



## Description

Hyperplast PC808 is a high performance super plasticising admixture based on polycarboxylic polymers with long chains specially designed to enable the water content of the concrete to perform more effectively.

This effect can be used in high strength, low W/C ratio and flowable concrete mixes, to achieve highest concrete durability and performance in the readymix and precast concrete industries.

## Applications

- ▲ High strength and high performance concrete.
- ▲ Pre-cast concrete.
- ▲ Improved cohesion allow for use in mass concrete pours and piling.
- ▲ High durability concrete.
- ▲ Structures with congested reinforcement.
- ▲ For high levels concrete pumping.
- ▲ Self compacting concrete.

## Advantages

- ▲ Optimises cement utilization.
- ▲ Improves shrinkage and creep behaviors.
- ▲ High density and impermeable concrete through very high water reduction.
- ▲ Increases durability and resistance to aggressive atmospheric conditions thorough reduced permeability.
- ▲ Minimizes segregation and bleeding problems by improving cohesion.
- ▲ Higher early and ultimate compressive strengths.

## Compatibility

Hyperplast PC808 suitable to use with all types of Portland cement and cement replacement materials. Hyperplast PC808 should not be used in conjunction with other admixtures unless DCP Technical Department approval is obtained.

## Standards

Hyperplast PC808 complies with BS EN934-2:1998 and ASTM C494, Type D and G.

## Technical Properties @ 25°C:

Color:	Brown liquid
Freezing point:	-1°C
Specific gravity:	1.10 ± 0.02
Chloride content: BS5075	Nil

## Method of Use

Hyperplast PC808 should be added to the concrete with the mixing water to achieve optimum performance.

An automatic dispenser should be used to dispense the correct quantity of Hyperplast PC808 to the concrete mix.

## Dosage

The recommended dosage of Hyperplast PC808 is 0.5 - 2.5 liters per 100 kg of cementitious materials in the mix, including GGBFS, PFA or microsilica.

Representative trials should be conducted to determine the optimum dosage of Hyperplast PC808 to meet the performance requirements by using the materials and conditions in actual use.

## Effects of Over Dosage

Overdosage of Hyperplast PC808 will cause the following:

- ▲ Significant increase in retardation.
- ▲ Increase in workability.

Ultimate concrete strength will not be adversely affected and will generally be increased provided that proper concrete curing is maintained.

## Cleaning

Clean Hyperplast PC808 with fresh cold water.

## Packaging

Hyperplast PC808 is available in 25 litre jerrycans, 210 litre drums and 1000 litre bulks supply.

### DCP Saudi Co.

Riyadh Offices:

Exit 9, Al Izdehar, Beside ACDelco Petrol Station

Jeddah Offices:

Al-Henaki Business Center, Tower C

# Hyperplast PC808

## Storage

Hyperplast PC808 has a shelf life of 12 months from date of manufacture if stored at temperatures between 2°C and 50°C.

If these conditions are exceeded, contact DCP Technical Department for advice.

## Cautions

### Health and Safety

Hyperplast PC808 is not classified as a hazardous material. Hyperplast PC808 should not come into contact with skin and eyes.

In case of contact with eyes, immediately flush with plenty of water and seek medical attention.

For further information, refer to the Material Safety Data sheet.

## Fire

Hyperplast PC808 is nonflammable.

## More from Don Construction Products

A wide range of construction chemical products are manufactured by DCP which include:

- ▲ Concrete admixtures.
- ▲ Surface treatments
- ▲ Grouts and anchors.
- ▲ Concrete repair.
- ▲ Flooring systems.
- ▲ Protective coatings.
- ▲ Sealants.
- ▲ Waterproofing.
- ▲ Adhesives.
- ▲ Tile adhesives and grouts.
- ▲ Building products.
- ▲ Structural strengthening.

### DCP Saudi Co.

#### Riyadh Offices:

Exit 9, Al Izdehar, Beside ACDelco Petrol Station


#### Jeddah Offices:


Al-Henaki Business Center, Tower C

#### Note:

We endeavor to ensure that any advice, recommendation or information we may give in product literature is accurate and correct. However, due to the fact that we have no direct or continuous control over where or how the products are applied, DCP cannot accept any liability either directly or indirectly arising from the use of DCP products, whether or not in accordance with any advice, specification, recommendation or information given by us.

 expertise

 quality

 full range

[www.dcp-int.com](http://www.dcp-int.com)