

Hyperseal DP-2010H

High performance hydrophilic waterstops for use with fresh and sea water



DESCRIPTION

Hyperseal DP-2010H is made of bentonite free high performance polymer modified chloroprene rubber strips. The swelling action is the result between water (fresh or saline) and hydrophilic groups which are part of the Hyperseal DP-2010H molecular structure.

Expansion of the waterstop creates a positive seal against the face of the concrete joint and prevents the water entry into the structure through the protected joint.

APPLICATIONS

Hydrophilic waterstop can be applied against existing concrete and are simply installed by nailing or using a hydrophilic adhesive. In contact with water, hydrophilic strips react and swell by a minimum of 150% of their original dimensions to form a compression seal.

ADVANTAGES

- » Active protection- Hyperseal DP-2010H hydrophilic waterstop swells in contact with both fresh water and saline (sea) water to form an effective compression joint.
- » Slow expansion rate to prevent damage to freshly placed concrete during curing.
- » Retains original shape after repeated expansion and contraction.
- » Resistant against fuel hydrocarbon spillages.

STANDARDS

Hyperseal DP-2010H complies with KS M 6518.

METHOD OF INSTALLATION

Hyperseal DP-2010H can be installed either by suitable adhesive using Hyperseal DPS-200 or mechanically by nails. When using Hyperseal DPS-200 adhesive, extrude enough materials on a sound clean substrates and immediately fix firmly Hyperseal DP-2010H into Hyperseal DPS-200 adhesive.

Also Hyperseal DP-2010H can be fastened in place using masonry nails of 400 - 600 mm length at approximately 300 mm centers, provided that the nails are penetrating around 20 mm into the substrate and sufficient distance is provided between the top of the nail and Hyperseal DP-2010H.



TECHNICAL PROPERTIES:

Colour:	Black, blue, or red
Service temperature range:	-30 to 70°C
Expansion volume:	
Fresh water	150 - 200%
Saline water	80 - 100%
Hydrostatic pressure resistance:	> 50 m (5 bars)

Care should be taken however to ensure that the substrate has sufficient strength to enable a mechanical fixing to be securely driven without damaging the Hyperseal DP-2010H. Alternatively, a groove can be cast into concrete to facilitate application.

Hyperseal DP-2010H is suitable for use in most weather conditions, but heavy rain or prolonged immersion will cause premature swelling. Should this occur, it will be necessary to allow it to dry out, or be dried with a hot air gun before concrete pouring takes place.

Hyperseal DP-2010H should not be used in expansion joints, or any concrete section of less than 150 mm width.



Hyperseal DP-2010H

PACKAGING

Sheet sizes:
DP-2010, (H): 20 mm x 10 mm . (10 m x 10 rolls/box).

Other sizes are available upon request

CAUTIONS

HEALTH AND SAFETY

There are no known hazards associated with Hyperseal during normal use.

For further information refer to the Material Safety Data Sheet.

MORE FROM DON CONSTRUCTION PRODUCTS

A wide range of construction chemical products are manufactured by DCP which include:

- » Concrete admixtures.
- » Surface treatments
- » Grouts and anchors.
- » Concrete repair.
- » Flooring systems.
- » Protective coatings.
- » Sealants.
- » Waterproofing.
- » Adhesives.
- » Tile adhesives and grouts.
- » Building products.
- » Structural strengthening.

Don Construction Products Qatar W.L.L

New Industrial Area,
Doha, Qatar
info.qatar@dcp-int.com
www.dcp-int.com

Note:

We endeavour to ensure that any information, advice or recommendation we may give in product literature is accurate and correct. However, because we have no control over where and how products are applied, we cannot accept any liability arising from the use of the products.

www.dcp-int.com

DCP Building Excellence