

Monoseal EX Method Statement

(High performance, high solid acrylic based floor and wall sealer)

Section A : General Comments

Equipment

It is suggested that the following list of equipment is adopted as a minimum requirement:

Protective clothing	: :	Protective overalls Good quality gloves, goggles and face mask
Application equipment	:	Brush, roller, or airless spray machine

Section B : Application

1.0 Surface Preparation

1.1 Ensure that the decorative plaster or coating has fully cured, sound, clean, and free from dust and other contaminants.

2.0 Coating application

2.1 Apply by use of brush, lamb wool roller, or airless spray machine at a rate of 8 - 10 m²/litre.

3.0 Cleaning

3.1 All tools must be cleaned **immediately** after application with **DCP solvent**. If the material sets on the tools, then mechanical cleaning will be required.

4.0 Storage

4.1 Store in a dry area out of direct sunlight between 5°C and 35°C.

5.0 Fire

5.1 **Monoseal EX** is flammable. Ensure adequate ventilation. Do not use near a naked flame and do not smoke during use.

6.0 Caution

- 6.1 **Monoseal EX** should not come in contact with skin and eyes.
- 6.2 In case of accidental splashes to the eyes, rinse thoroughly with clean water and seek medical advice.
- 6.3 Suitable protective gloves and goggles should be worn.





6.4 Do not use solvent to clean **Monoseal EX** from the skin.

Section C : Approval and variations

This method statement is offered by DCP as a 'standard proposal' for the application of **Monoseal EX**. It remains the responsibility of the Engineer to determine the correct method for any given application. Where alternative methods are to be used, these must be submitted to DCP for approval, in writing, prior to commencement of any work. DCP will not accept responsibility or liability for variations to the above method statement under any other condition.

