

Quickmast® 100

Resin based injection crack repair system



DESCRIPTION

Quickmast 100 is a two component, low viscosity epoxy resin system for crack injection applications in concrete, masonry, and brickwork.

APPLICATIONS

- » For injection of cracks in all types of structural concrete elements, masonry, and brickwork.
- » Suitable for injecting cracks widths from 0.2 - 10 mm.
- » Suitable for manual pouring into horizontal floor cracks.

ADVANTAGES

- » Excellent bond strength to concrete, brickwork, and masonry.
- » Low viscosity epoxy resin, formulated to allow cracks penetration down to 0.2 mm.
- » Can be used in damp or dry conditions.
- » Low creep.
- » Non-shrink.
- » Exhibit good chemical resistance.

STANDARDS

Quickmast 100 is suitable for use in contact with potable water when tested in accordance to BS 6920.

METHOD OF USE

Depending on crack width, depth, location, and thickness of the structural element that needs to be injected, many injection techniques requiring different injection tools and equipment may be used.

The method of injection given in this Technical Data Sheet is based on most common situation. For more details, DCP Technical Department should be consulted for assessments and advise.

SUBSTRATE PREPARATION

The surface of the cracks should be cleaned from dust, oil, plaster, grease, curing compound and corrosion deposits. All cracks to be repaired should be cleaned with compressed air. This should be carried out after drilling of injection holes.

TECHNICAL PROPERTIES:

Density:	1.1 ± 0.05 g/ml
Compressive strength: EN 13892-2	≥ 55 N/mm ² @ 7 days @ 20°C
Flexural strength: EN 13892-2	≥ 35 N/mm ² @ 7 days @ 20°C
Pot life:	1 - 2 hr
Minimum application temperature:	5°C
VOC:	< 20 g/ltr

INJECTION HOLES DRILLING & FIXING

Holes are drilled to install mechanical packers. Always try to allocate steel re-bars and conduit before drilling. Using high quality rotary hummer drill, and depending on packer diameter used, a suitable drill pit used, usually 13 mm or 16 mm diameter mechanical packers are used. The angle which drilling should be is 45°C or less to the surface and toward the crack. Depth of the drill holes intersecting the crack should be somewhat close to middle of structure, if possible.

Holes greater than 45 cm are not required even if the concrete being repaired is more than 90 cm thick. Holes should always be staggered from one side of the cracks to the other.

Spacing: distance between drilled holes usually varies from approximately 15 – 50 cm according to width of the cracks (30 cm is commonly used). Yet the wider the cracks, the further apart are drill holes.

Note: If concrete thickness 15 cm or less, do not attempt angle drilling. Also to minimize concrete spalling, packers will be set into the face of the crack.

FIXING OF INJECTION MECHANICAL PACKERS (NIPPLES)

Packers shall be placed in drill holes so that top of the rubber sleeve is below concrete surface. Tight the packer with wrench as much as you can. Mix a small quantity of epoxy adhesive using Quickmast GPS (Fast set). The mix adhesive should be applied on the cracks between the injection packers to seal the cracks at a thickness of 2 – 3 mm and at least 20 – 30 mm extending from both sides of the cracks.

Mixed Quickmast GPS has pot life = 10 – 15 minutes and 30 minutes cure time at 25°C. Injection process can commence 2 hours after applying Quickmast GPS.

Don Construction Products Ltd.

Helions Bumpstead Road, Haverhill CB9
United Kingdom
info.uk@dcp-int.com; info@dcp-int.co.uk
www.dcp-int.com





Quickmast® 100

INJECTION

Mix Quickmast 100, resin and hardener using mechanical slow speed drill when using single component injection pump. When using 2 components pump, the pump should be charged at 4:1 ratio (by volume), which is equivalent to the pre-packed proportion of the base and hardener components.

Load the mixed resin and charge the pump, hose and gun. Begin injection at point of highest resistance to ensure good penetration and minimal loss of materials.

The injection usually starts at the lowest point on vertical crack and at the narrowest area on horizontal surface.

Injection process will continue until the mixed resins (Quickmast 100) travelled to next packer. Disconnect and move to next packer.

After completing two packers, return to first packer and inject again. Continue with this fashion until crack is completely filled.

CLEANING

- » Resins must be cleaned up immediately before it sets.
- » Packers must be removed within 24 - 48 hours and patched with appropriate epoxy mortar using Quickmast 341C.
- » Electrical grinder can be used to remove excess cured resin that flowed out the cracks.

PACKAGING

Quickmast 100 is available in 1.6 kg (1.5 litre) and 5.32 kg (5 litre) packs.

THICKNESSES AND SIZE LIMITATIONS

Quickmast 100 is suitable for injecting cracks widths from 0.2 - 10 mm.

STORAGE

Quickmast 100 has a shelf life of 18 months from date of manufacture if stored at a temperature of 25°C.

If these conditions are exceeded, DCP Technical Department should be contacted for advice.

CAUTIONS

HEALTH AND SAFETY

Consult the appropriate Material Safety Data Sheet prior to using Quickmast 100.

FIRE

Quickmast 100, Quickmast GPS and Quickmast 341C are nonflammable.

MORE FROM DON CONSTRUCTION PRODUCTS

A wide range of construction chemical products are manufactured by DCP which include:

- » Concrete admixtures.
- » Surface treatments
- » Grouts and anchors.
- » Concrete repair.
- » Flooring systems.
- » Protective coatings.
- » Sealants.
- » Waterproofing.
- » Adhesives.
- » Tile adhesives and grouts.
- » Building products.
- » Structural strengthening.

Don Construction Products Ltd.
Helions Bumpstead Road, Haverhill CB9
United Kingdom
info.uk@dcp-int.com; info@dcp-int.co.uk
www.dcp-int.com

Note:

We endeavour to ensure that any information, advice or recommendation we may give in product literature is accurate and correct. However, because we have no control over where and how products are applied, we cannot accept any liability arising from the use of the products.

www.dcp-int.com

DCP Building Excellence



04-0084-UK-A-2024