

Quickmast® Anchor E

Epoxy resin cartridge system for anchoring (Formerly known as Keyfix E)



DESCRIPTION

Quickmast Anchor E is a two component high strength pure epoxy resin anchoring grout pre-packed in dual cartridge system with fast curing rate.

Quickmast Anchor E is formulated for permanent installation of steel reinforcement bars and threaded rods into concrete substrates in structural applications.

APPLICATIONS

Quickmast Anchor E is ideally designed for use in the following applications:

- » Permanent installation of reinforcement starter bars and dowel bars.
- » Permanent installation of hand rails, safety fence, wall ties, railway tracks and ground anchors.

ADVANTAGES

- » Exceptional rapid strength development.
- » Resistant to dynamic loading.
- » Exceptional high compressive.
- » Extremely dense.
- » Exceptional bond to concrete and steel surfaces.
- » Suitable for dry and damp concrete holes.
- » Good chemical resistance.
- » High ultimate and early strengths.

STANDARDS

Quickmast Anchor E complies with the requirements of ASTM C881 as Type I & IV, Grade 3, Class C.

METHOD OF USE

SUBSTRATE PREPARATION

Substrate should be sound, clean and free from grease or any contamination. Bars should be free from any loose rust deposits. Holes can be drilled using a hammer drill to produce a rough surface or by coring to produce a smooth surface. Quickmast Anchor E bond strength will be the same in both cases.

Deformed or ribbed bars will give a higher performance than smooth or other bar types. After drilling, to provide the maximum performance of the anchor, all drilling debris should be removed by brushing and blowing the holes at the following sequence: 2 blows, 2 brushes, 2 blows, 2 brushes then 2 blows.

TECHNICAL PROPERTIES:

| | |
|--|---|
| Consistency: ASTM C881 | Pass (Grade 3) |
| Gel time: ASTM C881 | 40 ± 5 min @ 73°F (23°C) |
| Bond strength: ASTM C882 | ≥ 3000 psi (20.5 MPa) @ 2 days ≥ 3500 psi (24 MPa) @ 14 days |
| Compressive yield strength: ASTM D695 | ≥ 13,000 psi (90 MPa) @ 7 days |
| Linear coefficient of shrinkage on cure: ASTM D2566 | < 0.0003 @ 24 hr |
| Compressive modulus: ASTM D695 | ≥ 500,000 psi (3450 MPa) @ 7 days |
| Heat Deflection Temperature: ASTM D468 | > 120°F (49°C) @ 7 days |
| Water absorption: ASTM D570 | < 0.5% @ 24 hr |
| VOC: ASTM D2369 | ≤ 5 g/ltr (complies with LEED) |

APPLICATION

- » Unscrew the protective cap, remove the insert plug and attach the static mixing nozzle.
- » Insert the cartridge into the cartridge gun and dispense sufficient material until an even colour is achieved.
- » Usually 0.34 fl. oz. (10 ml) of extruded material should be adequate.
- » Insert the nozzle into the base of the hole, apply pressure to the gun and slowly withdraw the nozzle as the hole fills.
- » Normally, it is enough to fill the hole approximately two-third full.
- » Insert the stud/steel bar into the hole with a twisting action, ensuring that is fully embedded.
- » Allow the resin to cure fully before loading.

When filling holes overhead or in porous block work, the use of plastic sleeves is recommended.

Quickmast[®] Anchor E

Partly used cartridge are reusable, Remove the static mixer and surplus base and catalyst components from the cartridge nozzle, insert the plug and screw on the protective cap.

CLEANING

All tools should be cleaned immediately after finishing by DCP Solvent. Hardened materials can be cleaned mechanically.

WORKING AND LOADING TIMES

ESTIMATING

The required quantity of Quickmast Anchor E depends on the hole diameter and depth. Normally, it is enough to fill the hole two-third full.

| Resin Cartridge Temperature | Working Time | Base material temperature | Loading time |
|-----------------------------|--------------|-----------------------------|--------------|
| 50 to 59°F (10 to 15°C) | 20 min | 41 to 50°F (5 to 10°C) | 24 hr |
| | | 50 to 59°F (10 to 15°C) | 12 hr |
| 59 to 68°F (15 to 20°C) | 15 min | 59 to 68°F (15 to 20°C) | 8 hr |
| 68 to 77°F (20 to 25°C) | 11 min | 68 to 77°F (20 to 25°C) | 7 hr |
| 77 to 86°F (25 to 30°C) | 8 min | 77 to 86°F (25 to 30°C) | 6 hr |
| 86 to 95°F (30 to 35°C) | 6 min | 86 to 95°F (30 to 35°C) | 5 hr |
| 95 to 104°F (35 to 40°C) | 4 min | 95 to 104°F (35 to 40°C) | 4 hr |
| +104°F (40°C) | 3 min | +104°F (40°C) | 3 hr |

*Notes: Working time is set at the highest base material temperature in the range.
Loading time is set at the lowest base material temperature in the range.*

Quickmast® Anchor E

DESIGN CONSIDERATION

Table I summarizes the forces that each deformed steel reinforcement bar can withstand at each specified holes depth. These forces were calculated in accordance with EOTA TR023 "Assessment of post-installed rebars connection", considering that the yield strength of the steel is 60900 psi (420 MPa) and the compressive strength of concrete is 3625 psi (25 MPa) cube.

TABLE I

| Bar diameter | | Hole diameter | | Embedded length | | Maximum pull out force* | | Needed quantity of Quickmast Anchor E per hole | |
|--------------|----|---------------|----|-----------------|-----|-------------------------|-----|--|-------|
| Inch | mm | Inch | mm | Inch | mm | lb | kN | fl. oz. | ml |
| 3/8" | 10 | 9/16" | 14 | 3-15/16" | 100 | 7756 | 35 | 0.35 | 10.3 |
| 7/16" | 12 | 5/8" | 16 | 4-3/4" | 120 | 11173 | 50 | 0.45 | 16.1 |
| 5/8" | 16 | 3/4" | 20 | 6-5/16" | 160 | 21694 | 97 | 1.13 | 33.5 |
| 3/4" | 20 | 1" | 25 | 7-7/8" | 200 | 33722 | 150 | 2.21 | 65.4 |
| 1" | 25 | 1-1/4" | 32 | 9-13/16" | 250 | 52965 | 236 | 4.53 | 134.0 |
| 1-1/4" | 32 | 1-9/16" | 40 | 12-5/8" | 320 | 86777 | 386 | 9.06 | 267.9 |

*Maximum pull out force that yield a concrete splitting failure pattern.

PACKAGING

Quickmast Anchor E is available in 20.2 fl. oz (600 ml) twin cartridge system.

STORAGE

Quickmast Anchor E has a shelf life of 24 months from the date of manufacture if stored in its original packaging, the correct way up and in cool dry conditions 50°F - 75°F (10°C - 25°C) out of direct sunlight.

The technical properties and usages of this product may be adversely affected if these conditions are exceeded. Technical Department should be contacted for advise.

CAUTIONS

HEALTH AND SAFETY

Quickmast Anchor E is irritant to eyes, skin and respiratory system. Wear suitable gloves and eye protection.

For further information refer to the Material Safety Data Sheet.

FIRE

Quickmast Anchor E is nonflammable.
DCP Solvent is flammable, do not use near a naked flame and do not smoke during use.

WARRANTY

Unless expressly stated otherwise in the Sales Documents, the Limited Warranty shall expire on the expiry date listed on the Product's label or packaging. The full text of DCP's limited warranty is found in DCP's standard terms and conditions of sale (the "Terms"), which are available at [DCP Website/USA – Terms & Conditions](#). DCP's limited warranty is in all cases subject to, and conditioned upon, the Terms.



Quickmast® Anchor E

MORE FROM DON CONSTRUCTION PRODUCTS

A wide range of construction chemical products are manufactured by DCP which include:

- » Concrete admixtures.
- » Surface treatments
- » Grouts and anchors.
- » Concrete repair.
- » Flooring systems.
- » Protective coatings.
- » Sealants.
- » Waterproofing.
- » Adhesives.
- » Tile adhesives and grouts.
- » Building products.
- » Structural strengthening.

Don Construction Products Inc.

Lancaster, SC 2970, USA

info.usa@dcp-int.com

www.dcp-int.com

Note:

We endeavour to ensure that any information, advice or recommendation we may give in product literature is accurate and correct. However, because we have no control over where and how products are applied, we cannot accept any liability arising from the use of the products.

www.dcp-int.com

DCP Building Excellence