

# Setseal 300C

Flexible acrylic cement modified one component waterproof coating



## Description

Setseal 300C is a one components; flexible polymer modified cementitious waterproof coating suitable for internal and external applications.

Setseal 300C provides a hardwearing, seamless, waterproof membrane for potable water retaining structures, tanks, basements, foundations and culverts.

## Applications

- ▲ Waterproofing for water retaining structures and reservoirs.
- ▲ Waterproofing of basements, roofs, and foundations.
- ▲ Waterproofing of bathrooms and wet areas.
- ▲ Protection of concrete substrates and masonry against carbon dioxide, chloride ions, water and de-icing salts.

## Advantages

- ▲ Single component, need only water additions.
- ▲ Non-toxic, approved for use in contact with potable water.
- ▲ Fungus and mould resistant.
- ▲ Excellent bond to porous and non-porous surfaces.
- ▲ Breathable.
- ▲ Durable, excellent protection against carbon dioxide, chloride ions and water.
- ▲ Cost effective, quick and easy application.
- ▲ Suitable for internal and external applications.

## Standards

Setseal 300C complies with EN 14891, Type CM.

## Method of Use

### Substrate Preparation

The surfaces to be coated should be clean, sound, and free from contamination. Remove any traces of curing compound, laitance, organic growth or any other loose materials.

This is best obtained by using high pressure water or light grit blasting. Substrate containing honey combing, damaged or deteriorated concrete should be repaired using suitable repair mortars from DCP repair systems before coating.

## Technical Properties @ 25°C:

Mixed density:	1.50 ± 0.10 g/cm <sup>3</sup>
Working time:	1 hr
Colour:	Grey
Initial setting time:	4 - 5 hr
Application temperature:	5 to 45°C
Application thickness:	2 mm (with two coats)
Elongation at break: ASTM D412	≥ 20% @ 28 days, 2 mm (@ 5mm/ min speed rate)
Tensile strength: ASTM D412	≥ 1.0 MPa @ 28 days, 2 mm (@ 5mm/ min speed rate)
Compressive strength: ASTM C109	≥ 8.0 MPa @ 28 days (Mortar consistency)
Flexural strength: ASTM C348	≥ 3.0 MPa @ 28 days (Mortar consistency)
Adhesion strength on C35 concrete: ASTM D4541	≥ 2.0 MPa @ 28 days
Water retention: ASTM C309	Pass @ 2 mm
Water permeability: DIN 1048	Nil @ 5 bars

Properties	EN 14891 requirement for Type CM	Measured value
Tensile adhesion strength:*	≥ 0.5 N/mm <sup>2</sup>	Pass
Tensile adhesion strength after water contact:*	≥ 0.5 N/mm <sup>2</sup>	Pass
Tensile adhesion strength after heat aging:*	≥ 0.5 N/mm <sup>2</sup>	Pass
Tensile adhesion strength after freeze-thaw cycles:*	≥ 0.5 N/mm <sup>2</sup>	Pass

# Setseal 300C

## Priming

No special primer is required, but substrate should be pre-soaked with clean water prior to application of Setseal 300C.

## Mixing

To ensure proper mixing, a mechanically powered mixer or drill fitted with suitable paddle should be used. Add the 4.2 litre water to a clean container. The powder component is then added slowly to the water while mixing continuously with low speed mixer/drill (400 - 600 rpm).

Mixing time should be continued for 3 minutes until a uniform consistency is obtained.

## Application

Setseal 300C can be applied by brush or roller. The mixed material should be brushed well into the surface. Strike off with brush in one direction. Care must be taken not to spread the materials too thin.

The first coat should be applied at a wet film thickness of 1mm. When the material begins to drag, do not add any water, but dampen the surface again.

A minimum of 3 - 5 hours, depending on the prevailing ambient temperature, should be given for the first coat to cure before applying the second coat. If the first coat is fully dried, pre-soaking is needed before applying the second coat.

The second coat should be applied in a perpendicular direction to the previous layer to ensure good bond and coverage.

To achieve a smooth finish, it is recommended to finish the surface with a trowel immediately after brushing the second coat. The total dry film thickness for both coats should be 2 mm.

## Remarks

- ▲ Setseal 300C should not be applied to frozen substrates or if ambient temperature is below 5°C or expected to fall below 5°C.
- ▲ The area must not be exposed to moving water during application.

Properties	EN 14891 requirement for Type CM	Measured value
Tensile adhesion strength after contact with lime water:*	$\geq 0.5 \text{ N/mm}^2$	Pass
Waterproofing:	No penetration and $\leq 20 \text{ g}$ water gain	Pass
Crack bridging under standard condition:	$\geq 0.75 \text{ mm}$	Pass

*If C2 tile adhesive (as per ISO 13007) is used in conjunction with Setseal 300C, results greater than  $1.0 \text{ N/mm}^2$  are anticipated.*

- ▲ Setseal 300C can be submerged with water after 5 – 7 days of application depending on ambient temperatures and relative humidity.

## Cleaning

All tools should be cleaned immediately after finishing using clean water. Hardened materials should be cleaned mechanically.

## Packaging

Setseal 300C is available in 15 kg bags.

## Coverage

Approximately  $12.5 - 13 \text{ m}^2/15 \text{ kg}$  for one coat @ 1 mm thickness.

## Storage

Setseal 300C has a shelf life of 12 months from date of manufacture if stored at temperatures range between 5°C and 40°C.

If these conditions are exceeded, DCP Technical Department should be contacted for advise.



# Setseal 300C

## Cautions

### Health and Safety

As Setseal 300C contains Portland cement, Setseal 300C may cause irritation to skin or eyes.

In case of accidental contact with eyes, immediately flush with plenty of water for at least 10 minutes and seek medical advice if necessary.

For further information refer to the Material Safety Data Sheet.

### Fire

Setseal 300C is nonflammable.

## More from Don Construction Products

A wide range of construction chemical products are manufactured by DCP which include:

- ▲ Concrete admixtures.
- ▲ Surface treatments
- ▲ Grouts and anchors.
- ▲ Concrete repair.
- ▲ Flooring systems.
- ▲ Protective coatings.
- ▲ Sealants.
- ▲ Waterproofing.
- ▲ Adhesives.
- ▲ Tile adhesives and grouts.
- ▲ Building products.
- ▲ Structural strengthening.

# Setseal 300C


**Note:**

We endeavor to ensure that any advice, recommendation or information we may give in product literature is accurate and correct. However, due to the fact that we have no direct or continuous control over where or how the products are applied, DCP cannot accept any liability either directly or indirectly arising from the use of DCP products, whether or not in accordance with any advice, specification, recommendation or information given by us.

[www.dcp-int.com](http://www.dcp-int.com)

 expertise

 quality

 full range

08-0079-A-2021