

Setseal C Spray

Flexible acrylic cement modified two component waterproof and protective coating



DESCRIPTION

Setseal C Spray is a two component flexible polymer modified cementitious coating used for waterproofing and protection of concrete structures against carbonation, chloride ions and water.

Setseal C Spray provides a hardwearing, seamless, protective waterproof membrane for potable water retaining structures, tanks, bridges, foundations and culverts.

APPLICATIONS

- » Water retaining structures and reservoirs.
- » Basements, foundations and roofs.
- » Bathrooms, kitchens and wet areas.
- » Bridge abutments.
- » Protection of concrete substrates and masonry against carbon dioxide, chloride ions, water and de-icing salts.

ADVANTAGES

- » Durable, excellent protection against carbon dioxide, chloride ions and water.
- » Exceptional weathering resistance.
- » Non-toxic, approved for use in contact with potable water.
- » Fungus, mould resistant.
- » Low water vapour permeability.
- » Anti-carbonation and durable waterproofing properties.
- » Cost effective, quick and easy brush or spray application.
- » Suitable for internal and external applications.
- » Can be painted.
- » Non-corrosive to steel or iron.

METHOD OF USE

SUBSTRATE PREPARATION

The surfaces to be coated should be clean, sound, and free from any contamination. Remove any traces of curing compound, mold/formwork release agents, laitance, organic growth or any other loose materials. This is best obtained by using high pressure water or light grit blasting.

Honey combing, damaged or deteriorated concrete exists, the substrate should be repaired using suitable low permeability repair mortar from DCP repair systems before commencing the coating.

TECHNICAL PROPERTIES @ 25°C:

Mixed density:	1.8 ± 0.1 g/cm ³
Mixing ratio:	5 kg liquid polymer with 15 kg powder
Working time:	45 min
Minimum application temperature:	5°C
Tensile strength: BS 6319, Part 7	≥ 1.5 MPa @ 7 days ≥ 2.0 MPa @ 28 days
Bond strength: ASTM D4541	≥ 1.2 MPa @ 28 days
Flexural strength: BS 6319, Part 3	≥ 3 MPa @ 7 days ≥ 4 MPa @ 28 days
Resistance to water pressure: DIN 1048	≥ 30 m (3 bars) positive (2 mm thickness)
VOC:	< 10 g/ltr (powder) < 20 g/ltr (liquid)

Note: These results were achieved using sprayable consistency and 2 mm thickness of application.

Notes:

- » Solvent based primers and coatings like Repcoat primer and Setseal A should be removed mechanically before applying Setseal C Spray.
- » For Fair-face concrete, it is recommended to clean and prepare the surface by performing slight mechanical roughening, or applying water jetting to enhance the adhesion of Setseal C Spray and prevent peeling.

PRIMING

No primer is required, but substrates should be pre-soaked with clean water prior to application of Setseal C Spray.

MIXING

To ensure proper mixing, a mechanically powered mixer or drill fitted with suitable paddle should be used.

The 5 kg of Setseal C Spray liquid should be added to a clean container. The 15 kg powder is then added slowly to the liquid while mixing continuously with low speed mixer/drill (400 - 600 rpm). Mixing time should be continued for 3 minutes until a uniform consistency is obtained.

DCP Saudi Co.

Sulay, Industrial Area, Istanbul St., Riyadh
Industrial City 3, Jeddah
Saudi Arabia
info.saudi@dcp-int.com
www.dcp-int.com





Setseal C Spray

APPLICATION

Setseal C Spray can be applied by brush or spray. The mixed material should be brushed well into the surface. Strike off with the brush in one direction. Care must be taken not to spread the material too thin. When the material begins to drag, do not add any water, but dampen the surface again.

Leave the first coat overnight to cure before applying the second coat. If the first coat is left for more than one day or if it is very dry, pre-soaking with clean water is needed before applying the second coat. The second coat shall be applied by brush in a similar way to the first layer but preferably perpendicular to the previous layer to ensure good bond and coverage.

For spray application, a maximum of 1 litre of water may be added to the mix if needed depending on the type of spray machine.

CLEANING

All tools should be cleaned immediately after finishing by clean water. Hardened materials should be cleaned mechanically.

REMARKS

Setseal C Spray should not be applied to frozen substrate or if ambient temperature is below 5°C or expected to fall below 5°C.

PACKAGING

Setseal C Spray is available as 20 kg packs (5 kg polymer & 15 kg powder).

COVERAGE

Approximately 11.5 - 12.5 m²/20 kg for one coat @ 1 mm thickness, depending on the condition of the surface and method of application.

STORAGE

Setseal C Spray has a shelf life of 12 months from date of manufacture if stored at temperatures between 5°C and 35°C.

If these conditions are exceeded, contact DCP Technical Department for advice.

CAUTIONS

HEALTH AND SAFETY

As Setseal C Spray contains Portland cement and sand, Setseal C Spray may cause irritation to skin or eyes. In case of accidental contact with eyes, immediately flush with plenty of water for at least 10 minutes and seek medical advice.

For further information, refer to the Material Safety Data Sheet.

FIRE

Setseal C Spray is nonflammable.

MORE FROM DON CONSTRUCTION PRODUCTS

A wide range of construction chemical products are manufactured by DCP which include:

- » Concrete admixtures.
- » Surface treatments
- » Grouts and anchors.
- » Concrete repair.
- » Flooring systems.
- » Protective coatings.
- » Sealants.
- » Waterproofing.
- » Adhesives.
- » Tile adhesives and grouts.
- » Building products.
- » Structural strengthening.

DCP Saudi Co.

Sulay, Industrial Area, Istanbul St., Riyadh
Industrial City 3, Jeddah
Saudi Arabia
info.saudi@dcp-int.com
www.dcp-int.com

Note:

We endeavour to ensure that any information, advice or recommendation we may give in product literature is accurate and correct. However, because we have no control over where and how products are applied, we cannot accept any liability arising from the use of the products.

www.dcp-int.com

DCP Building Excellence



08-0153-KSA-B-2025