



Method Statement

Ref. #: DCP03/08-0172-A-2023



Setseal CM

(Two-component acrylic cement modified waterproof and protective coating)



Table of Content

SECTION A: GENERAL COMMENTS	3
General Notes	3
High-Temperature Working	3
Low-Temperature Working	3
Tools and Equipment	4
SECTION B: APPLICATION	5
Substrate Preparation	5
Priming	6
Mixing	6
Application	7
Cleaning	8
Remarks	8
SECTION C: CAUTIONS	9
Health & Safety	9
SECTION D: APPROVAL AND VARIATIONS	9



Section A : General Comments

General Notes:

The information below is a detailed overview of the application of DCP's **Setseal CM** waterproofing and protection system and should be read in conjunction with the relevant technical data sheet prior to application. All DCP Products should be applied by experienced specialist contractors.

All the points below assume the correct preparation of the relevant surface.

High-Temperature Working:

It is suggested that, for temperatures above 35°C, the following guidelines are adopted as good working practice:

- i. Unmixed materials and equipment should be stored in a cool shaded area and away from direct sunlight.
- ii. Avoid application during the peak temperature of the day.
- iii. Plan for enough materials, tools, and labor to ensure a continuous applicant process.

Low-Temperature Working:

It is suggested that, for temperatures below 10°C, the following guidelines are adopted as good working practice:

- i. Unmixed materials should be stored at room temperature.
- ii. Cold temperatures will affect the properties of the material.
- iii. Avoid applying the waterproof coating if the temperature is around 5°C and falling.
- iv. Do not apply under rain or snow, and avoid dew points conditions during application.

Tools and Equipment:

It is suggested that the following list of equipment are adopted as a minimum requirement


- | | | |
|----------------------------|---|---|
| <i>Personal protection</i> | <ul style="list-style-type: none"> : Protective overalls : Goggles or a face mask : Good quality gloves : Safety shoes : Safety helmet |  |
| <i>Equipment</i> | <ul style="list-style-type: none"> : Low speed drill fitted with suitable paddle (Fig.1) : Empty bucket (25 litre) (Fig.2) : Brush (Fig.3) : Trowel (Fig.4) | |



Fig.1: Low speed drill fitted with suitable paddle

Fig.2: Empty bucket

Fig.3: Brush




Fig.4: Trowel

Section B : Application

1.0 Substrate Preparation

- 1.1 New concrete or cementitious substrates should be at least 28 days old.
- 1.2 The substrate (new or existing) should be clean, sound, smooth, and free from contamination such as mortar and paint splashes, curing compounds, oil, and grease.
- 1.3 Excess laitance deposits, organic growth, or any other loose materials are best removed by high-pressure water jetting, or light grit blasting.



- 1.4 Any surface imperfections, honeycombing, damaged or deteriorated concrete should be repaired with a suitable cementitious repair mortar. Consult the DCP's Technical Department for specific recommendations.



- 1.5 Repair work should not produce a dusty and flaky finish.
- 1.6 It is recommended to create fillet on corners using sand-cement or repair mortar.
- 1.7 Avoid contact with other substrates that may be affected by spillage or overcoating by applying masking tape.

*Note: It is recommended to test the adhesion between the substrates and **Setseal CM** on a small area onsite prior to proceeding with the works in order to ensure that the substrate is well prepared and compatible with the product.*

2.0 Priming

- 2.1 No special primer is required, but the substrate should be presoaked with clean water to a saturated surface dry (SSD) condition prior to the application of **Setseal CM**.



3.0 Mixing

- 3.1 A mechanically powered mixer or drill fitted with a suitable paddle-type should be used to ensure proper mixing.
- 3.2 Locate the mixer or the mixing container as close as possible to the area of application in order to minimize the transporting time.
- 3.3 For Brushable (slurry) consistency: Full pack of Setseal CM should be used.
- 3.3.1 Place 4.9 kg of the liquid component of **Setseal CM** into a clean container, and add the 20 kg dry powder slowly to the liquid while mixing continuously with a low-speed mixer/drill (200 – 400 rpm).
- 3.4 For Trowable consistency: 90% of the liquid component of Setseal CM should be used.
- 3.4.1 Place 4.41 kg of the liquid component of **Setseal CM** into a clean container, and add the 20 kg dry powder slowly to the liquid while mixing continuously with a low-speed mixer/drill (200 – 400 rpm).
- 3.5 Mixing should be continued for 3 minutes until a uniform consistency and a lump-free mixture are obtained.
- 3.6 Allow the mix to rest for 2 - 3 minutes, and then remix for an additional 1 minute without adding any more liquid.
- 3.7 Mixed **Setseal CM** should be applied to the prepared, dampened surface within its pot life (approximately 45 minutes @ 25°C from the start of mixing), pot life varies after mixing depending on the ambient and material temperature.

Notes:

- *Do not mix part of packs under any condition, as this will change the mixing ratio between the powder and the liquid polymer which will affect the material performance.*
- *Slow speed mixer should be only used.*
- *While mixing, ensure that the mixing blade is kept below the surface of the mix to prevent air entrapment.*
- *Do not mix more than the amount of material to be placed within its working time.*
- *The liquid part of **Setseal CM** should only be used for mixing.*
- *Do not use material from damaged bags.*
- *Do not use additives of any kind.*

4.0 Application

- 4.1 **Setseal CM** can be applied by brush, roller, or spray machines. The mixed material should be worked well into the surface filling all pores and voids.



- 4.2 Care must be taken not to spread the materials too thin.
- 4.3 The first coat should be applied at a wet film thickness of 1 mm. When the material begins to drag, do not add any water, but dampen the surface again.
- 4.4 Work the mix firmly onto the prepared substrate, strike off with the brush in one direction for a neat appearance, and to provide a mechanical key for the second coat.



- 4.5 For trowel applications, the first coat should be applied with a notched trowel and left to cure overnight. Apply the second coat with a flat trowel.
- 4.6 In well-ventilated areas, a minimum of 3 - 5 hours, depending on the prevailing ambient temperature, should be given for the first coat to cure before applying the second coat.
- 4.7 For limited ventilation or at low temperature, allow for 24 – 48 hours before applying the second coat.
- 4.8 If the first coat is left exposed for a long period, it is recommended to wash the surface with water and remove any excess moisture before applying the second coat, in order to ensure a dust-free surface.

- 4.9 Fiber-reinforced mesh or more preferably **AquaProof Tape Flex** can be placed into the first coat and pressed firmly while still wet prior to the application of the second coat to the areas of wall/floor angle connections, cold joints, and cracks.



- 4.10 For brush application, the second coat should be applied in a perpendicular direction to the previous layer to ensure good bond and coverage.
- 4.11 To achieve a smooth finish, it is recommended to finish the surface with a trowel immediately after brushing the second coat.
- 4.12 If a cementitious plaster or cementitious tile adhesive (recommended C2TE grade) is to be applied over **Setseal CM**, finish off the second coat with horizontal brush strokes to give more grip.
- 4.13 Condensation of water may occur in the curing phase of the first coat if **Setseal CM** is applied in closed or badly ventilated areas. In such cases, any standing water has to be removed from the surface.



Coverage of Setseal CM:

Approximately 12 – 13 m² per 24.9 kg pack, for one coat @ 1 mm thickness.

Note: Coverage highly depends on the condition of the surface and the method of application.

5.0 Cleaning

- 5.1 All tools should be cleaned immediately after finishing using clean water.
- 5.2 Hardened materials should be cleaned mechanically.

6.0 Remarks

- 6.1 Confirm availability of mixing equipment.
- 6.2 Check the substrate in advance. Ensure that the substrate is in good condition and clean.
- 6.3 Do not change the product mixing ratio.
- 6.4 No standing water should remain during application.
- 6.5 **Setseal CM** should not be applied onto frozen substrates or if the ambient temperature is around 5°C and falling.
- 6.6 The area must not be exposed to standing or moving water during application.
- 6.7 In confined or unventilated areas, it is typically recommended waiting 5 – 7 days after the application of the second coat, in order to conduct the water ponding test.



Section C : Cautions

Health and safety

Setseal CM may cause irritation to the skin or eyes. Avoid contact with skin or eyes. In case of accidental contact with eyes, immediately flush with plenty of water for at least 10 minutes and seek medical advice if necessary.

Fire:

Setseal CM is nonflammable.

For further information on refer to the Material Safety Data Sheet.

Section D : Approval and Variations

This method statement is offered by DCP as a 'standard proposal' for the application of **Setseal CM**. It remains the responsibility of the Engineer to determine the correct method for any given application. Where alternative methods are to be used, these must be submitted to DCP for approval, in writing, prior to commencement of any work. DCP will not accept responsibility or liability for variations to the above method statement under any other condition.