

Strongcoat Dissipative

Dissipative floor with resistance up to 1×10^9 Ohm



DESCRIPTION

Strongcoat Dissipative is a flow-applied 2 mm thick epoxy resin floor topping with dissipative properties. The system comprises of an epoxy primer, dissipative epoxy base and an epoxy topcoat.

APPLICATIONS

Strongcoat Dissipative has a resistance up to 1×10^9 Ohm. Strongcoat Dissipative is suitable for use in areas where a static dissipative floor is required, such as:

- » Electronic manufacturing facilities.
- » Hospital operation theatres.
- » Hazardous dust and chemical environments.

ADVANTAGES

- » Provide a dissipative floor for static electricity to pass through to earth controlling static electricity.
- » Alternative smooth finish.
- » Hard wearing surface that can be subjected to heavy foot traffic and forklift traffic.
- » Chemical resistant.

METHOD OF USE

SUBSTRATE PREPARATION

The substrate must be clean, dry, even, dense and free from oil, grease, dust and other contaminations. A clean surface will ensure maximum adhesion between the substrate and the coating.

Concrete floors must have a minimum compressive strength of 25 MPa and a maximum concrete relative humidity of 80% (max. moisture content of 4%), relative humidity can be measured by using hygrometers.

Concrete relative humidity should be less than 80% for concrete of 28 days old or more.

SURFACE PREPARATION

Unsound layers and contaminated concrete surfaces must be prepared using mechanical surface removing equipment. In case of areas deeply contaminated by oil or grease, such areas should be treated with hot compressed air.

ELECTRICAL PROPERTIES:

Surface resistance: $\leq 1 \times 10^9$ ohms
ASTM F150-78

PHYSICAL PROPERTIES FOR TOPCOAT:

Mixed density:	1.6 ± 0.1 g/cm ³				
Pot life:	40 - 60 min @ 25°C				
Cure time:	<table><tr><td>Foot traffic</td><td>24 hr @ 25°C</td></tr><tr><td>Vehicular traffic</td><td>48 hr @ 25°C</td></tr></table>	Foot traffic	24 hr @ 25°C	Vehicular traffic	48 hr @ 25°C
Foot traffic	24 hr @ 25°C				
Vehicular traffic	48 hr @ 25°C				
Compressive strength: BS 6319-2	≥ 75 MPa @ 7 days				
Flexural strength: BS 6319-3	≥ 30 MPa @ 7 days				
Tensile strength: BS 6319-7	≥ 12 MPa @ 7 days				
VOC:	< 50 g/ltr				

PHYSICAL PROPERTIES FOR BASECOAT:

Colour:	Black
Mixed density:	1.05 ± 0.05 g/cm ³
Pot life:	1 - 2 hr @ 25°C
Tack free time:	2 - 3 hr @ 25°C

PRIMING

Concrete substrates should be primed with Strongcoat Primer. The primer should be allowed to cure for 24 hours. Use lambs wool roller to apply the primer. More than one coat may be required for highly porous or textured surfaces.

STRONGCOAT DISSIPATIVE BASE COAT

Prior to mixing, stir the two components of Strongcoat Dissipative (base & hardener). The entire contents of the hardener container should be poured into the base container and the two materials mixed thoroughly for at least 3 minutes.

The use of a heavy duty slow speed drill fitted with a mixing paddle is recommended. Application is done by using a suitable short hair roller. Allow to cure for 24 hours at normal conditions before being over coated with the topcoat.

DCP Saudi Co.

Sulay, Industrial Area, Istanbul St., Riyadh
Industrial City 3, Jeddah
Saudi Arabia
info.saudi@dcp-int.com
www.dcp-int.com



Strongcoat Dissipative

STRONGCOAT DISSIPATIVE TOPCOAT

Taking care to ensure that the bottom and sides are thoroughly scraped, transfer the entire contents of the resin and hardener and colour pack into a separate mixing container.

Using a jiffy-type mixer attached to a slow-running electric drill, mix for approximately for 2 minutes. Once the Strongcoat Dissipative hardener, resin and colour pack have been mixed, transfer the entire contents into a Casco or Creteangel-type mixer, taking care to ensure that the bottom and sides are thoroughly scrapped.

Start the mixer and transfer to it the entire contents of the Strongcoat Dissipative filler container, taking care to ensure that these are completely dry and lump-free. Continue mixing for approximately 2 minutes.

Once mixed, the Topcoat should be laid using a V-shape notched trowel or pin leveler at a coverage rate of 3.4 kg/m² to achieve 2.0 mm thickness.

Care should be taken when joining the lanes, to achieve a smooth connection. Good lighting conditions will assist in even application and spotting the poorly covered areas.

It is recommended to mask off edges with tape which is then removed while product is still wet.

After around 10 minutes of laying the topcoat, it should be rolled using a spike roller at right angle to the direction of laying. After further 15 - 20 minutes, a second spike rolling should be done in a perpendicular direction to the first direction.

For more information about the installation and verification of Strongcoat Dissipative refer to the product's Method Statement or contact DCP Technical department.

REMARKS

In lighter colour shades, the product may experience accelerated yellowing over time, even indoors, particularly when exposed to heat from strong lighting (e.g., industrial discharge lamps, fluorescent lamps, metal halide or mercury vapour lamps).

OCCASIONAL SPILLAGE

Chemical Resistance after full cure (7 days @ 25°C)

Organic Acids

Lactic Acid 10%	RS + SS
Oleic Acid sat.	R
Citric Acid 25%	RS
Vinegar 10%	R

Inorganic Bases

Sodium Hydroxide 50%	R
Ammonia Solution 10%	R
Potassium Hydroxide 50%	R

Aqueous Solutions

Sodium Chloride sat	R
Tap Water	R
Chlorinated Water	R
Dead Sea Water	R

Solvents

White Spirit	R
Xylene	R
Toluene	R
Acetone	R

Oils & Fuels

Benzyl Alcohol	R
Brake Fluid	RS
Engine Oil	R
Diesel	R
Kerosene	R
Detergents & Soaps	R

Inorganic Acids

Sulphuric Acid 25%	R
Phosphoric Acid 20%	RS + SS
Hydrochloric Acid 36%	RS + SS
Nitric Acid 10%	R

R: Resistant

RS: Resistant with slight discolouration

SS: Slight softening

DCP Saudi Co.

Sulay, Industrial Area, Istanbul St., Riyadh

Industrial City 3, Jeddah

Saudi Arabia

info.saudi@dcp-int.com

www.dcp-int.com

Strongcoat Dissipative

PACKAGING

Strongcoat Primer: 5 kg packs.
Strongcoat Dissipative Topcoat: 15 kg packs.
Strongcoat Dissipative Base Coat: 5 kg packs.

COVERAGE

Strongcoat Primer: 5 m²/kg @ 200 micron DFT.
Strongcoat Dissipative Base Coat: 7.5 m²/kg @ 125 micron DFT.
Strongcoat Dissipative Topcoat: 3.2 kg/m² @ 2 mm DFT.

Actual coverage can vary depending on the substrate conditions.

STORAGE

Strongcoat Dissipative system has a shelf life of 12 months from date of manufacture if stored at temperatures between 5°C and 30°C.

If these conditions are exceeded, contact DCP Technical Department for advice.

CAUTIONS

HEALTH AND SAFETY

Strongcoat Dissipative and Base should not come into contact with skin and eyes.
In case of contact with eyes, immediately flush with plenty of water and seek medical attention.

For further information, refer to the Material Safety Data Sheet.

DCP Saudi Co.

Sulay, Industrial Area, Istanbul St., Riyadh
Industrial City 3, Jeddah
Saudi Arabia
info.saudi@dcp-int.com
www.dcp-int.com



Strongcoat Dissipative

MORE FROM DON CONSTRUCTION PRODUCTS

A wide range of construction chemical products are manufactured by DCP which include:

- » Concrete admixtures.
- » Surface treatments
- » Grouts and anchors.
- » Concrete repair.
- » Flooring systems.
- » Protective coatings.
- » Sealants.
- » Waterproofing.
- » Adhesives.
- » Tile adhesives and grouts.
- » Building products.
- » Structural strengthening.

DCP Saudi Co.

Sulay, Industrial Area, Istanbul St., Riyadh
Industrial City 3, Jeddah

Saudi Arabia

info.saudi@dcp-int.com

www.dcp-int.com

Note:

We endeavour to ensure that any information, advice or recommendation we may give in product literature is accurate and correct. However, because we have no control over where and how products are applied, we cannot accept any liability arising from the use of the products.

www.dcp-int.com

DCP Building Excellence



05-0048-KSA-A-2026