Supaflo PC560M

High performance early strength concrete hyperplasticiser



Description

Supaflo PC560M is a high performance super plasticising admixture based on polycarboxylic polymers with long chains specially designed to enable the water content of the concrete to perform more effectively.

This effect can be used in high strength concrete and flowable concrete mixes, to achieve highest concrete durability and performance.

Applications

- ▲ Self compacting concrete.
- ▲ Structures with congested reinforcement.
- → High strength and high performance concrete.
- ▲ Pre-cast concrete.
- ▲ Improved cohesion allow for use in mass concrete pours and piling.

Advantages

- ▲ Optimises cement utilization.
- ▲ High density and impermeable concrete through very high water reduction.
- ▲ Improves shrinkage and creep behaviors.
- ▲ Minimises segregation and bleeding problems by improving cohesion.
- ▲ Higher early and ultimate compressive strengths.
- ▲ Increases durability and resistance to aggressive atmospheric conditions thorough reduced permeability.

Compatibility

Supaflo PC560M can be used with all types of Portland cement and cement replacement materials. Supaflo PC560M should not be used in conjunction with other admixtures unless DCP technical department approval is obtained.

Standards

Supaflo PC560M $\,$ complies with IS 9103:1999 and ASTM C494, Type G.

Technical Properties @ 25°C:

Colour: Pale yellow liquid

Specific gravity: 1.06 ± 0.02

pH: 6 - 7

Chloride content: Nil

EN 934-2

Air entrainment: Typically less than 2%

additional air is entrained above control mix at normal

dosages

Method of Use

Supaflo PC560M should be added to the concrete with the mixing water to achieve optimum performance.

An automatic dispenser should be used to dispense the correct quantity of Supaflo PC560M to the concrete mix.

Dosage

The recommended dosage of Supaflo PC560M is 0.3 - 1.8 litre per 100 kg of cementitious materials in the mix, including GGBFS, PFA or microsilica.

Representative trials should be conducted to determine the optimum dosage of Supaflo PC560 to meet the performance requirements by using the materials and conditions in actual use.

Effects of Over Dosage

Overdosage of Supaflo PC560M will cause the following:

- ▲ Significant increase in retardation.
- ▲ Increase in workability.

Ultimate concrete strength will not be adversely affected and will generally be increased provided that proper concrete curing is maintained.

Supaflo PC560M

Cleaning

Clean Supaflo PC560M with fresh cold water.

Packaging

Supaflo PC560M is available in 25 ltr jerrycan and 225 kg drums.

Storage

Supaflo PC560M has a shelf life of 12 months from date of manufacture if stored at temperatures between 2°C and 50°C.

If these conditions are exceeded, DCP Technical Department should be contacted for advice.

Cautions

Health and Safety

Supafl o PC560M is not classified as a hazardous material. Supafl o PC560M should not come into contact with skin and eyes.

In case of contact with eyes, immediately flush with plenty of water and seek medical attention.

For further information, refer to the Material Safety Data Sheet.

Fire

Supaflo PC560M is nonflammable.

More from Don Construction Products

A wide range of construction chemical products are manufactured by DCP which include:

- ▲ Concrete admixtures.
- ▲ Surface treatments
- ▲ Grouts and anchors.
- ▲ Concrete repair.
- ▲ Flooring systems.
- ▲ Protective coatings.
- ▲ Sealants.
- ▲ Waterproofing.
- ▲ Adhesives.
- ▲ Tile adhesives and grouts.
- ▲ Building products.
- ▲ Structural strengthening.

