## Supaflo® PC670

High performance concrete superplasticizer



## **DESCRIPTION**

Supaflo PC670 is a high performance super plasticising admixture based on polycarboxylic ether polymers with long chains specially designed to enable the water content of the concrete to perform more effectively.

This effect can be used in high strength concrete and flowable concrete mixes, to achieve highest concrete durability and performance.

## **APPLICATIONS**

- » High strength and high performance concrete.
- Structures with congested reinforcement.
- » Pre-cast concrete.
- » Improved cohesion allow for use in mass concrete pours and piling.
- » Self compacting concrete.

## **ADVANTAGES**

- » Optimises cement utilization.
- » High density and impermeable concrete through very high water reduction.
- » Improves shrinkage and creep behaviors.
- Minimises segregation and bleeding problems by improving cohesion.
- » Higher early and ultimate compressive strengths.
- Increases durability and resistance to aggressive atmospheric conditions thorough reduced permeability.

## **COMPATIBILITY**

Supaflo PC670 is suitable to use with all types of Portland cement and cement replacement materials. Supaflo PC670 should not be used in conjunction with other admixtures unless DCP technical department approval is obtained.

## **STANDARDS**

Supaflo PC670 complies with IS 9103:1999 and ASTM C494, Type D and G, depending on dosage used.

## **METHOD OF USE**

Supaflo PC670 should be added to the concrete with the mixing water to achieve optimum performance.

An automatic dispenser should be used to dispense the correct quantity of Supaflo PC670 to the concrete mix.

## **TECHNICAL PROPERTIES @ 25°C:**

Colour: Yellowish to brownish liquid

Freezing point: ≈ -1°C

Specific gravity:  $1.09 \pm 0.02$ 

Air entrainment: Typically less than 1.5%

additional air is entrained above control mix at normal

dosages

## **DOSAGE**

The recommended dosage of Supaflo PC670 is 0.5 - 2.0 litre per 100 kg of cementitious materials in the mix, including GGBFS, PFA or microsilica.

Representative trials should be conducted to determine the optimum dosage of Supaflo PC670 to meet the performance requirements by using the materials and conditions in actual use.

## **EFFECTS OF OVER DOSAGE**

Overdosage of Supaflo PC670 will cause the following:

- » Significant increase in retardation.
- » Increase in workability.

Ultimate concrete strength will not be adversely affected and will generally be increased provided that proper concrete curing is maintained.

## CLEANING

Clean Supaflo PC670 with fresh cold water.

## **PACKAGING**

Supaflo PC670 is available in 20 kg pails, 225 kg drums and 1000 litre bulks supply.



# Supaflo® PC670

## **STORAGE**

Supaflo PC670 has a shelf life of 12 months from date of manufacture if stored at temperatures between 2°C and 50°C.

If these conditions are exceeded, contact DCP Technical Department for advice.

## **CAUTIONS**

## **HEALTH AND SAFETY**

Supaflo PC670 is not classified as a hazardous material. Supaflo PC670 should not come into contact with skin and eves.

In case of contact with eyes, immediately flush with plenty of water and seek medical attention.

For further information, refer to the Material Safety Data Sheet.

## **FIRE**

Supaflo PC670 is nonflammable.

## MORE FROM DON CONSTRUCTION PRODUCTS

A wide range of construction chemical products are manufactured by DCP which include:

- Concrete admixtures.
- Surface treatments
- Orouts and anchors.
- » Concrete repair.
- » Flooring systems.
- » Protective coatings.
- » Sealants.
- Waterproofing.
- » Adhesives.
- » Tile adhesives and grouts.
- » Building products.
- » Structural strengthening.

## **Don Construction Chemicals India Private Limited**

Kaveripettai, Thiruvallur Dist., Chennai, Tamil Nadu RIICO Industrial Area, Manda Chomu, Jaipur India

info.india@dcp-int.com; marketing.india@dcp-int.com
www.dcp-int.com

## Note:

We endeavour to ensure that any information, advice or recommendation we may give in product literature is accurate and correct. However, because we have no control over where and how products are applied, we cannot accept any liability arising from the use of the products.