

# TIBMIX

Pre-blended metallic dry shake floor topping



## Description

Tibmix is a non-oxidizing, chemically inert, metallic dry shake floor topping for monolithic floors. The product contains a blend of specially graded aggregates, additives and Ordinary Portland Cements. Tibmix can also be used to suppress steel fibres in concrete floors.

Coloured versions of Tibmix are also available which contain a high quality, durable pigment.

When trowelled into freshly laid concrete, Tibmix produces a dense, tough, abrasion resistant surface suitable for most industrial floors. The product is designed for application either by hand or using automatic spreading equipment.

Abrasion resistance conforms to BS EN 13892-4 AR0,5 (Special Class).

Tibmix should be used in conjunction with Setseal 6 polymer curing membrane/sealer/hardener.

## Standards

TIBMIX complies with EN 13813, Class CT-C80-F10-AR0,5.

## Method of Use

### Base Concrete

The base concrete should be a minimum grade C40 with a cement content no less than 325 kg/m<sup>3</sup> and should be placed in accordance with good concrete practice. The water: cement ratio should be kept to the minimum needed to produce a fully compacted concrete without excess surface water.

Should free water be present at the surface this should be allowed to evaporate or brushed away, before the application of Tibmix.

## Application

Broadcast the Tibmix evenly over the surface of the base concrete. Where manual trowelling is involved, application in two stages is recommended.

The first stage should be to apply two thirds of the coverage rate of Tibmix following removal or evaporation of surface bleed water.

## Technical Properties:

Compressive strength*: EN 13892-2	> 80 MPa @ 28 days
Flexural strength*: EN 13892-2	> 10 MPa @ 28 days
Abrasion resistance: EN 13892-4	AR0,5 (special class)
Slip resistance: EN 13036-4	
	Dry 70 Wet 37
BRE screed test:	0.5 mm

*Using a water addition 2.2 litre per 25 kg of TIBMIX.*

Immediately after this stage Tibmix should be trowelled in, either by hand or using a power float (pan fitted to blades).

Stage two is to apply the remainder of the coverage rate and to repeat trowelling.

For large floor constructions Tibmix can be spread and trowelled satisfactorily in one stage by mechanical means.

When the surface has sufficiently stiffened (usually about two hours from the first trowelling), a second trowelling should be carried out to close any pores and remove surface undulations. Further treatment may be necessary to remove disc marks and to achieve the final finish required.

## Working Conditions

Application of both the Tibmix and Setseal 6 should be carried out in as clean and protected an environment as possible.

## Curing, Hardening and Sealing

After final trowelling is complete, Setseal 6 (see appropriate data sheet) should be applied by spray taking care to avoid any puddling.

# TIBMIX

## Joints

Floor expansion joints should be formed using Quickmast Joint Sealant (see appropriate data sheet).

Saw cut contraction joints may be filled with a polyurethane sealant or if a harder seal is required, Quickmast 104 flexible epoxy resin (see appropriate data sheet).

## Cleaning

All equipment and tools should be rinsed with water immediately after use and then dried.

## Packaging

TIBMIX is available in 25 kg polythene-lined paper bags.

## Coverage

Recommended application rate of 5.4 kg/m<sup>2</sup> depending on application - please contact our Technical Department.

## Storage

TIBMIX has a shelf life of 9 months from date of manufacture if stored under cover, in unopened bags clear of the ground in cool dry conditions, protected from frost and excessive draught.

When stored as above, and used within 9 months of the date shown on the packaging, the activity of the reducing agent added will be maintained and the mixed product will contain no more than 0.0002% (2ppm) soluble chromium (VI) on the total dry weight of the cement.

If these conditions are exceeded, DCP Technical Department should be contacted for advice.

## Cautions

## Health and Safety

For further information refer to the Material Safety Data Sheet.

## More from Don Construction Products

A wide range of construction chemical products are manufactured by DCP which include:

- ▲ Concrete admixtures.
- ▲ Surface treatments
- ▲ Grouts and anchors.
- ▲ Concrete repair.
- ▲ Flooring systems.
- ▲ Protective coatings.
- ▲ Sealants.
- ▲ Waterproofing.
- ▲ Adhesives.
- ▲ Tile adhesives and grouts.
- ▲ Building products.
- ▲ Structural strengthening.

### Note:

We endeavour to ensure that any information, advice or recommendation we may give in product literature is accurate and correct. However, because we have no control over where and how products are applied, we cannot accept any liability arising from the use of the products.

[www.dcp-int.com](http://www.dcp-int.com)



expertise



quality



full range